

This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problem Mailbox.**

THIS PAGE BLANK (USPTO)

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11)

EP 0 763 532 A2

(12)

EUROPEAN PATENT APPLICATION

(43) Date of publication:
19.03.1997 Bulletin 1997/12

(51) Int. Cl.⁶: C07D 277/66, C09K 19/34,
G02F 1/13

(21) Application number: 96113638.9

(22) Date of filing: 26.08.1996

(84) Designated Contracting States:
DE FR GB

(30) Priority: 25.08.1995 JP 239037/95
25.08.1995 JP 239038/95
25.03.1996 JP 93044/96
25.03.1996 JP 93045/96

(71) Applicant: DAI NIPPON PRINTING CO., LTD.
Shinjuku-ku, Tokyo-to (JP)

(72) Inventors:

- Hanna, Junichi
Yokohama-shi, Kanagawa-ken (JP)
- Funabashi, Masahiro
Yokohama-shi, Kanagawa-ken (JP)

- Akada, Masanori,
c/o Dai Nippon Printing Co., Ltd.
Shinjuku-ku, Tokyo-to (JP)
- Ando, Masayuki,
c/o Dai Nippon Printing Co., Ltd.
Shinjuku-ku, Tokyo-to (JP)
- Kosaka, Yozo,
c/o Dai Nippon Printing Co., Ltd.
Shinjuku-ku, Tokyo-to (JP)

(74) Representative: Müller-Boré & Partner
Patentanwälte
Grafinger Strasse 2
81671 München (DE)

(54) Liquid crystalline compound and use thereof

(57) A process for producing a liquid crystalline compound represented by the following general formula (A):





FIG. 1

EP 0 763 532 A2

Description

The present invention relates to a liquid crystalline compound and use thereof. More particularly, the present invention relates to a process for producing a novel liquid crystalline compound, which exhibits liquid crystallinity and, in addition, photoconductivity and fluorescence, and use of the liquid crystalline compound in a liquid crystalline charge transport material.

Liquid crystalline compounds having various structures are known in the art and have been extensively used as a liquid crystal display material.

Materials, wherein a charge transport molecule which serves as a charge transport site are dissolved or dispersed in a matrix material, such as a polycarbonate resin, or materials, wherein a charge transport molecule structure pends as a pendant on a polymer backbone; such as polyvinyl carbazole, are known in the art. These materials have been extensively used as materials for photoconductors in copying machines, printers and the like.

For the above conventional charge transport materials, in the case of dispersive charge transport materials, that the charge transport molecule has high solubility in the polymer as a matrix is preferred from the viewpoint of improving the charge transport capability. In fact, however, bringing the charge transport molecule to a high concentration in the matrix leads to crystallization of the charge transport molecule in the matrix, and, for this reason, the upper limit of the concentration of the charge transport molecule is generally 20 to 50% by weight although it varies depending upon the kind of the charge transport molecule. This means that the matrix not having charge transport capability occupies not less than 50% by weight of the whole material. This in turn raises a new problem that the charge transport capability and response speed of a film formed from the material are limited by the excess matrix present in the material.

On the other hand, in the case of the pendant type charge transport polymer, the proportion of the pendant having charge transport capability can be increased. This polymer, however, involves many practical problems associated with mechanical strength, environmental stability and durability of the formed film, film-forming properties and the like. In this type of charge transport material, the charge transport pendants are locally located in close proximity, and the local proximity portion serves as a stable site in hopping of charges and functions as a kind of trap, unfavorably resulting in lowered charge mobility.

For all the above charge transport materials, electrical properties of such amorphous materials raise a problem that, unlike crystalline materials, the hopping site fluctuates in terms of space, as well as in terms of energy. For this reason, the charge transport depends greatly upon the concentration of the charge transport site, and the mobility is generally about 10^{-6} to 10^{-5} $\text{cm}^2/\text{V}\cdot\text{sec}$ which is much smaller than that of the molecular crystal, 0.1 to 1 $\text{cm}^2/\text{V}\cdot\text{sec}$. Further, the amorphous materials have an additional problem that the charge transport properties depend greatly upon temperature and field strength. This is greatly different from the crystalline charge transport materials.

A polycrystalline charge transport material is a promising material in applications where a charge transport layer having a large area is necessary, because it can form an even charge transport film having a large area. The polycrystalline material, however, is inherently an uneven material from the microscopic viewpoint and involves a problem that a defect formed in the interface of particles should be inhibited.

Accordingly, the present invention aims to solve the above problems of the prior art and to provide a novel charge transport material which simultaneously realizes advantages of the amorphous materials, that is, structural flexibility and evenness in a large area, and advantages of the crystalline materials having molecular orientation and is excellent in high-quality charge transport capability, thin film-forming properties, various types of durability and the like.

An object of the present invention is to provide a novel liquid crystalline compound which exhibits liquid crystallinity and, in addition, photoconductivity and fluorescence and a process for producing the same.

Another object of the present invention is to provide a novel charge transport material which simultaneously realizes advantages of the amorphous materials, that is, structural flexibility and evenness in a large area, and advantages of the crystalline materials having molecular orientation and is excellent in high-quality charge transport capability, thin film-forming properties, various types of durability and the like.

According to one aspect of the present invention, there is provided a process for producing a liquid crystalline compound represented by the general formula (A) described below, comprising the steps of: reacting a compound represented by the general formula (1), described below; with a compound represented by the general formula (2) described below; brominating the reaction product to give a compound represented by the general formula (3) described below; and substituting the bromine atom with an R_2 group.

According to another aspect of the present invention, there is provided a process for producing a liquid crystalline compound represented by the general formula (B) described below, comprising the step of: reacting a compound represented by the general formula (4), described below, with a compound represented by the general formula (5) described below.

According to a further aspect of the present invention, there is provided a process for producing a liquid crystalline compound represented by the general formula (C) described below, comprising the step of: reacting two moles of a compound represented by the general formula (6), described below, with one mole of a compound represented by the general formula (7) described below.

According to a yet further aspect of the present invention, there is provided a process for producing a liquid crystalline compound represented by the general formula (D) described below, comprising the step of: reacting two moles of a compound represented by the general formula (8), described below, with one mole of a compound represented by the general formula (9) described below.

According to a yet further aspect of the present invention, there is provided a liquid crystalline charge transport material which exhibits smectic liquid crystallinity and has a reduction potential relative to a standard reference electrode (SCE) in the range of from -0.3 to -0.6 (V vs. SCE).

According to a yet further aspect of the present invention, there is provided a liquid crystalline charge transport material which exhibits smectic liquid crystallinity and has an oxidation potential relative to a standard reference electrode (SCE) in the range of from 0.2 to 1.3 (V vs. SCE).




Figs. 1, 2, 3 and 4 are cross-sectional views of embodiments where the crystalline charge transport material according to the present invention has been applied to a charge transport layer in an image recording device:

Fig. 5 is a cross-sectional view of an embodiment where the liquid crystalline charge transport material has been applied to a space light modulating device; and

Fig. 6 is a cross-sectional view of an embodiment where the liquid crystalline charge transport material according to the present invention has been applied to a thin film transistor.



Process for producing liquid crystalline compound

The first aspect of the present invention relates to a process for producing a liquid crystalline compound represented by the general formula (A), comprising the steps of: reacting a compound represented by the general formula (1) with a compound represented by the general formula (2); brominating the reaction product to give a compound represented by the general formula (3); and substituting the bromine atom of the compound (3) with an R_2 group:






wherein R_1 and R_2 represent (a) a cyano group, (b) a nitro group, (c) a fluorine atom, or (d) a $C_1 - C_{22}$ straight-chain or branched, saturated or unsaturated, alkyl or alkoxy group attached to the aromatic ring through an oxygen atom, or a sulfur atom, provided that at least one of R_1 and R_2 represents said alkyl or alkoxy group.

The second aspect of the present invention relates to a process for producing a liquid crystalline compound represented by the general formula (B), comprising the step of: reacting a compound represented by the general formula (4) with a compound represented by the general formula (5):






wherein R_1 and R_2 represent (a) a cyano group, (b) a nitro group, (c) a fluorin atom, or (d) a $C_1 - C_{22}$ straight-chain or branched, saturated or unsaturated, alkyl or alkoxy group attached to the aromatic ring through an oxygen atom, or a sulfur atom, provided that at least one of R_1 and R_2 represents said alkyl or alkoxy group; and X and Y are respectively groups which are reacted with each other to form Z selected from a $-COO-$, $-OCO-$, $-N=N-$, $-CH=N-$, $-N=N-$, $-CH_2S-$, $-CH=CH-$, or acetylene group.

The third aspect of the present invention relates to a process for producing a liquid crystalline compound represented by the general formula (C), comprising the step of: reacting 2 moles of a compound represented by the general formula (6) with one mole of a compound represented by the general formula (7):




wherein R_1 is a $C_1 - C_{22}$ straight-chain or branched saturated or unsaturated alkyl or alkoxy group attached to the aromatic ring through an oxygen or sulfur atom.

The fourth aspect of the present invention relates to a process for producing a liquid crystalline compound represented by the general formula (D), comprising the step of: reacting two moles of a compound represented by the general formula (8) with one mole of a compound represented by the general formula (9):



wherein R_1 is a $C_1 - C_{22}$ straight-chain or branched saturated or unsaturated alkyl or alkoxy group attached to the aromatic ring through an oxygen or sulfur atom; and X and Y are respectively groups which are reacted with each other to form Z selected from a $-COO-$, $-OCO-$, $-N=N-$, $-CH=N-$, $-N=N-$, $-CH_2S-$, $-CH=CH-$, or acetylene group.

According to a specific one embodiment of the present invention, there is provided a process for producing a liquid crystalline compound represented by the following general formula (I), comprising the steps of: reacting a 4-alkoxybenzaldehyde with o-aminobenzenethiol to synthesize a 2-(4'-alkoxyphenyl)benzothiazole; brominating the 2-(4'-alkoxyphenyl)benzothiazole to synthesize a 2-(4'-alkoxyphenyl)-6-bromobenzothiazole; and reacting the resultant bromide with an alkanethiol:



wherein R represents a $C_4 - C_{20}$ alkyl group; and R' represents a $C_4 - C_{20}$ alkyl group, provided that the total number of carbon atoms contained in R and R' is 10 or more.

A further preferred embodiment of the production process will be described.

According to the present invention, a 4-alkoxybenzaldehyde is reacted with 1 mole or more, preferably 1.1 to 1.5 moles or more, based on one mole of the 4-alkoxybenzaldehyde, of o-aminobenzenethiol in a solvent suitable for a dehydration reaction (oxidative cyclization), preferably dimethylsulfoxide, at a temperature of 100°C or above, preferably 120 to 160°C , for about 30 min to 2 hr.

In this reaction, the aldehyde group, the amino group, and the thiol group are combined together to form a thiazole ring, thus giving a 2-(4'-alkoxyphenyl)benzothiazole as an intermediate. This reaction can be easily achieved, and the intermediate is produced in a high yield of not less than 90%. The intermediate may be purified before use in the subsequent step or alternatively used in the subsequent step without purification.


The 2-(4'-alkoxyphenyl)benzothiazole is then brominated. In the bromination, the 2-(4'-alkoxyphenyl)benzothiazole is dissolved in a suitable solvent, such as glacial acetic acid, and bromine in an equimolar or slightly excessive molar amount is dropwise added thereto. In this reaction, bromine is easily substituted in the 6-position of the benzothiazole ring to give a 2-(4'-alkoxyphenyl)-6-bromobenzothiazole, and the reaction under mild conditions with heating can give the bromide in a yield of not less than 60%. When this intermediate contains a dibromination product and/or a substance remaining unreacted as impurities, it is preferably purified by recrystallization before use in the subsequent step.

Finally, the above bromide is reacted with an alkanethiol to give a liquid crystalline compound according to the present invention. Since this reaction is an aromatic nucleophilic displacement reaction by taking advantage of a thiolate anion, it is preferably performed in an alkaline atmosphere. For example, a liquid crystalline compound represented by the general formula (I) is produced by suspending an oil dispersion of sodium hydride in an ether; dropwise adding a corresponding alkanethiol to the suspension to produce a sodium salt of the alkanethiol, and reacting the sodium salt with the above bromide in a suitable solvent at a temperature of about 30 to 100°C for 30 min to 2 hr.

According to the process of the present invention, the number of carbon atoms of the alkyl group in the 4-alkoxybenzaldehyde and the alkanethiol is important, and the number of carbon atoms of the alkyl group is preferably not less than 4, preferably 4 to 20 from the viewpoint of developing excellent liquid crystallinity. For the alkanethiol, the number


of carbon atoms of the alkyl group is 4 or more, preferably 4 to 20. These alkyl groups may be somewhat branched. However, in order to develop excellent liquid crystallinity, the alkyl group is more preferably linear with the total number of carbon atoms of R and R' being 10 or more, preferably 12 to 40.

Further, liquid crystalline compounds represented by the following general formula (II) also fall within the scope of the present invention:



wherein R represents C_7H_{15} and R' represents C_6H_{13} , C_8H_{17} , $C_{10}H_{21}$ or $C_{12}H_{25}$.

The above liquid crystalline compounds according to the present invention can be produced in a high yield from a p-alkoxybenzaldehyde, for example, by the following reaction scheme:



wherein R and R' are as defined above and DMI represents N,N'-dimethylimidazolidinone.

The present invention provides a novel liquid crystalline compound which exhibits liquid crystallinity and, in addition, photoconductivity and fluorescence. The novel liquid crystalline compound is useful as a material for a liquid crystal display, a photosensitive material for electrophotography and the like. In particular, the liquid crystalline compound of the present invention has strong fluorescence and, hence, when used as a material for a color liquid crystal display or used in combination with a dichroic dye, can effectively utilize an ultraviolet portion in a backlight source, offering a display image having excellent sharpness and brightness.

Liquid crystalline charge transport material

According to a further aspect of the present invention, there is provided a liquid crystalline charge transport material which exhibits smectic liquid crystallinity and has a reduction potential relative to a standard reference electrode (SCE) in the range of from -0.3 to -0.6 (V vs. SCE). According to a further aspect of the present invention, there is provided a liquid crystalline charge transport material which exhibits smectic liquid crystallinity and has an oxidation potential relative to a standard reference electrode (SCE) in the range of from 0.2 to 1.3 (V vs. SCE).

A liquid crystalline molecule, by virtue of its molecular structure, has self-orientation, and, in the case of charge transport utilizing this molecule as a hopping site, unlike the above molecule dispersive material, the spacial and energy scattering of the hopping site is inhibited, enabling a band-like transport property such as found in a molecular crystal to be realized. This enables a mobility of about 10^{-3} to 10^{-2} $cm^2/V\cdot sec$, that is, a larger mobility than that in the conventional molecular dispersive material, to be realized, and, in addition, the charge transport properties do not depend upon electric field.

In order that the material serves as a hole transport material, the molecule should have a low ionization potential, and, hence, the oxidation potential should be in the range of from 0.2 to 1.3 (V vs. SCE) relative to a standard reference

electrode (SCE). Further, in order that the material serves as an electron transport material, the molecule should have high electron affinity, and, hence, the reduction potential should be in the range of from -0.3 to -0.6 (V vs. SCE). The above requirements are the same as the well known requirements for a charge transport molecule used in the conventional molecule dispersive material.

Preferred liquid crystalline charge transport materials of the present invention will be listed in Tables 1 to 71. Among the charge transport materials listed in these tables, more preferred materials are those which satisfy the above requirements, have (aromatic ring of 6π electron system) n (wherein n is an integer of 1 to 4) cores and exhibit smectic liquid crystallinity, those wherein the aromatic ring of 6π electron system is linked through a carbon-carbon double bond or a carbon-carbon triple bond, and those which has a core of a benzothiazole ring, a benzoxazole ring, a benzimidazole ring, a naphthalene ring, or other aromatic ring of 10π electron system and exhibit smectic liquid crystallinity.

The liquid crystalline charge transport materials according to the present invention are useful for various applications such as photosensors, electroluminescence devices, photoconductors, space modulating devices, and thin film transistors.

The liquid crystalline charge transfer materials according to the present invention can realize high-speed mobility and inhibition of the creation of structural traps. Therefore, high-speed response photosensors may be mentioned as the first application thereof. Next, by virtue of excellent charge transport properties, the liquid crystalline charge transfer materials according to the present invention can be used as a charge transfer layer in electroluminescence devices. Further, since electric field orientation and photoconductivity can be simultaneously switched, they can be used in image display devices.

The application to image display devices will be described as a representative example. In an image display device, when a device comprising a transparent substrate, such as glass, a transparent electrode, such as ITO (indium-tin-oxide), a charge generating layer capable of generating carriers according to exposure, the liquid crystalline charge transport material of the present invention, and a counter electrode (such as a gold electrode) laminated in that order is subjected to imagewise exposure (input image) through the bottom of the device as shown in the schematic diagram, the liquid crystalline charge transport material is aligned according to the exposure, resulting in flow of carriers in the counter electrode (gold electrode). The input image can be reproduced by optical reading of the alignment of the liquid crystal. The larger the smectic properties of the liquid crystal, the longer the storage time of the alignment of the liquid crystal and the longer the storage time of the input information.

Figs. 1 to 3 are explanatory diagrams of embodiments where the liquid crystalline charge transport material according to the present invention has been applied to a charge transport layer in an image recording device. Fig. 1 is a schematic view of a photosensor, an embodiment where the liquid crystalline charge transport material according to the present invention has been applied to a charge transport layer. Use of the photosensor will be described in more detail. As shown in Fig. 3, the device is subjected to pattern exposure from the direction of the above in the drawing while applying a voltage across the upper and lower electrodes 15. Carriers are generated in a pattern form in 14', and charges transported by a charge transport layer 14" are discharged in a space 19 and reach the surface of an information recording layer 11.


The information recording layer is, for example, a liquid crystal/polymer composite layer formed of a composite of a smectic liquid crystal and a polymer. The liquid crystal is aligned in a pattern form in an electric field of accumulated charges and accumulated, enabling optical recording to be performed.

In the embodiment shown in Fig. 4, exposure with a voltage being applied may be carried out in the same manner as described above in connection with the embodiment shown in Fig. 3. The generated charges (image) are accumulated on the top surface of a dielectric layer 20, and the liquid crystal is aligned in a pattern form in an electric field of charges accumulated in the same manner as described above in connection with the embodiment shown in Fig. 3 and accumulated, enabling optical reading to be performed.

Further, the liquid crystalline charge transport material according to the present invention can be used also in a space optical light modulating device schematically shown in Fig. 5. Furthermore, the liquid crystalline charge transport materials of the present invention can also be used as an active layer of a thin film transistor. For example, as shown in Fig. 6, the liquid crystalline material may be disposed on a substrate having thereon source, drain, and gate electrodes.


Thus, the liquid crystalline charge transport materials according to the present invention are useful for various applications such as photosensors, electroluminescence devices, photoconductors, space modulating devices, and thin film transistors.

TABLE 1




No	L	R	Cr	LC
7109	O ₂ N-	-CO-C ₁₀ H ₇ -Si ₂ O ₂ Me ₂ -cy	K?	A58 I
7122	NC-CH=CH-	-C ₄ H ₉	K61.1	A57.7 N113.8 I
7123	NC-CH=CH-	-C ₅ H ₁₁	K61.8	A93.3 N122.2 I
7124	NC-CH=CH-	-C ₆ H ₁₃	K79.7	A113 N120.6 I
7125	NC-CH=CH-	-C ₇ H ₁₅	K70.2	A125 I
7126	NC-CH=CH-	-C ₈ H ₁₇	K59.3	A127.4 I
7127	NC-CH=CH-	-C ₉ H ₁₉	K55	A131 I
7130	C ₅ H ₁₁ -	-C ₉ H ₁₉	K42.5	B65.5 I
7131	C ₇ H ₁₅ -	-C ₇ H ₁₅	K52.5	B68 I
7132	C ₂ H ₅ -OOC-CH=CH-	-C ₄ H ₉	K96.3	S104 S153.9 I
7133	C ₂ H ₅ -OOC-CH=CH-	-C ₅ H ₁₁	K88.8	S88.5 S149.1 I
7134	C ₂ H ₅ -OOC-CH=CH-	-C ₆ H ₁₃	K74.2	S81 S146.2 I
7135	C ₂ H ₅ -OOC-CH=CH-	-C ₇ H ₁₅	K61	S74 S142.5 I
7136	C ₂ H ₅ -OOC-CH=CH-	-C ₈ H ₁₇	K62	S75 S143 I
7137	C ₂ H ₅ -OOC-CH=CH-	-C ₉ H ₁₉	K60	S73 S141.4 I
7138	CH ₃ -O-	-C ₃ H ₇	K51.9	S27.9 A33.6 I
7139	CH ₃ -O-	-C ₄ H ₉	K38.7	S26.2 A36.7 I
7140	CH ₃ -O-	-C ₅ H ₁₁	K38	S23.5 A31.2 I
7141	CH ₃ -O-	-C ₆ H ₁₃	K31.6	S14 A28.7 I
7142	CH ₃ -O-	-C ₇ H ₁₅	K36.1	S23.8 A27.7 N33.6 I
7148	C ₂ H ₅ -O-	-C ₄ H ₉	K49.3	A67.1 I
7149	C ₄ H ₉ -O-	-C ₄ H ₉	K7.4	S76 A96.2 I
7150	C ₄ H ₉ -O-	-C ₅ H ₁₁	K11.3	S53.4 I
7151	C ₄ H ₉ -O-	-C ₆ H ₁₃	K20.8	S54.5 A83.4 I
7152	C ₅ H ₁₁ -O-	-C ₃ H ₇	K36.5	S74 S76.5 I
7153	C ₅ H ₁₁ -O-	-C ₄ H ₉	K59.5	S61.5 S81.2 I
7154	C ₅ H ₁₁ -O-	-C ₅ H ₁₁	K39.5	S54 S84.8 I
7155	C ₅ H ₁₁ -O-	-C ₆ H ₁₃	K40.5	S46.5 S85.5 I

TABLE 2




No	L	R	Cr	LC
7156	C ₅ H ₁₁ -O-	-C ₇ H ₁₅	K35.4	S84.8 I
7157	C ₅ H ₁₁ -O-	-C ₈ H ₁₇	K39.5	S84 I
7158	C ₅ H ₁₁ -O-	-C ₉ H ₁₉	K42.5	S82.5 I
7159	C ₆ H ₁₃ -O-	-C ₈ H ₉	K18.2	S43.4 A74.1 I
7160	C ₆ H ₁₃ -O-	-C ₉ H ₁₉	K35	B87 I
7161	C ₇ H ₁₅ -O-	-C ₃ H ₇	K47	B72 I
7162	C ₇ H ₁₅ -O-	-C ₇ H ₁₅	K53.5	B85.5 I
7163	C ₅ H ₁₁ -CO-	-C ₅ H ₁₁	K75.5	S104.5 I
7164	C ₅ H ₁₁ -CO-	-C ₆ H ₁₃	K80.5	S102 S103 I
7165	C ₅ H ₁₁ -CO-	-C ₇ H ₁₅	K71	S95 S101 I
7166	C ₅ H ₁₁ -CO-	-C ₈ H ₁₇	K87	S95.3 S98 I
7167	C ₅ H ₁₁ -CO-	-C ₉ H ₁₉	K84.5	S93.8 S99.6 I
7168	C ₆ H ₁₃ -CO-	-C ₈ H ₁₇	K72	S101.8 S105.8 I
7169	C ₇ H ₁₅ -CO-	-C ₈ H ₁₇	K86.6	S97 S104.5 I

TABLE 3




No	L	R	Cr	LC
26206	C ₃ H ₇ -	-C ₃ H ₇	K90	P120 P190 I
26207	C ₄ H ₉ -	-C ₄ H ₉	K57	P119 P190 I
26208	C ₅ H ₁₁ -	-C ₅ H ₁₁	K41	P114 P190 I
26209	C ₆ H ₁₃ -	-C ₆ H ₁₃	K55	P184 I
26210	C ₇ H ₁₅ -	-C ₇ H ₁₅	K28	P180 I
26211	C ₈ H ₁₇ -	-C ₈ H ₁₇	K39	P173 I
26212	C ₉ H ₁₉ -	-C ₉ H ₁₉	K45	P165 I
26213	C ₁₀ H ₂₁ -	-C ₁₀ H ₂₁	K62	P160 I
26217	C ₂ H ₅ -	-O-C ₂ H ₅	K166	S182 I
26221	C ₃ H ₇ -O-	-O-C ₃ H ₇	K210	P215 I
26222	C ₄ H ₉ -O-	-O-C ₄ H ₉	K197	P227 I
26223	C ₅ H ₁₁ -O-	-O-C ₅ H ₁₁	K185	P218 I
26224	C ₆ H ₁₃ -O-	-O-C ₆ H ₁₃	K172	P218 I
26225	C ₇ H ₁₅ -O-	-O-C ₇ H ₁₅	K166	P209 I
26226	C ₈ H ₁₇ -O-	-O-C ₈ H ₁₇	K163	P203 I
26227	C ₉ H ₁₉ -O-	-O-C ₉ H ₁₉	K162	P194 I
26228	C ₁₀ H ₂₁ -O-	-O-C ₁₀ H ₂₁	K161	P189 I
26230	CH ₃ -O-	-OOC-C ₂ H ₅	K148	S155 N193 I




No	L	R	Cr	LC
28692	C ₃ H ₇ -	-C ₃ H ₇	K163.3	B171.5 I
28693	C ₄ H ₉ -	-C ₄ H ₉	K36.3	E106.9 S113.4 B179.5 I
28694	C ₅ H ₁₁ -	-C ₅ H ₁₁	K50	B155.9 U
28695	C ₆ H ₁₃ -	-C ₆ H ₁₃	K30	E76.7 S107.9 B182.8 I
28696	C ₇ H ₁₅ -	-C ₇ H ₁₅	K27.7	E82 S100.4 B175.5 I
28697	C ₈ H ₁₇ -	-C ₈ H ₁₇	K58.1	E64.5 S93.4 B178.3 I
28698	C ₉ H ₁₉ -	-C ₉ H ₁₉	K52.6	E75.3 S87.3 B174.1 I

TABLE 4




No	L	R	Cr	LC
22075	$C_6H_{13}-CHMe-ODC-$	$-O-C_{10}H_{21}$	1	K? A? I
22076	$C_2H_5-CHMe-CH_2-ODC-$	$-O-C_{10}H_{21}$	1	K22 A48 I
22077	$C_6H_{13}-CHCF_3-ODC-$	$-O-C_{10}H_{21}$	1	K-13 A-6 I




No	L	R	Cr	LC
8085	$C_6H_{17}-O-$	$-C_5H_{11}$	K36	C44.5 A75 N83.5 I

TABLE 5




No	L	R	Cr	LC
22305	C ₇ H ₁₅ -	-C ₇ H ₁₅	K83.1	C58 N109.5 I
22307	C ₆ H ₁₃ -O-	-C ₅ H ₁₁	K81	A85 N120 I
22309	C ₈ H ₁₇ -O-	-C ₇ H ₁₅	K73	A106.1 N111.3 I
22317	C ₇ H ₁₅ -	-O-C ₇ H ₁₅	K83.1	C58 N109.5 I
22318	C ₈ H ₁₇ -	-O-C ₆ H ₁₃	K70	C73 N109 I
22320	C ₆ H ₁₃ -O-	-O-C ₇ H ₁₅	K82	C88.4 N133.4 I
22321	C ₆ H ₁₃ -O-	-O-C ₈ H ₁₇	K85.1	C89.1 N133.3 I
22322	C ₇ H ₁₅ -O-	-O-C ₇ H ₁₅	K88.9	C94.7 A105.5 N129.8 I
22323	C ₇ H ₁₅ -O-	-O-C ₈ H ₁₇	K82.5	C103.8 A110.7 N132.2 I
22324	C ₇ H ₁₅ -O-	-O-C ₉ H ₁₉	K90.4	C103 A113.8 N128 I
22325	C ₈ H ₁₇ -O-	-O-C ₇ H ₁₅	K84.7	C93.8 A115.7 N129.7 I
22326	C ₈ H ₁₇ -O-	-O-C ₈ H ₁₇	K85.5	C101.8 A119.8 N131 I
22327	C ₈ H ₁₇ -O-	-O-C ₉ H ₁₉	K90	C104.2 A122.4 N131.8 I

TABLE 6




No	L	R	Cr	LC
22328	C ₉ H ₉ -O-	-O-C ₈ H ₇	K87	C106.3 A122.5 N129.8 I
22329	C ₉ H ₉ -O-	-O-C ₈ H ₇	K89.4	C115.5 A125.7 N128.4 I
22333	C ₆ H ₅ -	-CO-C ₆ H ₅	K116	S120 N130 I
22334	C ₁₀ H ₂₁ -O-	-COO-CH(C ₃ H ₇ -/-C ₂ H ₅) ₂	R K<30	A25 I
22337	C ₈ H ₁₇ -O-	-COO-CHMe-C ₆ H ₁₃	R K69.3	A62.1 I
22338	C ₁₀ H ₂₁ -O-	-COO-CHMe-C ₆ H ₁₃	R K60	A20 U
22341	C ₁₀ H ₂₁ -O-	-COO-CH ₂ -CHMe-C ₂ H ₅	1 K85.2	A103.6 I
22342	C ₉ H ₉ -O-	-CH=CH-COO-CHCF ₃ -C ₆ H ₁₃	R K51	CA63 A69 I
22343	C ₁₀ H ₂₁ -O-	-CH=CH-COO-CHCF ₃ -C ₆ H ₁₃	R K50	CA56 A66 I
22344	C ₁₁ H ₂₃ -O-	-CH=CH-COO-CHCF ₃ -C ₆ H ₁₃	R K45	CA52 A61 I
22345	C ₁₀ H ₂₁ -O-	-COO-CHCF ₃ -C ₆ H ₁₃	1 K<-30	A25 I
22346	C ₁₀ H ₂₁ -O-	-COO-CHCF ₃ -C ₆ H ₁₇	1 K?	S6 A13.3 I
22347	C ₁₀ H ₂₁ -O-	-COO-CHCF ₃ -C ₆ H ₁₃	2 K52	A61 I

TABLE 7




No	L	R	Cr	LC
35478	C ₆ H ₅ -O-	-CN	K158	N>300 Z
35479	C ₇ H ₁₅ -O-	-CN	K132	N292 Z
35481	C ₈ H ₁₇ -O-	-CHMe-COS-C ₆ H ₁₃	1 K89.2	C*120 A140.7 I
35482	C ₉ H ₁₉ -O-	-CHMe-COS-C ₆ H ₁₃	1 K86.7	C*125.3 A135.7 I
35483	C ₁₀ H ₂₁ -O-	-CHMe-COS-C ₆ H ₁₃	1 K85.4	C*127.5 A133.6 I
35484	C ₁₁ H ₂₃ -O-	-CHMe-COS-C ₆ H ₁₃	1 K83.3	S112.8 C*128.2 A131.1 I
35485	C ₁₂ H ₂₅ -O-	-CHMe-COS-C ₆ H ₁₃	1 K86.9	S104.8 C*128.6 A129.1 I
35486	C ₁₃ H ₂₇ -O-	-CHMe-COS-C ₆ H ₁₃	1 K81.9	S102.6 C*128.8 I
35487	C ₁₄ H ₂₉ -O-	-CHMe-COS-C ₆ H ₁₃	1 K77.4	S103 C*124.4 I
35488	C ₇ H ₁₅ -O-	-CHMe-COO-CHMe-C ₃ H ₇	5 K98	C*100.8 A141.8 N*151 I
35489	C ₈ H ₁₇ -O-	-CHMe-COO-CHMe-C ₃ H ₇	5 K94.1	C*101.6 A139.1 N*147.9 I
35490	C ₉ H ₁₉ -O-	-CHMe-COO-CHMe-C ₃ H ₇	5 K79.1	C*105.9 A134.1 A#? N*142.8 I
35491	C ₁₀ H ₂₁ -O-	-CHMe-COO-CHMe-C ₃ H ₇	5 K66.9	C*108.4 A#138.6 N*147.9 I
35492	C ₁₁ H ₂₃ -O-	-CHMe-COO-CHMe-C ₃ H ₇	5 K73.3	C*114.1 A#127.5 N*134.3 I
35493	C ₁₂ H ₂₅ -O-	-CHMe-COO-CHMe-C ₃ H ₇	5 K69	C*113.4 A#126.4 N*132.6 I
35494	C ₁₃ H ₂₇ -O-	-CHMe-COO-CHMe-C ₃ H ₇	5 K68.6	C*119.7 A#133.7 N*138.5 I
35495	C ₁₄ H ₂₉ -O-	-CHMe-COO-CHMe-C ₃ H ₇	5 K71.7	C*119.4 A#132.8 N*136.5 I
35496	C ₈ H ₁₇ -O-	-COO-CHCF ₃ -C ₆ H ₁₃	1 K93.5	S147.4 C*150.7 A176.4 I
35497	C ₈ H ₁₇ -O-	-COO-CHCF ₃ -C ₆ H ₁₇	1 K84	S133 C*135.6 A163.8 I
35498	C ₆ H ₁₃ -CHCF ₃ -OOC-	-O-C ₁₀ H ₂₁	1 K?	S10 S75 C*106 A150.5 I


TABLE 8



No	L	R	Cr	LC
46421	C ₆ H ₁₃ -	-C ₅ H ₁₁	K54	S142.5 N178 I




No	L	R	Cr	LC
35500	C ₇ H ₁₅ -	-F	K114.9	S187.9 N229.7 I
35501	C ₇ H ₁₅ -O-	-CN	K136	N304 Z
35502	H ₂ C=CH-COO-C ₆ H ₁₃ -O-	-NO ₂	K134	S>180 Z
35503	C ₆ H ₁₃ -CHCF ₃ -OOC-	-C ₁₀ H ₂₁	1 K49.5	A127.7 I
35504	C ₆ H ₁₃ -CHCF ₃ -OOC-	-O-C ₁₀ H ₂₁	1 K35	S100.4 C*124.5 A152.5 I
35505	C ₆ H ₁₃ -CHCF ₃ -OOC-	-COO-C ₁₀ H ₂₁	1 K40	S96 C*97.7 A123.7 I
35506	C ₆ H ₁₃ -CHCF ₃ -OOC-	-OOC-C ₁₀ H ₂₁	1 K75	S120 C*156.9 A184.2 I
35507	C ₁₀ H ₂₁ -O-	-COO-CHCF ₃ -C ₆ H ₁₃	1 K?	S97 C*120 A151.9 I
35508	C ₆ H ₁₃ -OOC-	-COO-CHCF ₃ -C ₆ H ₁₃	1 K?	S64.1 C*66 A108.4 I




No	L	R	Cr	LC
22447	C ₅ F ₁₁ -CH ₂ -O-	-O-C ₆ H ₁₃	K?	A92 I
22448	C ₅ F ₁₁ -CH ₂ -O-	-O-C ₃ H ₆ -CHMe-C ₂ H ₅	1 K?	C*37 A80 I


TABLE 9



No	L	R	Cr	LC
7534	C ₆ H ₁₇ -	-C ₆ H ₁₃	K39.9	C23 A25.5 I
7538	C ₆ H ₁₃ -O-	-C ₄ H ₉	K68.7	C45.1 A55.8 I
7539	C ₁₀ H ₂₁ -O-	-C ₈ H ₁₇	K57.7	C71.5 A77.3 I
7542	C ₁₀ H ₂₁ -O-	-O-C ₈ H ₁₇	K60.1	C81.7 A89.1 I
7543	C ₈ H ₁₇ -O-	-CO-C ₁₀ H ₂₁	K106.9	C103.8 A120.4 I
7545	C ₁₀ H ₂₁ -O-	-COO-C ₈ H ₁₇	K103.6	A88.2 I
7548	C ₆ H ₁₃ -COO-	-C ₈ H ₁₇	K51.8	A64.3 N49.8 U
7549	C ₆ H ₁₃ -CHF-CH ₂ -O-	-C ₈ H ₁₇	K77.9	A69.6 I




No	L	R	Cr	LC
8788	C ₁₀ H ₂₁ -O-	-C ₄ H ₉	K90.1	A109.9 I




No	L	R	Cr	LC
27629	C ₈ H ₁₇ -	-C ₁₂ H ₂₅	K76.6	C99.4 N128.2 I


TABLE 10



No	L	R	Cr	LC
28106	C ₆ H ₁₇ -	-C ₆ H ₁₇	K77.8	C101.4 N121.8 I




No	L	R	Cr	LC
26603	C ₁₀ H ₂₁ -	-C ₆ H ₁₇	K77.5	C114.9 N123.8 I
26604	C ₁₀ H ₂₁ -	-O-C ₁₀ H ₂₁	K92.2	C132.8 A135.9 N143.4 I




No	L	R	Cr	LC
8726	C ₆ H ₉ -	-C ₆ H ₁₃	K90	A96 N106 I


TABLE 11



No	L	R	Cr	LC
27356	H-	-O-C ₆ H ₅	K211	A207 N240 I
27357	H-	-O-C ₆ H ₁₃	K183	B225 A228 U




No	L	R	Cr	LC
27633	C ₆ H ₅ -	-H	K75	S96 I
27634	C ₆ H ₁₁ -	-H	K65	S106 I
27635	C ₆ H ₁₃ -	-H	K55	S103 I
27636	C ₇ H ₁₅ -	-H	K48	S100 S103 S107 I
27637	C ₈ H ₁₇ -	-H	K42	S102 I
27638	C ₆ H ₅ -O-	-H	K106	S136 I
27639	C ₆ H ₁₁ -O-	-H	K62	S133 I
27640	C ₆ H ₁₃ -O-	-H	K76	S133 I
27641	C ₇ H ₁₅ -O-	-H	K63	S136 I
27642	C ₈ H ₁₇ -O-	-H	K54	S137 I




No	L	R	Cr	LC
8268	C ₆ H ₅ -S-	-Br	K?	I
8269	C ₆ H ₅ -S-	-CN	K30.3	N-63 E
8270	C ₇ H ₁₅ -	-C ₇ H ₁₅	K56	I
8278	C ₇ H ₁₅ -	-COO-C ₂ H ₅	K84	S47 I
8279	C ₆ H ₅ -O-	-COO-C ₂ H ₅	K87	S86 I
8280	C ₆ H ₁₁ -O-	-COO-C ₂ H ₅	K72	S90 I
8281	C ₆ H ₁₃ -O-	-COO-C ₂ H ₅	K60	S82 I
8282	C ₇ H ₁₅ -O-	-COO-C ₂ H ₅	K86	S82 I
8283	C ₈ H ₁₇ -O-	-COO-C ₂ H ₅	K72	S84 I

TABLE 12




No	L	R	Cr	LC
29065	C ₃ H ₇ -	-C ₃ H ₇	K50	S74 I
29066	C ₄ H ₉ -	-C ₄ H ₉	K50	S75 I
29067	C ₅ H ₁₁ -	-C ₅ H ₁₁	K53	S77 I
29068	C ₆ H ₁₃ -	-C ₆ H ₁₃	K51	S82 I
29069	C ₇ H ₁₅ -	-C ₇ H ₁₅	K55	G78 F83 C89 I
29070	C ₈ H ₁₇ -	-C ₈ H ₁₇	K65	G72 F87 C91 I
29071	C ₉ H ₁₉ -	-C ₉ H ₁₉	K64	G62 F91 C95 I
29072	C ₁₀ H ₂₁ -	-C ₁₀ H ₂₁	K71	F95 C96 I
29074	C ₄ H ₉ -	-CO-C ₃ H ₇	K148.3	A155.7 I
29075	C ₅ H ₁₁ -	-CO-C ₄ H ₉	K137.2	A163 I
29076	C ₆ H ₁₃ -	-CO-C ₅ H ₁₁	K138.4	A162 I
29077	C ₇ H ₁₅ -	-CO-C ₆ H ₁₃	K132	C138.9 A161.8
29078	C ₈ H ₁₇ -	-CO-C ₇ H ₁₅	K133	C151 A159.7 I
29079	C ₉ H ₁₉ -	-CO-C ₈ H ₁₇	K129.4	C154.2 A158.7 I
29080	C ₁₀ H ₂₁ -	-CO-C ₉ H ₁₉	K127	C152 I




No	L	R	Cr	LC
5713	Br-	-CO-C ₇ H ₁₅	K116.1	A123.8 I
5719	NC-	-C ₈ H ₁₇	K49.9	A20.8 N22.2 I
5723	NC-	-S-C ₄ H ₉	K32.6	N-52 E
5727	C ₄ H ₉ SiMe ₂ -C ₃ H ₈ -O-	-C ₁₀ H ₂₁	K57	S43 I
5730	C ₄ H ₉ -S-	-CN	K55.7	N5 E
5732	C ₂ H ₅ -O-	-CO-C ₇ H ₁₅	K120.8	A123.1 I
5733	C ₃ H ₇ -O-	-CO-C ₇ H ₁₅	K124.4	A122.8 I
5734	C ₄ H ₉ -O-	-CO-C ₇ H ₁₅	K127.6	A130.9 I
5735	C ₅ H ₁₁ -O-	-CO-C ₇ H ₁₅	K120.5	A127.4 I
5736	C ₆ H ₁₃ -O-	-CO-C ₇ H ₁₅	K120	A129.8 I
5737	C ₇ H ₁₅ -O-	-CO-C ₇ H ₁₅	K113	A127.4 I
5738	C ₈ H ₁₇ -O-	-CO-C ₇ H ₁₅	K109.5	A126.2 I
5739	C ₉ H ₁₉ -O-	-CO-C ₇ H ₁₅	K107.5	A123.8 I
5740	C ₁₂ H ₂₅ -O-	-CO-C ₇ H ₁₅	K100.6	S93.8 A122.2 I


TABLE 13



No	L	R	Cr	LC
36004	C ₅ H ₁₁ -	-C ₅ H ₁₁	K21.5	B88.4 A96.7 I
36005	C ₆ H ₁₃ -	-C ₅ H ₁₁	K22.5	B94.7 A97.2 I
36006	C ₇ H ₁₅ -	-C ₅ H ₁₁	K20.5	B96.2 A99.8 I
36007	C ₈ H ₁₇ -	-C ₅ H ₁₁	K21	B96.8 A99.1 I
36008	C ₉ H ₁₉ -	-C ₅ H ₁₁	K23.7	B97.2 A100.1 I
36009	C ₁₀ H ₂₁ -	-C ₅ H ₁₁	K55	B98.4 I




No	L	R	Cr	LC
27648	C ₄ H ₉ -O-	-H	K128	S150 I
27649	C ₆ H ₁₃ -	-C ₂ H ₅	K56	S155 I
27650	C ₄ H ₉ -O-	-C ₂ H ₅	K102	S180 I
27651	C ₄ H ₉ -O-	-C ₅ H ₁₁	K61	S176 I




No	L	R	Cr	LC
27643	C ₅ H ₁₁ -	-C ₅ H ₁₁	K42.4	C47.9 A62 N97.8 I
27644	C ₅ H ₁₁ -	-CO-C ₄ H ₉	K74.9	A186.8 I


TABLE 14



No	L	R	Cr	LC
25783	C ₆ H ₅ -	-O-C ₆ H ₁₃	K148	A152 N155 I




No	L	R	Cr	LC
25800	C ₆ H ₁₃ -O-	-O-C ₆ H ₁₃	K110.8	C130.6 N161 I
25801	C ₇ H ₁₅ -O-	-O-C ₇ H ₁₅	K109.8	C139.4 N155.8 I
25802	C ₈ H ₁₇ -O-	-O-C ₈ H ₁₇	K107.3	C149 N157.3 I
25803	C ₁₀ H ₂₁ -O-	-O-C ₁₀ H ₂₁	K98.6	C147.4 I
25805	H ₂ C=CH-C ₆ H ₅ -O-	-O-C ₆ H ₅ -CH=CH ₂	K99	A114 N144 I
25806	H ₂ C=CH-C ₉ H ₁₉ -O-	-O-C ₉ H ₁₉ -CH=CH ₂	K92	A145 I




No	L	R	Cr	LC
25816	Me ₃ Si-C ₃ H ₆ -O-	-C ₆ H ₁₃	K96	C109 I
25817	C ₄ H ₉ SiMe ₂ -C ₃ H ₆ -COO-	-C ₆ H ₁₃	K51	C90 I
25818	C ₆ H ₁₃ -	-C ₆ H ₁₃	K68.8	A116.5 N120.1 I
25819	C ₉ H ₁₉ -	-C ₆ H ₁₃	K61	C72.2 A126.8 I
25828	C ₃ H ₇ -O-	-C ₆ H ₁₃	K79	C70 A101 N147.5 I
25841	C ₃ H ₇ -O-	-O-C ₆ H ₁₇	K78	C98 N161 I
25842	C ₄ H ₉ -COO-	-C ₆ H ₁₃	K101.9	C128.5 N149.4 I


TABLE 15




No	L	R	Cr	LC
25843	C ₆ H ₁₃ -COO-	-C ₆ H ₁₃	K73.1	S83.2 C139.3 N148.7 I
25844	C ₆ H ₁₇ -COO-	-C ₆ H ₁₃	K58	S75.8 C146.4 N148.1 I
25845	C ₆ H ₁₇ -COO-	-C ₆ H ₁₇	K59.4	S74.5 S78.5 C148.5 I
25846	C ₁₀ H ₂₁ -COO-	-C ₆ H ₁₃	K74.9	S86.2 C147 I



No	L	R	Cr	LC
26979	C ₆ H ₁₃ -	-C ₆ H ₁₃	K134.2	S166.3 S167.3 I




No	L	R	Cr	LC
26980	C ₄ H ₉ -	-C ₇ H ₁₅	K76	S130 N137 I




No	L	R	Cr	LC
25848	C ₁₀ H ₂₁ -	-O-CH ₃	K95	N154 U
25849	C ₁₀ H ₂₁ -	-O-C ₆ H ₁₃	K43	C53 A142 U
25850	C ₁₀ H ₂₁ -	-O-C ₇ H ₁₅	K54	B64 C110 A143 U
25851	C ₁₀ H ₂₁ -	-O-C ₈ H ₁₇	K59	B73 C120 A146 U
25852	C ₁₀ H ₂₁ -	-O-C ₁₀ H ₂₁	K66	B84 C137 A144.6 I

TABLE 16




No	L	R	Cr	LC
7226	NC-	-C ₆ H ₁₁	K48	A91.5 N113 I
7227	NC-	-C ₈ H ₁₇	K44	A95 N104 I
7235	NC-	-O-C ₆ H ₁₁	K85	A94 N140 I
7243	NC-	-OOC-CH=CH-CH ₃	K139	N259 Z
7244	NC-	-OOC-CH=CH-C ₂ H ₅	K113	N229 Z




No	L	R	Cr	LC
8776	C ₅ H ₁₁ -	-C ₅ H ₁₁	K146.5	E145.5 A163.5 N171.5 I
8777	C ₆ H ₁₃ -	-C ₆ H ₁₃	K138	E135.5 A156.5 I
8778	C ₇ H ₁₅ -	-C ₇ H ₁₅	K125.5	E135.5 A163 I
8779	C ₈ H ₁₇ -	-C ₈ H ₁₇	K123	E129 A156.5 I
8780	C ₉ H ₁₉ -	-C ₉ H ₁₉	K113.5	E110 A148 I
8783	C ₃ H ₇ -O-	-O-C ₃ H ₇	K194	A237 N278 I
8784	C ₄ H ₉ -O-	-O-C ₄ H ₉	K136	E190 A241 N256 I
8785	C ₅ H ₁₁ -O-	-O-C ₅ H ₁₁	K136	E178 A236 N244 I
8786	C ₆ H ₁₃ -O-	-O-C ₆ H ₁₃	K141	E170 A229 I
8787	C ₇ H ₁₅ -O-	-O-C ₇ H ₁₅	K130	E163 N225 I

TABLE 17




No	L	R	Cr	LC
22138	NC-	-O-C ₆ H ₁₁	K128	A122 N156 I
22139	NC-	-O-C ₆ H ₉	K125	A140 N152 I
22140	NC-	-O-C ₁₀ H ₂₁	K125	A146 N149 I
22141	NC-	-O-C ₁₁ H ₂₃	K122.5	A149 I
22142	NC-	-O-C ₁₂ H ₂₅	K123	A151 I
22146	O ₂ N-	-O-C ₆ H ₁₁	K98	A109 N136 I
22147	O ₂ N-	-O-C ₆ H ₉	K94	A127.5 N135 I
22148	O ₂ N-	-O-C ₁₀ H ₂₁	K93	A135 N135.5 I
22149	O ₂ N-	-O-C ₁₁ H ₂₃	K92	A136.5 I
22150	O ₂ N-	-O-C ₁₂ H ₂₅	K92	A136.5 I
22161	C ₆ H ₁₃ -	-CN	K74	A105.9 N131.11




No	L	R	Cr	LC
22168	C ₁₀ H ₂₁ -O-	-CN	K78	R72 A139 N152 I
22169	C ₁₁ H ₂₃ -O-	-CN	K79	A146 N149.5 I
22172	C ₆ H ₁₇ -S-	-CN	K99	A109.5 N129.5 I
22173	C ₉ H ₁₉ -S-	-CN	K107	A122 N127 I
22174	C ₁₀ H ₂₁ -S-	-CN	K100	A128.5 I
22175	C ₁₁ H ₂₃ -S-	-CN	K100	A130.5 I
22176	C ₁₂ H ₂₅ -S-	-CN	K104	A133 I
22181	C ₂ H ₅ -CHMe-C ₅ H ₁₀ -O-	-CN	S K80	A122 N135 I
22182	C ₉ H ₁₉ -O-	-COO-C ₃ H ₆ -SiMe ₂ -C ₄ H ₉	K48	C67 A81 I
22184	C ₆ H ₁₃ -O-	-C ₅ H ₁₁	K81	A84.9 N120 I
22185	C ₆ H ₁₇ -O-	-C ₇ H ₁₅	K73	A106.1 N111.3 I
22186	C ₁₀ H ₂₁ -O-	-C ₄ H ₉ -CHMe-OOC-C ₂ H ₅	1 K22.1	A9.1 I
22187	C ₁₀ H ₂₁ -O-	-O-C ₂ H ₄ -O-C ₄ H ₉	K63	C72.3 N98.3 I
22188	C ₁₀ H ₂₁ -O-	-O-CH ₂ -CHMe-O-C ₂ H ₅	1 K49	C*59 A64 N*73 I

TABLE 18




No	L	R	Cr	LC
22305	C ₇ H ₁₅ -	-C ₇ H ₁₅	K83.1	C58 N109.5 I
22307	C ₆ H ₁₃ -O-	-C ₅ H ₁₁	K81	A85 N120 I
22309	C ₆ H ₁₇ -O-	-C ₇ H ₁₅	K73	A106.1 N111.3 I
22317	C ₇ H ₁₅ -	-O-C ₇ H ₁₅	K83.1	C58 N109.5 I
22318	C ₈ H ₁₇ -	-O-C ₆ H ₁₃	K70	C73 N109 I
22320	C ₆ H ₁₃ -O-	-O-C ₇ H ₁₅	K82	C88.4 N133.4 I
22321	C ₆ H ₁₃ -O-	-O-C ₈ H ₁₇	K85.1	C89.1 N133.3 I
22322	C ₇ H ₁₅ -O-	-O-C ₇ H ₁₅	K88.9	C94.7 A105.5 N129.8 I
22323	C ₇ H ₁₅ -O-	-O-C ₈ H ₁₇	K82.5	C103.8 A110.7 N132.2 I
22324	C ₇ H ₁₅ -O-	-O-C ₉ H ₁₉	K90.4	C103 A113.8 N128 I
22325	C ₈ H ₁₇ -O-	-O-C ₇ H ₁₅	K84.7	C93.8 A115.7 N129.7 I
22326	C ₈ H ₁₇ -O-	-O-C ₈ H ₁₇	K85.5	C101.8 A119.8 N131 I
22327	C ₈ H ₁₇ -O-	-O-C ₉ H ₁₉	K90	C104.2 A122.4 N131.8 I




No	L	R	Cr	LC
35500	C ₇ H ₁₅ -	-F	K114.9	S187.9 N229.7 I
35502	H ₂ C=CH-COO-C ₆ H ₁₂ -O-	-NO ₂	K134	S>180° Z
35503	C ₆ H ₁₃ -CHCF ₃ -OOC-	-C ₁₀ H ₂₁	1 K49.5	A127.7 I
35504	C ₆ H ₁₃ -CHCF ₃ -OOC-	-O-C ₁₀ H ₂₁	1 K35	S100.4 C*124.5 A152.5 I
35505	C ₆ H ₁₃ -CHCF ₃ -OOC-	-COO-C ₁₀ H ₂₁	1 K40	S96 C*97.7 A123.7 I
35506	C ₆ H ₁₃ -CHCF ₃ -OOC-	-OOC-C ₁₀ H ₂₁	1 K75	S120 C*156.9 A184.2 I
35507	C ₁₀ H ₂₁ -O-	-COO-CHCF ₃ -C ₆ H ₁₃	1 K?	S97 C*120 A151.9 I
35508	C ₈ H ₁₇ -OOC-	-COO-CHCF ₃ -C ₆ H ₁₃	1 K?	S64.1 C*66 A108.4 I


TABLE 19



No	L	R	Cr	LC
24420	C ₆ H ₁₃ -	-C ₅ H ₁₁	K44.5	S65 N84 I
24421	C ₆ H ₁₃ -	-C ₆ H ₁₃	K46.5	S36.5 N69.5 I




No	L	R	Cr	LC
8289	C ₆ H ₁₃ -	-O-C ₆ H ₁₃	K107.4	C114.1 I
8290	C ₆ H ₁₃ -	-O-C ₁₀ H ₂₁	K92.8	C116.5 I
8291	C ₆ H ₁₃ -	-OOC-C ₆ H ₁₃	K81.7	C106.7 A110.9 I




No	L	R	Cr	LC
28262	C ₆ H ₁₃ -	-O-C ₆ H ₁₃	K79.5	C155.1 N230.7 I
28263	C ₁₀ H ₂₁ -	-O-C ₁₀ H ₂₁	K80.3	C198.2 I
28265	C ₆ H ₁₃ -	-OOC-C ₆ H ₁₃	K82.3	C199.4 N225.2 I

TABLE 20




No	L	R	Cr	LC
8292	C ₆ H ₁₃ -	-C ₆ H ₁₇	K87.3	S118.6 A186.4 I
8293	C ₆ H ₁₇ -	-C ₆ H ₁₇	K82.4	S92.7 C149 A181.2 I




No	L	R	Cr	LC
8294	C ₆ H ₁₃ -	-C ₆ H ₁₇	K84.6	S119.5 A147.5 I
8295	C ₆ H ₁₇ -	-C ₆ H ₁₇	K34.8	S117.5 A155.2 I

TABLE 21




No	L	R	Cr	LC
25914	C ₅ H ₁₁ -	-H	K76	N56 U
25915	C ₆ H ₁₃ -	-H	K75	S60 N80 I
25916	C ₇ H ₁₅ -	-H	K79	S64 N86 I
25917	C ₁₂ H ₂₅ -	-H	K84	A95 I
25918	C ₂ H ₅ -O-	-H	K120	N165 U
25919	C ₃ H ₇ -O-	-H	K110	N101 U
25920	C ₄ H ₉ -O-	-H	K84	N140 U
25921	C ₅ H ₁₁ -O-	-H	K80	N134 U
25922	C ₆ H ₁₃ -O-	-H	K80.5	N134 U
25923	C ₇ H ₁₅ -O-	-H	K73.5	N149.5 U
25924	C ₈ H ₁₇ -O-	-H	K83	N142.5 U
25925	C ₉ H ₁₉ -O-	-H	K96	A126 I
25926	C ₁₀ H ₂₁ -O-	-H	K99	A126 I
25931	C ₆ H ₁₃ -O-	-F	K97	A198 I
25932	C ₆ H ₁₃ -O-	-Cl	K132	A244 I
25933	C ₆ H ₁₃ -O-	-Br	K135	A239 I
25934	C ₆ H ₁₃ -	-CN	K118	A220 N233 I
25935	C ₅ H ₁₁ -O-	-CN	K142	A246 N265 I
25936	C ₆ H ₁₃ -O-	-CN	K146	A258 N264 I
25937	C ₆ H ₁₃ -O-	-NO ₂	K123	A241 I
25938	C ₁₀ H ₂₁ -	-O-C ₄ H ₉ -SiMe ₂ C ₄ H ₉	K46	C122 E
25943	C ₅ H ₁₁ -	-C ₅ H ₁₁	K93	C123 N164 I
25944	C ₆ H ₁₃ -	-C ₆ H ₁₃	K89	C137 N154 B
25945	C ₆ H ₁₃ -	-C ₁₀ H ₂₁	K66	C168 N172.9 I
25946	C ₇ H ₁₅ -	-C ₇ H ₁₅	K81	C149 N158 I
25947	C ₈ H ₁₇ -	-C ₈ H ₁₇	K78	C151 N152 B

TABLE 22




No	L	R	Cr	LC
25949	C ₂ H ₅ -	-O-C ₇ H ₁₅	K67	A142 N178 I
25952	C ₃ H ₁₁ -	-O-C ₆ H ₁₃	K55	C158 N186 I
25953	C ₃ H ₁₁ -	-O-C ₆ H ₁₇	K80	C167 N182 I
25954	C ₆ H ₁₃ -	-O-C ₄ H ₉	K80.6	C141 N183.5 I
25955	C ₆ H ₁₃ -	-O-C ₇ H ₁₅	K69	A166 N179 I
25956	C ₆ H ₁₃ -	-O-C ₉ H ₁₉	K77	C171 N175 I
25957	C ₇ H ₁₅ -	-O-C ₆ H ₁₇	K79	C174 N178 I
25958	C ₈ H ₁₇ -	-O-C ₇ H ₁₅	K72	A170 N177 I
25960	C ₁₀ H ₂₁ -	-O-C ₇ H ₁₅	K76	C171 N181 B
25961	C ₁₀ H ₂₁ -	-O-C ₈ H ₁₇	K79	C173 I
25962	C ₁₀ H ₂₁ -	-O-C ₁₀ H ₂₁	K78	A154 I
25963	C ₁₂ H ₂₅ -	-O-C ₉ H ₁₉	K74	C169 I
25965	C ₁₀ H ₂₁ -	-COO-CH ₃	K140	A224 I
25966	C ₆ H ₁₃ -	-OOC-C ₆ H ₁₇	K58.2	S68.1 C172.6 N176.1 I
25967	C ₁₀ H ₂₁ -	-OOC-CH ₃	K117	C134 N183 I
25968	C ₁₀ H ₂₁ -	-OOC-C ₂ H ₅	K107	C153 N181 I
25969	C ₁₀ H ₂₁ -	-OOC-CHMe-O-CH ₃	1 K108	C*139 N*140 I
25970	C ₁₀ H ₂₁ -	-OOC-CHMe-O-C ₆ H ₁₃	1 K110	C*121 I
25971	C ₁₀ H ₂₁ -	-OCCO-C ₄ H ₉	K64	C146 A147 N166 I
25972	C ₁₀ H ₂₁ -	-OCCO-C ₇ H ₁₅	K80	C153 N157 I
25974	CH ₃ -O-	-O-C ₆ H ₁₃	K93	A109 N215 I
25977	C ₄ H ₉ -O-	-O-C ₄ H ₉	K145	A156 N222 I

TABLE 23




No	L	R	Cr	LC
27803	NC-	-C ₆ H ₁₃	K128	A169 N199 I
27804	C ₄ H ₉ -	-C ₃ H ₇	K76	A96 N150 I
27805	C ₄ H ₉ -	-C ₄ H ₉	K71	A120 N146 I
27806	C ₄ H ₉ -	-C ₅ H ₁₁	K52	A115 N138 I
27807	C ₄ H ₉ -	-C ₆ H ₁₃	K58	A117 N151 I
27808	C ₆ H ₁₃ -	-C ₂ H ₅	K50	A77 N115 I
27809	C ₆ H ₁₃ -	-C ₃ H ₇	K61	A126 N146 I
27810	C ₆ H ₁₃ -	-C ₄ H ₉	K47	A133 N139 I
27811	C ₆ H ₁₃ -	-C ₅ H ₁₁	K50	A148 N150 I
27812	C ₆ H ₁₃ -	-C ₆ H ₁₃	K50	A145 I
27815	C ₉ H ₁₉ -O-	-C ₄ H ₉	K111	A166 N167 I
27816	C ₉ H ₁₉ -O-	-C ₆ H ₁₃	K108	C130 N169 I
27817	C ₁₀ H ₂₁ -O-	-C ₆ H ₁₃	K105	C122 N165 I
27818	C ₁₀ H ₂₁ -O-	-C ₇ H ₁₅	K87	C143 A169 I
27819	C ₁₂ H ₂₅ -O-	-C ₆ H ₁₃	K58	C136 A146 I
27820	C ₄ H ₉ -CMe ₂ -C ₄ H ₉ -O-	-C ₆ H ₁₃	K93	C101 A111 N112 I
27821	C ₄ H ₉ -CMe ₂ -C ₆ H ₁₃ -O-	-C ₆ H ₁₃	K90	C117 A129 N129 I
27823	C ₆ H ₁₃ -O-CHMe-COO-	-C ₂ H ₅	K75	A61 I
27824	H ₂ C/CH ₂ \CH-C ₁₁ H ₂₃ -O-	-C ₅ H ₁₁	K111	C113 A156 N157 I




No	L	R	Cr	LC
28262	C ₆ H ₁₃ -	-O-C ₄ H ₉	K79.5	C155.1 N230.7 I
28263	C ₁₀ H ₂₁ -	-O-C ₁₀ H ₂₁	K80.3	C198.2 I
28265	C ₆ H ₁₃ -	-OOC-C ₆ H ₁₃	K82.3	C199.4 N225.2 I


TABLE 24



No	L	R	Cr	LC
32163	H-	-O-C ₆ H ₁₁	K105	S126 I
32165	C ₆ H ₁₃ -	-O-C ₆ H ₉	K68	S115 N165 I
32166	C ₆ H ₁₃ -	-O-C ₆ H ₁₁	K83	S167 N177 I
32167	C ₆ H ₉ -O-	-O-C ₆ H ₉	K103	S117 N210 I
32168	C ₆ H ₉ -O-	-O-C ₆ H ₁₁	K105	S141 N195 I
32170	C ₆ H ₁₃ -O-	-O-C ₆ H ₁₁	K95	S145 N199 I




No	L	R	Cr	LC
32162	C ₆ H ₁₃ -	-C ₆ H ₉	K56	C89 A123 I




No	L	R	Cr	LC
27671	C ₆ H ₁₃ -	-H	K82	S128 I
27672	C ₆ H ₁₃ -O-	-H	K95	S152 I
27673	C ₆ H ₉ -	-C ₆ H ₁₁	K47	S143 I

TABLE 25




No	L	R	Cr	LC
8296	C ₆ H ₁₃ -	-C ₆ H ₁₇	K50.9	A126.6 I
8297	C ₁₀ H ₂₁ -	-C ₆ H ₁₇	K37.1	A128.7 I
8299	C ₆ H ₁₃ -CHF-	-C ₆ H ₁₇	1 K63.4	A132.9 I




No	L	R	Cr	LC
37286	C ₃ H ₇ -	-C ₇ H ₁₅	K95.5	S88 G99.5 C118 A154 N174.5 I
37287	C ₃ H ₇ -	-C ₁₀ H ₂₁	K76.5	S94.5 S95.5 C120.9 A159.7 N164.4 I
37288	C ₄ H ₉ -	-C ₉ H ₁₉	K81	S87 S98 C102 A103 N164 I
37289	C ₅ H ₁₁ -	-C ₇ H ₁₅	K50	G101 C105 A173 N176 I
37290	C ₅ H ₁₁ -	-C ₁₀ H ₂₁	K69.2	S98.4 S107.3 S119.9 S170.6 I
37291	C ₆ H ₁₃ -	-C ₇ H ₁₅	K52	G83 C126 A159 N166 I
37292	C ₇ H ₁₅ -	-C ₇ H ₁₅	K50	G101 B133 A173 I
37293	C ₈ H ₁₇ -	-C ₇ H ₁₅	K62	G94 B134 A172 I
37294	C ₅ H ₁₁ -	-CHMe-C ₂ H ₅	2 K55.1	S103.8 A114.7 N120.6 I


TABLE 26



No	L	R	Cr	LC
36949	C ₃ H ₇ -O-	-C ₇ H ₁₅	K94	C136 A144 N153 I
36950	C ₄ H ₉ -O-	-C ₇ H ₁₅	K68	C144 A147 N154 I
36951	C ₄ H ₉ -O-	-C ₁₁ H ₂₃	K90	C145 A155 I
36952	C ₆ H ₁₃ -O-	-C ₇ H ₁₅	K68	C103 A171 I




No	L	R	Cr	LC
37296	C ₂ H ₅ -	-C ₉ H ₁₉	K76	G94 C117 A124 I
37297	C ₃ H ₇ -	-C ₉ H ₁₉	K83	G105 C112 A130 I
37298	C ₄ H ₉ -	-C ₉ H ₁₉	K72	G110 C119 A142 I




No	L	R	Cr	LC
26651	C ₈ H ₁₇ -O-	-O-C ₈ H ₁₇	K?	G259 C339.5 N344 I
26652	C ₁₂ H ₂₅ -O-	-O-C ₁₂ H ₂₅	K?	H235 C308 I
26653	C ₁₆ H ₃₃ -O-	-O-C ₁₆ H ₃₃	K?	H229 F272 C290 I

TABLE 27




No	L	R	Cr	LC
26625	Cl-	-Cl	K298	C258 N313 I
26628	C ₄ H ₉ -	-C ₄ H ₉	K145	C166 N244 I
26629	C ₆ H ₁₃ -	-C ₆ H ₁₃	K142	E135 C194 N225 I
26633	C ₄ H ₉ -O-	-O-C ₄ H ₉	K197.7	C210.6 N294.2 I
26634	C ₅ H ₁₁ -O-	-O-C ₅ H ₁₁	K179.8	I224.1 C270.7 I
26635	C ₆ H ₁₃ -O-	-O-C ₆ H ₁₃	K167.4	I232.6 C262.7 I
26636	C ₇ H ₁₅ -O-	-O-C ₇ H ₁₅	K160.7	I236.1 C250.3 I
26637	C ₈ H ₁₇ -O-	-O-C ₈ H ₁₇	K153.1	I237.1 C244 I
26638	C ₉ H ₁₉ -O-	-O-C ₉ H ₁₉	K147.6	I233.7 I
26639	C ₁₀ H ₂₁ -O-	-O-C ₁₀ H ₂₁	K140.6	I226.8 I
26640	C ₁₂ H ₂₅ -O-	-O-C ₁₂ H ₂₅	K129	I221.1 I




No	L	R	Cr	LC
43323	C ₄ H ₉ -	-C ₄ H ₉	K319	S340 A? Z

TABLE 28




No	L	R	Cr	LC
3978	C ₆ H ₁₃ -O-	-S-C ₅ H ₁₁	K24	A71.5 I
3979	C ₆ H ₁₃ -O-	-S-C ₆ H ₁₃	K30	A74.5 I
3980	C ₆ H ₁₃ -O-	-S-C ₇ H ₁₅	K39.5	A72.5 I
3981	C ₆ H ₁₃ -O-	-S-C ₈ H ₁₇	K27	A73 I
3982	C ₆ H ₁₃ -O-	-S-C ₉ H ₁₉	K42.5	A72 I
3983	C ₆ H ₁₃ -O-	-S-C ₁₀ H ₂₁	K31.5	A71.5 I
3984	C ₇ H ₁₅ -O-	-S-CH ₃	K62.5	A73 I
3985	C ₇ H ₁₅ -O-	-S-C ₆ H ₁₃	K40	A74.5 I
3986	C ₇ H ₁₅ -O-	-S-C ₇ H ₁₅	K41	C42 A73 I
3987	C ₇ H ₁₅ -O-	-S-C ₁₀ H ₂₁	K53	A71 I
3988	C ₇ H ₁₅ -O-	-S-C ₁₁ H ₂₃	K61	A69.5 I
3989	C ₈ H ₁₇ -O-	-S-C ₆ H ₁₃	K47	A76 I
3990	C ₈ H ₁₇ -O-	-S-C ₇ H ₁₅	K39	G34 C51 A75 I
3991	C ₈ H ₁₇ -O-	-S-C ₈ H ₁₇	K51	G40 C55 A75 I
3992	C ₈ H ₁₇ -O-	-S-C ₉ H ₁₉	K47.6	G40.5 C54.5 A74.1 I
3993	C ₈ H ₁₇ -O-	-S-C ₁₀ H ₂₁	K54.8	G42.2 C59.7 A74 I
3994	C ₈ H ₁₇ -O-	-S-C ₁₁ H ₂₃	K61.4	C53.4 A74.5 I
3995	C ₉ H ₁₉ -O-	-S-CH ₃	K73	A77.5 I
3996	C ₉ H ₁₉ -O-	-S-C ₆ H ₁₃	K48	A76 I
3997	C ₉ H ₁₉ -O-	-S-C ₈ H ₁₇	K52	G38.1 C58 A75.8 I
3998	C ₉ H ₁₉ -O-	-S-C ₉ H ₁₉	K48.5	G38.5 C57 A74.8 I
3999	C ₉ H ₁₉ -O-	-S-C ₁₀ H ₂₁	K54.7	G42.2 C59.7 A73.9 I
4000	C ₉ H ₁₉ -O-	-S-C ₁₁ H ₂₃	K60	C54.7 A73.4 I
4001	C ₁₀ H ₂₁ -O-	-S-C ₆ H ₁₃	K56	A76.5 I
4002	C ₁₀ H ₂₁ -O-	-S-C ₉ H ₁₉	K58.8	G54 C69.3 A75.7 I
4003	C ₁₀ H ₂₁ -O-	-S-C ₁₀ H ₂₁	K62.1	G57.8 C71 A75 I
4004	C ₁₀ H ₂₁ -O-	-O-C ₁₁ H ₂₃	K62	S58.6 C70.9 A74.8 I
4005	C ₁₁ H ₂₃ -O-	-S-C ₁₀ H ₂₁	K64.5	G61.8 C73.9 A75 I
4006	C ₁₁ H ₂₃ -O-	-O-C ₁₁ H ₂₃	K65	S63 C74.2 A74.7 I
4016	C ₆ H ₁₃ -S-	-C ₆ H ₁₃	K50	A57.5 I

TABLE 29




No	L	R	Cr	LC
4017	C ₄ H ₉ -S-	-S-C ₆ H ₁₃	K42.5	A42 I
4018	C ₆ H ₁₃ -S-	-S-C ₆ H ₁₃	K40	A48.5 I
4019	CH ₃ -CMe ₂ -C ₅ H ₁₀ -O-	-C ₆ H ₁₇	K73	C64 A71 W
4020	CH ₃ -CMe ₂ -C ₅ H ₁₀ -O-	-O-C ₉ H ₁₉	K86	C80 A82 W
4021	CH ₃ -CMe ₂ -C ₅ H ₁₀ -O-	-S-C ₁₀ H ₂₁	K60	C53 A55 W
4023	C ₆ H ₁₃ -O-C ₂ H ₄ -O-C ₂ H ₄ -O-	-O-C ₉ H ₁₉	K48	A44 I
4028	C ₅ H ₁₁ -COO-	-C ₆ H ₁₃	K79	B85.5 A95 I
4030	C ₁₀ H ₂₁ -O-	-O-CH ₂ -CHMe-C ₂ H ₅	S K63	A69 I
4031	C ₆ H ₁₇ -	-O-C ₃ H ₆ -CHMe-C ₂ H ₅	1 K51.8	A55 I
4032	C ₁₀ H ₂₁ -O-	-O-C ₃ H ₆ -CHMe-C ₂ H ₅	1 K63	C*57.5 A82 I
4033	C ₁₀ H ₂₁ -O-	-O-C ₂ H ₄ -CHMe-C ₃ H ₆ -CHMe-CH ₃	1 K45	C*37 A58 I
4034	C ₆ H ₁₇ -	-O-C ₅ H ₁₀ -CHMe-C ₂ H ₅	1 K46	C*35 A60 I
4035	C ₆ H ₁₇ -O-	-C ₅ H ₁₀ -CHMe-C ₂ H ₅	S K36	S46 C*55 A71 I
4036	C ₁₀ H ₂₁ -O-	-O-C ₅ H ₁₀ -CHMe-C ₂ H ₅	1 K77	C*76 A86 I
4037	C ₆ H ₁₇ -O-	-S-C ₅ H ₁₀ -CHMe-C ₂ H ₅	S K55.8	S24 C*55.6 A64.3 I
4041	C ₅ H ₁₁ -	-S-CF ₂ -H	K50.8	N-17 E
4042	C ₁₀ H ₂₁ -O-	-O-C ₉ H ₁₉ -CH/CH ₂ \CH ₂	K88	S70.6 C84 A87.6 I
4049	CH ₃ -CHMe-CHF-COO-	-O-C ₉ H ₁₉ -CH/CH ₂ \CH ₂	S K78	A64 I
4051	C ₂ H ₅ -CHMe-CH ₂ -O-	-C ₆ H ₁₇	1 K51	A66 I
4053	C ₂ H ₅ -CHMe-CH ₂ -O-	-O-C ₁₀ H ₂₁	1 K82	A63 I
4055	C ₂ H ₅ -CHMe-C ₃ H ₆ -O-	-C ₁₂ H ₂₅	1 K46	A62 I
4056	C ₂ H ₅ -CHMe-C ₃ H ₆ -O-	-S-C ₆ H ₁₇	2 K24	C36 A49.8 I
4058	C ₂ H ₅ -CHMe-C ₅ H ₁₀ -O-	-C ₆ H ₁₇	S K40.2	G*43.4 C*57.8 A72.3 I
4059	C ₂ H ₅ -CHMe-C ₅ H ₁₀ -O-	-C ₁₂ H ₂₅	1 K57.1	C*58 A68 I
4060	C ₂ H ₅ -CHMe-C ₅ H ₁₀ -O-	-O-C ₆ H ₁₇	1 K73	C*78 A86 I
4061	C ₂ H ₅ -CHMe-C ₅ H ₁₀ -O-	-O-C ₉ H ₁₉	S K77.7	C*79.2 A84.7 I
4062	C ₂ H ₅ -CHMe-C ₅ H ₁₀ -O-	-S-C ₆ H ₁₃	S K46	C*51.5 A63 I
4063	C ₂ H ₅ -CHMe-C ₅ H ₁₀ -O-	-S-C ₇ H ₁₅	S K44.6	C*52.5 A59.8 I
4064	C ₂ H ₅ -CHMe-C ₅ H ₁₀ -O-	-S-C ₆ H ₁₇	1 K43	C*55 A60 I
4065	C ₂ H ₅ -CHMe-C ₅ H ₁₀ -O-	-S-C ₉ H ₁₉	S K28.1	C*53.5 A60.5 I

TABLE 30




No	L	R	Cr	LC
4178	Me ₃ Si-C ₆ H ₁₀ -O-	-O-C ₆ H ₁₇	K69	C88 A93 E
4179	Me ₃ Si-C ₆ H ₁₂ -O-	-C ₆ H ₁₇	K25	C47 A56.6 I
4180	Me ₃ Si-C ₁₀ H ₂₀ -O-	-O-C ₆ H ₁₇	K41	C84 A92 E
4181	Me ₃ Si-C ₁₁ H ₂₂ -O-	-C ₆ H ₁₇	K56.7	C63.8 I
4182	Me ₃ Si-C ₁₁ H ₂₂ -O-	-O-C ₆ H ₁₇	K70	C92 E
4183	C ₄ H ₉ SiMe ₂ -C ₃ H ₈ -O-	-O-C ₆ H ₁₇	K45	C65 A68 E
4184	C ₄ H ₉ SiMe ₂ -C ₄ H ₈ -O-	-C ₆ H ₁₇	K16.7	C22.3 A25.9 I
4185	C ₄ H ₉ SiMe ₂ -C ₄ H ₈ -O-	-O-C ₆ H ₁₇	K16.5	C63.1 A64 I
4186	C ₄ H ₉ SiMe ₂ -C ₅ H ₁₀ -O-	-O-C ₆ H ₁₇	K38	C74 A82 E
4187	C ₄ H ₉ SiMe ₂ -C ₆ H ₁₂ -O-	-O-C ₆ H ₁₇	K22	C72 A78.5 E
4188	EtMe ₂ Si-C ₄ H ₈ -O-	-C ₆ H ₁₇	K35.2	C30.6 A32.3 I
4189	EtMe ₂ Si-C ₄ H ₈ -O-	-O-C ₆ H ₁₇	K49.4	C71 A71.3 I
4190	EtMe ₂ Si-C ₆ H ₁₂ -O-	-C ₆ H ₁₇	K22.6	C41.6 A50.4 I
4191	EtMe ₂ Si-C ₆ H ₁₂ -O-	-O-C ₆ H ₁₇	K38.6	C78 A84 I
4192	EtMe ₂ Si-C ₁₁ H ₂₂ -O-	-C ₆ H ₁₇	K45.7	C58.6 A58.9 I
4211	C ₅ H ₁₁ -	-CN	K94	A93.5 N109 I
4212	C ₆ H ₁₃ -	-CN	K86.5	A101.5 N103 I
4213	C ₇ H ₁₅ -	-CN	K96.5	A109 I
4214	C ₉ H ₁₉ -	-CN	K90	A107 I
4219	C ₅ H ₁₁ -O-	-CN	K97	A102.5 N133 I
4220	C ₆ H ₁₃ -O-	-CN	K93.5	A121 N134 I
4221	C ₇ H ₁₅ -O-	-CN	K102.5	A127 N129.5 I
4222	C ₈ H ₁₇ -O-	-CN	K102	A133 I
4223	C ₉ H ₁₉ -O-	-CN	K?	X? I

TABLE 31




No	L	R	Cr	LC
4229	C ₆ H ₁₃ -OCOO-	-CN	K83	A96 N121
4230	C ₆ H ₁₇ -O-	-O-C ₆ H ₁₇ -SiMe ₃	K38.7	C64.5
4231	C ₆ H ₁₇ -O-	-O-C ₁₁ H ₂₂ -SiMe ₃	K69.4	C92
4232	C ₁₂ H ₂₅ -O-	-O-C ₁₁ H ₂₂ -SiMe ₃	K81.6	C89.9
4233	C ₆ H ₁₇ -O-	-O-C ₆ H ₉ -SiMe ₂ C ₆ H ₉	K36.4	A30.6 N30.7
4234	C ₆ H ₁₇ -O-	-O-C ₆ H ₁₂ -SiMe ₂ Et	K28.7	C56
4235	C ₁₂ H ₂₅ -O-	-O-C ₁₁ H ₂₂ -SiMe ₂ Et	K75.4	C84.9
4236	C ₅ H ₁₁ -	-C ₆ H ₁₃	K10	A26.5
4237	C ₅ H ₁₁ -	-C ₇ H ₁₅	K30.6	S47.7
4239	C ₆ H ₁₃ -	-C ₇ H ₁₅	K21.1	A47.3
4240	C ₆ H ₁₃ -	-C ₆ H ₁₇	K20.5	A48.4
4241	C ₇ H ₁₅ -	-C ₆ H ₁₃	K15	A29
4242	C ₇ H ₁₅ -	-C ₆ H ₁₇	K23.4	A50.3
4243	C ₇ H ₁₅ -	-C ₅ H ₉	K41.1	F24 A59.7
4244	C ₇ H ₁₅ -	-C ₁₀ H ₂₁	K29.8	F33.8 C43.3 A60.6
4245	C ₇ H ₁₅ -	-C ₁₁ H ₂₃	K39.2	F48.4 C53.5 A64.7
4246	C ₇ H ₁₅ -	-C ₁₂ H ₂₅	K41.4	F53.8 C58 A65.2
4247	C ₇ H ₁₅ -	-C ₁₄ H ₂₉	K38.5	F62.7 A67.2
4248	C ₆ H ₁₇ -	-C ₆ H ₁₃	K18	A29.5
4249	C ₆ H ₁₇ -	-C ₇ H ₁₅	K18.5	A48.1
4250	C ₆ H ₁₇ -	-C ₆ H ₁₇	K31.5	A50.2
4251	C ₆ H ₁₇ -	-C ₅ H ₉	K29	F24.6 A59.8
4252	C ₆ H ₁₇ -	-C ₁₀ H ₂₁	K33.6	F36.7 C46.2 A59.8
4253	C ₆ H ₁₇ -	-C ₁₁ H ₂₃	K41	F50.8 C55.4 A64.2
4254	C ₆ H ₁₇ -	-C ₁₂ H ₂₅	K47.5	F55.6 C62.2 A64.2
4255	C ₆ H ₁₇ -	-C ₁₄ H ₂₉	K57.7	F64.5 C66.3

TABLE 32




No	L	R	Cr	LC
4256	C ₆ H ₁₇ -	-C ₁₆ H ₃₃	K56	F67 I
4257	C ₉ H ₁₉ -	-C ₈ H ₁₃	K23.5	A30.5 N33 I
4258	C ₉ H ₁₉ -	-C ₈ H ₁₇	K27.3	A51.2 I
4259	C ₉ H ₁₉ -	-C ₁₀ H ₂₁	K32.5	F36.5 C44 A60.7 I
4260	C ₉ H ₁₉ -	-C ₁₂ H ₂₅	K41	F56.8 C63.2 A65.6 I
4261	C ₁₀ H ₂₁ -	-C ₈ H ₁₃	K31	A29.3 N31 I
4262	C ₁₀ H ₂₁ -	-C ₈ H ₁₇	K35.5	A49.7 I
4263	C ₁₀ H ₂₁ -	-C ₁₀ H ₂₁	K46.3	C45 A59.8 I
4264	C ₁₀ H ₂₁ -	-C ₁₁ H ₂₃	K41.2	F52.6 C54.8 A64.6 I
4265	C ₁₀ H ₂₁ -	-C ₁₂ H ₂₅	K48.8	F58 C64 A65 I
4266	C ₁₂ H ₂₅ -	-C ₈ H ₁₇	K46.8	A48.3 I
4267	C ₁₂ H ₂₅ -	-C ₁₁ H ₂₃	K52.9	F52.2 A63.6 I
4268	C ₁₂ H ₂₅ -	-C ₁₂ H ₂₅	K59.9	F59.7 C64 A64.7 I
4269	C ₈ H ₉ -	-O-C ₈ H ₁₃	K42	A72 I
4271	C ₈ H ₁₃ -	-O-C ₈ H ₉	K40	A56.5 N60.5 I
4272	C ₈ H ₁₃ -	-O-C ₈ H ₁₁	K48	A62 I
4273	C ₈ H ₁₃ -	-O-C ₈ H ₁₃	K49	A77 I
4274	C ₈ H ₁₃ -	-O-C ₇ H ₁₅	K32.5	C50.6 A76.6 I
4275	C ₈ H ₁₃ -	-O-C ₈ H ₁₇	K29	C68 A85 I
4276	C ₈ H ₁₃ -	-O-C ₉ H ₁₉	K47.7	C77.2 A83.6 I
4277	C ₈ H ₁₃ -	-O-C ₁₀ H ₂₁	K38	S35 C82 A87 I
4278	C ₈ H ₁₃ -	-O-C ₁₁ H ₂₃	K38.8	S42.3 C84.3 A86.4 I
4279	C ₈ H ₁₃ -	-O-C ₁₂ H ₂₅	K35	S47.4 C85.6 A87.1 I
4280	C ₈ H ₁₃ -	-O-C ₁₄ H ₂₉	K34.4	S54.9 C85.2 A86.6 I
4281	C ₈ H ₁₃ -	-O-C ₁₅ H ₃₁	K49.9	S56.7 C83.3 A85.2 I
4283	C ₇ H ₁₅ -	-O-C ₅ H ₁₁	K46	A64 N66 I
4284	C ₇ H ₁₅ -	-O-C ₆ H ₁₃	K51	A78 I
4285	C ₇ H ₁₅ -	-O-C ₇ H ₁₅	K32.2	C45 A77.5 I

TABLE 33




No	L	R	Cr	LC
4286	C ₇ H ₁₅ -	-O-C ₆ H ₁₇	K32	C64 A87 I
4287	C ₇ H ₁₅ -	-O-C ₉ H ₁₉	K34.2	C76.3 A85.1 I
4288	C ₇ H ₁₅ -	-O-C ₁₀ H ₂₁	K32	S33 C83 A88 I
4289	C ₇ H ₁₅ -	-O-C ₁₁ H ₂₃	K38.7	S45.2 C86.8 A88.6 I
4290	C ₇ H ₁₅ -	-O-C ₁₂ H ₂₅	K46	S54 C88 A89 I
4292	C ₈ H ₁₇ -	-O-C ₆ H ₁₃	K47	A61 I
4293	C ₈ H ₁₇ -	-O-C ₈ H ₁₅	K46	A76 I
4294	C ₈ H ₁₇ -	-O-C ₇ H ₁₅	K46.5	C39 A77.5 I
4295	C ₈ H ₁₇ -	-O-C ₈ H ₁₇	K39	C58 A84 I
4296	C ₈ H ₁₇ -	-O-C ₉ H ₁₉	K40.5	C76 A84.6 I
4297	C ₈ H ₁₇ -	-O-C ₁₀ H ₂₁	K42	C84 A88 I
4298	C ₈ H ₁₇ -	-O-C ₁₁ H ₂₃	K54.3	C87.2 I
4299	C ₈ H ₁₇ -	-O-C ₁₂ H ₂₅	K57	S58 C89 I
4300	C ₈ H ₁₇ -	-O-C ₁₄ H ₂₉	K59.8	S67.2 C88.3 I
4301	C ₈ H ₁₇ -	-O-C ₁₅ H ₃₁	K57.9	S69.6 C87.5 I
4303	C ₉ H ₁₉ -	-O-C ₅ H ₁₁	K49	A62 N63 I
4304	C ₉ H ₁₉ -	-O-C ₆ H ₁₃	K48	A77 I
4305	C ₉ H ₁₉ -	-O-C ₇ H ₁₅	K40	A78 I
4306	C ₉ H ₁₉ -	-O-C ₈ H ₁₇	K36	C53 A85 I
4307	C ₉ H ₁₉ -	-O-C ₉ H ₁₉	K39	C73.9 A84.9 I
4308	C ₉ H ₁₉ -	-O-C ₁₀ H ₂₁	K37	S32 C83 A87 I
4309	C ₉ H ₁₉ -	-O-C ₁₁ H ₂₃	K45	S46 C87 I
4310	C ₉ H ₁₉ -	-O-C ₁₂ H ₂₅	K47	S59 C89 I
4311	C ₁₀ H ₂₁ -	-O-C ₉ H ₁₉	K46.6	C71.4 A83.8 I
4312	C ₁₀ H ₂₁ -	-O-C ₁₁ H ₂₃	K51.4	S47 C86.5 I
4326	C ₈ H ₁₇ -	-OOC-C ₇ H ₁₅	K79.4	A74.4 I
4334	C ₃ H ₇ -O-C ₅ H ₁₀ -	-O-C ₈ H ₁₇	K8	C47 A69 I
4335	C ₃ H ₇ -O-C ₅ H ₁₀ -	-OOC-C ₇ H ₁₅	K70	I

TABLE 34




No	L	R	Cr	LC
4336	C ₆ H ₁₃ -O-CHMe-	-O-C ₁₀ H ₂₁	1 K<-40	C*-40 A-23 I
4337	C ₇ H ₅ -O-CHMe-C ₅ H ₁₀ -	-O-C ₆ H ₁₃	1 K-22	C*-21 A48 I
4338	C ₇ H ₅ -O-CHMe-C ₅ H ₁₀ -	-O-C ₆ H ₁₇	1 K?	S8 C* 49 A55 I
4339	C ₇ H ₅ -O-CHMe-C ₅ H ₁₀ -	-O-C ₁₀ H ₂₁	1 K?	S10 C* 55 I
4340	C ₇ H ₅ -O-CHMe-C ₅ H ₁₀ -	-O-C ₁₁ H ₂₃	1 K27	C* 56 I
4341	C ₇ H ₅ -O-CHMe-C ₅ H ₁₀ -	-O-C ₁₂ H ₂₅	1 K13	C* 56 I
4342	C ₇ H ₅ -O-CHMe-C ₅ H ₁₀ -	-O-C ₆ H ₁₇	1 K?	S-6 C* 46 A52 I
4343	C ₅ H ₁₁ -O-CHMe-C ₅ H ₁₀ -	-O-C ₆ H ₁₇	1 K?	S-4 C* 37 A44 I
4346	CH ₃ -O-	-C ₉ H ₁₉	K40	S31 N41 I
4349	C ₂ H ₅ -O-	-C ₆ H ₁₇	K42.5	A43.5 N58.5 I
4353	C ₃ H ₇ -O-	-C ₇ H ₁₅	K42	A43.5 N52 I
4354	C ₃ H ₇ -O-	-C ₆ H ₁₇	K45	A49.5 I
4358	C ₄ H ₉ -O-	-C ₇ H ₁₅	K40.5	A42 N64 I
4359	C ₄ H ₉ -O-	-C ₆ H ₁₇	K35	A53.5 N60 I
4363	C ₅ H ₁₁ -O-	-C ₇ H ₁₅	K49	C48.5 A52 N66 I
4364	C ₅ H ₁₁ -O-	-C ₆ H ₁₇	K38	A54 N58 I
4365	C ₅ H ₁₁ -O-	-C ₉ H ₁₉	K41	A65.5 I
4366	C ₅ H ₁₁ -O-	-C ₁₀ H ₂₁	K47.5	A67 I

TABLE 35




No	L	R	Cr	LC
4370	C ₆ H ₁₃ -O-	-C ₇ H ₁₅	K45.5	A33 N69.5 I
4371	C ₆ H ₁₃ -O-	-C ₈ H ₁₇	K27.5	C44.5 A57.5 N65 I
4372	C ₆ H ₁₃ -O-	-C ₉ H ₁₉	K33.5	C49.5 A71 N71.5 I
4373	C ₆ H ₁₃ -O-	-C ₁₀ H ₂₁	K32.5	C62 A74.5 I
4377	C ₇ H ₁₅ -O-	-C ₇ H ₁₅	K44	C44 A49 N68 I
4378	C ₇ H ₁₅ -O-	-C ₈ H ₁₇	K46	C49 A61 N66 I
4379	C ₇ H ₁₅ -O-	-C ₉ H ₁₉	K35	C51.5 A71.5 I
4380	C ₇ H ₁₅ -O-	-C ₁₀ H ₂₁	K46	C62.5 A72 I
4384	C ₈ H ₁₇ -O-	-C ₇ H ₁₅	K49	A44 N69.5 I
4385	C ₈ H ₁₇ -O-	-C ₈ H ₁₇	K35	C57 A64 N70 I
4386	C ₈ H ₁₇ -O-	-C ₉ H ₁₉	K33	C60 A74.5 I
4387	C ₈ H ₁₇ -O-	-C ₁₀ H ₂₁	K37	C68.5 A73.5 I
4391	C ₉ H ₁₉ -O-	-C ₇ H ₁₅	K48	C51 A57 N70 I
4392	C ₉ H ₁₉ -O-	-C ₈ H ₁₇	K33	C56 A65 N68.5 I
4393	C ₉ H ₁₉ -O-	-C ₉ H ₁₉	K34	C61 A75 I
4394	C ₉ H ₁₉ -O-	-C ₁₁ H ₂₃	K45	C78 A80 I
4397	C ₁₀ H ₂₁ -O-	-C ₇ H ₁₅	K53	A54.5 N71.5 I

TABLE 36




No	L	R	Cr	LC
4398	C ₁₀ H ₂₁ -O-	-C ₈ H ₁₇	K32	C59.5 A65.5 N69.5 I
4399	C ₁₀ H ₂₁ -O-	-C ₁₀ H ₂₁	K41	C74 A77 I
4401	C ₁₁ H ₂₃ -O-	-C ₇ H ₁₅	K55	C54.5 A62.5 N70 I
4402	C ₁₁ H ₂₃ -O-	-C ₈ H ₁₇	K44.5	C60 A67 N69 I
4405	C ₁₂ H ₂₅ -O-	-C ₇ H ₁₅	K59.5	C57.5 A63 N71 I
4406	C ₁₂ H ₂₅ -O-	-C ₈ H ₁₇	K42	C61.5 A68.5 N70 I
4408	C ₁₀ H ₂₁ -O-	-C ₅ H ₁₁ -CHMe-O-C ₂ H ₅	K43	C*13 N*27 I
4409	C ₃ H ₇ -O-	-O-C ₇ H ₁₅	K68.6	C65 A78.7 N83.6 I
4410	C ₃ H ₇ -O-	-O-C ₈ H ₁₇	K49.8	C70.5 A88.2 N88.7 I
4411	C ₃ H ₇ -O-	-O-C ₉ H ₁₉	K43.7	C72 A89.4 I
4412	C ₃ H ₇ -O-	-O-C ₁₀ H ₂₁	K45.6	C71 A92.6 I
4413	C ₃ H ₇ -O-	-O-C ₁₁ H ₂₃	K41.9	C68 A93 I
4414	C ₃ H ₇ -O-	-O-C ₁₂ H ₂₅	K43.4	C61.6 A94.1 I
4415	C ₄ H ₉ -O-	-O-C ₇ H ₁₅	K53.4	C75.1 A82.4 N92.1 I
4416	C ₄ H ₉ -O-	-O-C ₈ H ₁₇	K54.4	C84 A94.7 N96.6 I
4417	C ₄ H ₉ -O-	-O-C ₉ H ₁₉	K44.4	C87.7 A96.6 I
4418	C ₄ H ₉ -O-	-O-C ₁₀ H ₂₁	K41.8	C90 A99.4 I
4419	C ₄ H ₉ -O-	-O-C ₁₁ H ₂₃	K42.3	C89 A99.8 I
4420	C ₄ H ₉ -O-	-O-C ₁₂ H ₂₅	K41.8	C88.4 A101 I
4422	C ₅ H ₁₁ -O-	-O-C ₆ H ₁₃	K62	C65.9 A76.6 N92.7 I
4423	C ₅ H ₁₁ -O-	-O-C ₇ H ₁₅	K54.4	C77.4 A84.2 N91.3 I
4424	C ₅ H ₁₁ -O-	-O-C ₈ H ₁₇	K50.2	C85.9 A93.9 N94.8 I
4425	C ₅ H ₁₁ -O-	-O-C ₉ H ₁₉	K66.7	C90 A95 I
4426	C ₅ H ₁₁ -O-	-O-C ₁₀ H ₂₁	K41.4	C93.9 A97.2 I
4427	C ₅ H ₁₁ -O-	-O-C ₁₁ H ₂₃	K51.4	C95.9 A98.2 I
4428	C ₅ H ₁₁ -O-	-O-C ₁₂ H ₂₅	K41.7	C96.2 A98.6 I

TABLE 37




No	L	R	Cr	LC
4429	C ₆ H ₁₃ -O-	-O-C ₆ H ₁₃	K62	A68 N69 I
4430	C ₆ H ₁₃ -O-	-O-C ₇ H ₁₅	K45.8	C80.6 A84.7 N94.9 I
4431	C ₆ H ₁₃ -O-	-O-C ₈ H ₁₇	K42.6	C89.8 A96.6 N98.7 I
4432	C ₆ H ₁₃ -O-	-O-C ₉ H ₁₉	K49.9	C94.4 A97.9 I
4433	C ₆ H ₁₃ -O-	-O-C ₁₀ H ₂₁	K43.8	C98.7 A100.3 I
4434	C ₆ H ₁₃ -O-	-O-C ₁₁ H ₂₃	K55.4	C100.4 A101 I
4435	C ₆ H ₁₃ -O-	-O-C ₁₂ H ₂₅	K52.2	C102.2 I
4436	C ₇ H ₁₅ -O-	-O-C ₆ H ₁₃	K60.8	C68.2 A79.4 N94.6 I
4437	C ₇ H ₁₅ -O-	-O-C ₇ H ₁₅	K59.2	C79.9 A87.6 N93.6 I
4438	C ₇ H ₁₅ -O-	-O-C ₈ H ₁₇	K51.6	C87.2 A96.4 N97.1 I
4439	C ₇ H ₁₅ -O-	-O-C ₉ H ₁₉	K56	C94.9 A97.8 I
4440	C ₇ H ₁₅ -O-	-O-C ₁₀ H ₂₁	K55.6	C99.6 A100.3 I
4441	C ₇ H ₁₅ -O-	-O-C ₁₁ H ₂₃	K67.4	C100.1 I
4442	C ₇ H ₁₅ -O-	-O-C ₁₂ H ₂₅	K54.8	C100.3 I
4444	C ₈ H ₁₇ -O-	-O-C ₆ H ₁₃	K59.3	C73 A80 N96.2 I
4445	C ₈ H ₁₇ -O-	-O-C ₇ H ₁₅	K53.4	C81.5 A88.3 N95.4 I
4446	C ₈ H ₁₇ -O-	-O-C ₈ H ₁₇	K51	C92.3 A99.5 N100.3 I
4447	C ₈ H ₁₇ -O-	-O-C ₉ H ₁₉	K48.2	C96.4 A99 I
4448	C ₈ H ₁₇ -O-	-O-C ₁₀ H ₂₁	K51.7	C101.7 A102.1 I
4449	C ₈ H ₁₇ -O-	-O-C ₁₁ H ₂₃	K59.9	C101.7 I
4450	C ₈ H ₁₇ -O-	-O-C ₁₂ H ₂₅	K57.1	C102.9 I
4451	C ₉ H ₁₉ -O-	-O-C ₆ H ₁₃	K61.6	C68.9 A83.2 N93.7 I
4452	C ₉ H ₁₉ -O-	-O-C ₇ H ₁₅	K55.2	C78.7 A89.6 N93.6 I
4453	C ₉ H ₁₉ -O-	-O-C ₈ H ₁₇	K55.1	C87.5 A96.2 I
4454	C ₉ H ₁₉ -O-	-O-C ₉ H ₁₉	K65	C97 A101 I
4455	C ₉ H ₁₉ -O-	-O-C ₁₀ H ₂₁	K52.5	C101.1 I
4456	C ₉ H ₁₉ -O-	-O-C ₁₁ H ₂₃	K62	C101 I
4457	C ₉ H ₁₉ -O-	-O-C ₁₂ H ₂₅	K60.3	C100.3 I
4458	C ₁₀ H ₂₁ -O-	-O-C ₆ H ₁₃	K62.3	C71.6 A83.8 N93.6 I

TABLE 38




No	L	R	Cr	LC
4459	C ₁₀ H ₂₁ -O-	-O-C ₇ H ₁₅	K50.4	C79.7 A90.1 N93.6 I
4460	C ₁₀ H ₂₁ -O-	-O-C ₈ H ₁₇	K50	C89 A99.6 I
4461	C ₁₀ H ₂₁ -O-	-O-C ₉ H ₁₉	K52.3	C96.2 A99 I
4462	C ₁₀ H ₂₁ -O-	-O-C ₁₀ H ₂₁	K52.7	C101.4 I
4463	C ₁₀ H ₂₁ -O-	-O-C ₁₁ H ₂₃	K62.9	C101.2 I
4464	C ₁₀ H ₂₁ -O-	-O-C ₁₂ H ₂₅	K65.4	C102.8 I
4465	C ₁₀ H ₂₁ -O-	-O-C ₁₄ H ₂₉	K67	C103 I
4466	C ₁₁ H ₂₃ -O-	-O-C ₆ H ₁₃	K69.3	C69 A86.2 N91.8 I
4467	C ₁₁ H ₂₃ -O-	-O-C ₇ H ₁₅	K58.2	C77 A90.1 N91.9 I
4468	C ₁₁ H ₂₃ -O-	-O-C ₈ H ₁₇	K56	C84.9 A97.1 I
4469	C ₁₁ H ₂₃ -O-	-O-C ₉ H ₁₉	K56.2	C92.7 A96.1 I
4470	C ₁₁ H ₂₃ -O-	-O-C ₁₀ H ₂₁	K53.1	C100.6 I
4471	C ₁₁ H ₂₃ -O-	-O-C ₁₁ H ₂₃	K69.8	C99.8 I
4472	C ₁₁ H ₂₃ -O-	-O-C ₁₂ H ₂₅	K65.6	C101 I
4473	C ₁₁ H ₂₃ -O-	-O-C ₁₆ H ₃₃	K71.3	S75.6 C100.9 I
4474	C ₁₂ H ₂₅ -O-	-O-C ₆ H ₁₃	K70.3	C70.7 A86.2 N91.4 I
4475	C ₁₂ H ₂₅ -O-	-O-C ₇ H ₁₅	K57.1	C77.2 A89.4 N90.9 I
4476	C ₁₂ H ₂₅ -O-	-O-C ₈ H ₁₇	K50	C86 A98 I
4477	C ₁₂ H ₂₅ -O-	-O-C ₉ H ₁₉	K53.8	C93.5 A96.9 I
4478	C ₁₂ H ₂₅ -O-	-O-C ₁₀ H ₂₁	K54.6	C100.3 I
4479	C ₁₂ H ₂₅ -O-	-O-C ₁₁ H ₂₃	K59.5	C100.7 I
4480	C ₁₂ H ₂₅ -O-	-O-C ₁₂ H ₂₅	K63.7	C104.3 I
4481	C ₁₂ H ₂₅ -O-	-O-C ₁₆ H ₃₃	K71.2	S73.7 C99 I
4484	C ₈ H ₁₇ -O-	-O-C ₄ H ₉ -CMe ₂ -C ₄ H ₉	K54	C34 N37 I
4485	C ₈ H ₁₇ -O-	-O-C ₆ H ₁₃ -CMe ₂ -C ₄ H ₉	K43	C55 I
4498	C ₇ H ₁₅ -O-	-OOC-C ₆ H ₁₃	K64.9	C66.2 N85.8 I
4499	C ₇ H ₁₅ -O-	-OOC-C ₉ H ₁₉	K74.8	C96.5 I
4500	C ₇ H ₁₅ -O-	-OOC-C ₁₃ H ₂₇	K81	S73 C101 I
4501	C ₈ H ₁₇ -O-	-OOC-C ₆ H ₁₃	K63.4	C69.7 N89.7 I
4502	C ₈ H ₁₇ -O-	-OOC-C ₇ H ₁₅	K75	C74.4 N91.3 I

TABLE 39




No	L	R	Cr	LC
4614	C ₇ H ₁₅ -COO-	-C ₇ H ₁₅	K54	A40 N57 I
4615	C ₇ H ₁₅ -COO-	-C ₈ H ₁₇	K51	C52 A54 N56 I
4616	C ₇ H ₁₅ -COO-	-C ₉ H ₁₉	K53	C64 A65 I
4619	C ₈ H ₁₇ -COO-	-C ₈ H ₁₇	K49	C53.5 A54.8 N56.5 I
4620	C ₈ H ₁₇ -COO-	-C ₁₀ H ₂₁	K53	S50 C70 I
4623	C ₉ H ₁₉ -COO-	-C ₈ H ₁₇	K42	C55.5 N59.8 I
4626	C ₁₀ H ₂₁ -COO-	-C ₈ H ₁₇	K57	C56.5 A56.7 N59 I
4629	C ₁₁ H ₂₃ -COO-	-C ₈ H ₁₇	K56	C57.5 N60.8 I
4630	C ₇ H ₁₅ -COO-	-O-C ₈ H ₁₇	K73	C89 A92 N93 I
4636	C ₄ H ₉ -CMe ₂ -CH ₂ -COO-	-O-C ₈ H ₁₇	K53	C49 N50 I
4637	C ₆ H ₁₃ -CMe ₂ -CH ₂ -COO-	-O-C ₈ H ₁₇	K45	C42 N46 I
4643	C ₅ H ₁₁ -OCOO-	-C ₁₂ H ₂₅	K48	A52 I
4645	C ₉ H ₁₉ -OCOO-	-C ₁₂ H ₂₅	K46	C59 I
4647	C ₁₂ H ₂₅ -OCOO-	-C ₁₂ H ₂₅	K57	C60 I
4661	C ₈ H ₁₇ -O-	-C ₃ H ₆ -CHMe-C ₂ H ₅	1 K33.5	N*19U
4662	C ₉ H ₁₉ -O-	-C ₃ H ₆ -CHMe-C ₂ H ₅	1 K35	N*20U
4663	C ₁₀ H ₂₁ -O-	-C ₃ H ₆ -CHMe-C ₂ H ₅	1 K38	N*21.5U
4664	C ₁₂ H ₂₅ -O-	-C ₃ H ₆ -CHMe-C ₂ H ₅	1 K43.5	N*40.5U
4665	C ₈ H ₁₇ -	-O-C ₃ H ₆ -CHMe-C ₂ H ₅	1 K-13	S10 S18 C*51 A51.4 I
4666	C ₈ H ₁₇ -	-O-C ₃ H ₆ -CHMe-C ₂ H ₅	2 K16	C57.5 A59 I

TABLE 40




No	L	R	Cr	LC
4697	C ₈ H ₁₇ -O-	-O-CH ₂ -CHF-C ₆ H ₁₃	1 K62.5	C*92 A97 I
4698	C ₉ H ₁₉ -O-	-O-CH ₂ -CHF-C ₆ H ₁₃	1 K61	C*90.3 A96.2 I
4699	C ₁₀ H ₂₁ -O-	-O-CH ₂ -CHF-C ₆ H ₁₃	1 K47	C*90 A97 I
4700	C ₁₂ H ₂₅ -O-	-O-CH ₂ -CHF-C ₆ H ₁₃	1 K66	C*89 A96 I
4701	C ₈ H ₁₇ -	-C ₂ H ₄ -CHF-C ₆ H ₁₃	1 K31	C*25 A62 I
4702	C ₈ H ₁₇ -O-	-C ₂ H ₄ -CHF-C ₆ H ₁₃	S K74	A82 I
4703	C ₁₀ H ₂₁ -O-	-C ₂ H ₄ -CHF-C ₆ H ₁₃	1 K71	C*69 A82 I
4704	C ₁₀ H ₂₁ -O-	-C ₂ H ₄ -CHF-C ₆ H ₁₇	S K85	C*84 A86 I
4705	C ₁₂ H ₂₅ -O-	-C ₂ H ₄ -CHF-C ₆ H ₁₃	S K74	A82 I
4706	C ₁₀ H ₂₁ -O-	-O-C ₂ H ₄ -CHF-C ₆ H ₁₃	1 K50	C*96 N*97 I
4707	C ₁₀ H ₂₁ -O-	-O-C ₃ H ₆ -CHF-C ₆ H ₁₃	1 K61	C*102 A103 I
4715	C ₃ H ₇ -O-C ₅ H ₁₀ -	-OOC-CH=CH-C ₇ H ₁₅	K63	C61 N69 I
4716	C ₃ H ₇ -O-C ₅ H ₁₀ -	-OOC-CH=CH-C ₈ H ₁₇	K53	C62 A64 N68 I
4717	C ₃ H ₇ -O-C ₅ H ₁₀ -	-OOC-CH=CH-C ₉ H ₁₉	K63	C73 I
4718	C ₆ H ₁₃ -	-O-CH ₂ -CH=CH-C ₂ H ₅	K57	A63 I
4719	C ₆ H ₁₃ -	-O-CH ₂ -CH=CH-C ₃ H ₇	K67	A76 I
4720	C ₆ H ₁₃ -	-O-CH ₂ -CH=CH-C ₄ H ₉	K62	C65 A71 I
4721	C ₆ H ₁₃ -	-O-CH ₂ -CH=CH-C ₅ H ₁₁	K61	C76 A80 I
4722	C ₆ H ₁₃ -	-O-CH ₂ -CH=CH-C ₆ H ₁₃	K74	C78 I
4723	C ₆ H ₁₃ -	-O-CH ₂ -CH=CH-C ₇ H ₁₅	K65	C82 I
4724	C ₆ H ₁₃ -	-O-CH ₂ -CH=CH-C ₈ H ₁₇	K73	C82 I
4725	C ₆ H ₁₃ -	-O-CH ₂ -CH=CH-C ₉ H ₁₉	K56	S72 C84 I
4726	C ₇ H ₁₅ -	-O-CH ₂ -CH=CH-C ₂ H ₅	K53	A66 I
4727	C ₇ H ₁₅ -	-O-CH ₂ -CH=CH-C ₃ H ₇	K69	A78 I
4728	C ₇ H ₁₅ -	-O-CH ₂ -CH=CH-C ₄ H ₉	K60	C61 A73 I
4729	C ₇ H ₁₅ -	-O-CH ₂ -CH=CH-C ₅ H ₁₁	K59	C75 A82 I
4730	C ₇ H ₁₅ -	-O-CH ₂ -CH=CH-C ₆ H ₁₃	K67	C80 I

TABLE 41




No	L	R	Cr	LC
4731	C ₇ H ₁₅ -	-O-CH ₂ -CH=CH-C ₇ H ₁₅	K64	C86 I
4732	C ₇ H ₁₅ -	-O-CH ₂ -CH=CH-C ₈ H ₁₇	K72	C85 I
4733	C ₇ H ₁₅ -	-O-CH ₂ -CH=CH-C ₉ H ₁₉	K67	S74 C87 I
4734	C ₈ H ₁₇ -	-O-CH ₂ -CH=CH-C ₂ H ₅	K53	A65 I
4735	C ₈ H ₁₇ -	-O-CH ₂ -CH=CH-C ₃ H ₇	K68	A77 I
4736	C ₈ H ₁₇ -	-O-CH ₂ -CH=CH-C ₄ H ₉	K57	A73 I
4737	C ₈ H ₁₇ -	-O-CH ₂ -CH=CH-C ₅ H ₁₁	K56	C69.5 A81 I
4738	C ₈ H ₁₇ -	-O-CH ₂ -CH=CH-C ₆ H ₁₃	K67	C79 I
4739	C ₈ H ₁₇ -	-O-CH ₂ -CH=CH-C ₇ H ₁₅	K39	S62 C84 I
4740	C ₈ H ₁₇ -	-O-CH ₂ -CH=CH-C ₈ H ₁₇	K51	S67 C85 I
4741	C ₈ H ₁₇ -	-O-CH ₂ -CH=CH-C ₉ H ₁₉	K66	S74 C86 I
4742	C ₉ H ₁₉ -	-O-CH ₂ -CH=CH-C ₂ H ₅	K57	A66 I
4743	C ₉ H ₁₉ -	-O-CH ₂ -CH=CH-C ₃ H ₇	K70	A77 I
4744	C ₉ H ₁₉ -	-O-CH ₂ -CH=CH-C ₄ H ₉	K57	C48 A73 I
4745	C ₉ H ₁₉ -	-O-CH ₂ -CH=CH-C ₅ H ₁₁	K56	C65 A82 I
4746	C ₉ H ₁₉ -	-O-CH ₂ -CH=CH-C ₆ H ₁₃	K62	C78 A80 I
4747	C ₉ H ₁₉ -	-O-CH ₂ -CH=CH-C ₇ H ₁₅	K60	S58 C84 I
4748	C ₉ H ₁₉ -	-O-CH ₂ -CH=CH-C ₈ H ₁₇	K50	S63 C86 I
4749	C ₉ H ₁₉ -	-O-CH ₂ -CH=CH-C ₉ H ₁₉	K61	S74 C87 I
4750	C ₃ H ₇ -O-C ₅ H ₁₀ -	-O-CH ₂ -CH=CH-C ₃ H ₇	K47	A56 I
4751	C ₃ H ₇ -O-C ₅ H ₁₀ -	-O-CH ₂ -CH=CH-C ₄ H ₉	K20	A41 I
4752	C ₃ H ₇ -O-C ₅ H ₁₀ -	-O-CH ₂ -CH=CH-C ₅ H ₁₁	K36	C58 A63 I
4753	C ₃ H ₇ -O-C ₅ H ₁₀ -	-O-CH ₂ -CH=CH-C ₆ H ₁₃	K51	C60 I
4754	C ₃ H ₇ -O-C ₅ H ₁₀ -	-O-CH ₂ -CH=CH-C ₇ H ₁₅	K44	C65 I
4755	C ₃ H ₇ -O-C ₅ H ₁₀ -	-O-CH ₂ -CH=CH-C ₈ H ₁₇	K50	S49 C68 I
4756	C ₃ H ₇ -O-C ₅ H ₁₀ -	-O-CH ₂ -CH=CH-C ₉ H ₁₉	K53	S59 C71 I
4760	C ₆ H ₁₃ -	-O-C ₃ H ₆ -CH=CH ₂	K39	A69 I
4761	C ₆ H ₁₃ -	-O-C ₃ H ₆ -CH=CH-C ₃ H ₇	K57	C68 A80 I
4762	C ₇ H ₁₅ -	-O-C ₃ H ₆ -CH=CH ₂	K48	A72 I

TABLE 42




No	L	R	Cr	LC
4763	C ₇ H ₁₅ -	-O-C ₃ H ₆ -CH=CH-C ₃ H ₇	K57	C66 A82 I
4764	C ₈ H ₁₇ -	-O-C ₃ H ₆ -CH=CH ₂	K43	A69 I
4765	C ₈ H ₁₇ -	-O-C ₃ H ₆ -CH=CH-C ₃ H ₇	K53	C55 A82 I
4766	C ₉ H ₁₉ -	-O-C ₃ H ₆ -CH=CH ₂	K50	A70 I
4767	C ₉ H ₁₉ -	-O-C ₃ H ₆ -CH=CH-C ₃ H ₇	K47	C52 A82 I
4769	C ₆ H ₁₃ -	-O-C ₄ H ₈ -CH=CH ₂	K35	A64 I
4770	C ₇ H ₁₅ -	-O-C ₄ H ₈ -CH=CH ₂	K37	A67 I
4771	C ₈ H ₁₇ -	-O-C ₄ H ₈ -CH=CH ₂	K33	A64 I
4772	C ₉ H ₁₉ -	-O-C ₄ H ₈ -CH=CH ₂	K33	A65 I
4774	C ₃ H ₇ -O-C ₅ H ₁₀ -	-O-C ₄ H ₈ -CH=CH ₂	K18	A55 I
4776	C ₆ H ₁₃ -	-O-C ₅ H ₁₀ -CH=CH ₂	K34	A79 I
4777	C ₆ H ₁₃ -	-O-C ₅ H ₁₀ -CH=CH-CH ₃	K45	C50 A85 I
4778	C ₇ H ₁₅ -	-O-C ₅ H ₁₀ -CH=CH ₂	K35	A81 I
4779	C ₇ H ₁₅ -	-O-C ₅ H ₁₀ -CH=CH-CH ₃	K48	A87 I
4780	C ₈ H ₁₇ -	-O-C ₅ H ₁₀ -CH=CH ₂	K37	A80 I
4781	C ₈ H ₁₇ -	-O-C ₅ H ₁₀ -CH=CH-CH ₃	K44	A85 I
4782	C ₉ H ₁₉ -	-O-C ₅ H ₁₀ -CH=CH ₂	K38	A81 I
4783	C ₉ H ₁₉ -	-O-C ₅ H ₁₀ -CH=CH-CH ₃	K51	A86 I
4785	C ₃ H ₇ -O-C ₅ H ₁₀ -	-O-C ₅ H ₁₀ -CH=CH ₂	K10	A59 I
4786	C ₃ H ₇ -O-C ₅ H ₁₀ -	-O-C ₅ H ₁₀ -CH=CH-CH ₃	K21	A70 I
4788	C ₆ H ₁₃ -	-O-C ₆ H ₁₂ -CH=CH ₂	K26	C54 A75 I
4789	C ₇ H ₁₅ -	-O-C ₆ H ₁₂ -CH=CH ₂	K24	C50 A78 I
4790	C ₈ H ₁₇ -	-O-C ₆ H ₁₂ -CH=CH ₂	K42	C43 A76 I
4791	C ₉ H ₁₉ -	-O-C ₆ H ₁₂ -CH=CH ₂	K34	C38 A77 I
4792	C ₃ H ₇ -O-C ₅ H ₁₀ -	-O-C ₆ H ₁₂ -CH=CH ₂	K15	C35 A60 I
4793	C ₆ H ₁₃ -	-O-C ₇ H ₁₄ -CH=CH ₂	K20	C65 A81 I
4794	C ₇ H ₁₅ -	-O-C ₇ H ₁₄ -CH=CH ₂	K16	S23 C62 A84 I
4795	C ₈ H ₁₇ -	-O-C ₇ H ₁₄ -CH=CH ₂	K20	C60 A83 I
4796	C ₉ H ₁₉ -	-O-C ₇ H ₁₄ -CH=CH ₂	K30	C53 A84 I
4797	C ₃ H ₇ -O-C ₅ H ₁₀ -	-O-C ₇ H ₁₄ -CH=CH ₂	K-30	C30 A61 I

TABLE 43




No	L	R	Cr	LC
4798	C ₆ H ₁₃ -	-O-C ₆ H ₁₃ -CH=CH ₂	K33	S35 C73 A80 I
4799	C ₇ H ₁₅ -	-O-C ₆ H ₁₃ -CH=CH ₂	K32	S33 C72 A82 I
4800	C ₈ H ₁₇ -	-O-C ₆ H ₁₃ -CH=CH ₂	K36	C72 A81 I
4801	C ₉ H ₁₉ -	-O-C ₆ H ₁₃ -CH=CH ₂	K35	C71 A82 I
4802	C ₃ H ₇ -O-C ₅ H ₁₀ -	-O-C ₆ H ₁₃ -CH=CH ₂	K-3	C57 A64 I
4803	C ₆ H ₁₃ -	-O-C ₆ H ₁₃ -CH=CH ₂	K29	S28 C76 A82 I
4804	C ₆ H ₁₃ -	-O-C ₁₀ H ₂₀ -CH=CH ₂	K33	S35 C76 A81 I
4805	C ₇ H ₁₅ -	-O-C ₆ H ₁₃ -CH=CH ₂	K28	S29 C77 A85 I
4806	C ₇ H ₁₅ -	-O-C ₁₀ H ₂₀ -CH=CH ₂	K38	S40 C79 A84 I
4807	C ₈ H ₁₇ -	-O-C ₆ H ₁₃ -CH=CH ₂	K38	C78 A84 I
4808	C ₈ H ₁₇ -	-O-C ₁₀ H ₂₀ -CH=CH ₂	K43	C80 A82 I
4809	C ₉ H ₁₉ -	-O-C ₆ H ₁₃ -CH=CH ₂	K38	C78 A85 I
4810	C ₉ H ₁₉ -	-O-C ₁₀ H ₂₀ -CH=CH ₂	K43	C82 A83 I
4811	C ₃ H ₇ -O-C ₅ H ₁₀ -	-O-C ₆ H ₁₃ -CH=CH ₂	K0	C55 A65 I
4812	C ₃ H ₇ -O-C ₅ H ₁₀ -	-O-C ₁₀ H ₂₀ -CH=CH ₂	K19	S36 S59 C70 I
4817	C ₆ H ₁₃ -	-O-C ₂ H ₅ -CHXCH-C ₄ H ₉	K52	A43 I
4818	C ₉ H ₁₉ -	-O-C ₂ H ₅ -CHXCH-C ₄ H ₉	K52	A44 I
4822	C ₆ H ₁₃ -	-O-C ₄ H ₉ -CHXCH-C ₂ H ₅	K45	C52 A55 I
4823	C ₇ H ₁₅ -	-O-C ₄ H ₉ -CHXCH-C ₂ H ₅	K42	C52 A55 I
4824	C ₈ H ₁₇ -	-O-C ₄ H ₉ -CHXCH-C ₂ H ₅	K38	C46 A57 I
4825	C ₉ H ₁₉ -	-O-C ₄ H ₉ -CHXCH-C ₂ H ₅	K38	C44 A58 I
4826	C ₃ H ₇ -O-C ₅ H ₁₀ -	-O-C ₄ H ₉ -CHXCH-C ₂ H ₅	K10	C33 A37 I
4828	C ₉ H ₁₉ -O-	-O-C ₄ H ₉ -O-CH ₂ -CH/CH ₂ \CH ₂	K72.4	C58.4 N72 I
4829	C ₆ H ₁₃ -O-	-O-C ₄ H ₉ -CH/CH ₂ \CH ₂	K64	C48 N88 U
4830	C ₄ H ₉ -O-C ₄ H ₉ -O-	-O-C ₄ H ₉ -CH/CH ₂ \CH ₂	K42	C45 A47 N64 I
4831	C ₆ H ₁₃ -O-	-O-C ₅ H ₁₁ -CH/CH ₂ \CH ₂	K53	C73 A75 N86 I
4832	C ₄ H ₉ -O-C ₄ H ₉ -O-	-O-C ₅ H ₁₁ -CH/CH ₂ \CH ₂	K39	C63 A65 N67 I
4833	C ₆ H ₁₇ -O-	-O-C ₆ H ₁₃ -CH/CH ₂ \CH ₂	K56	C78 A84 N89 I
4834	C ₉ H ₁₉ -O-	-O-C ₆ H ₁₃ -CH/CH ₂ \CH ₂	K56.5	C79 A85 N89.5 I

TABLE 44




No.	L	R	Cr	LC
4835	C ₁₁ H ₂₃ -O-	-O-C ₆ H ₁₂ -CH/CH ₂ \CH ₂	K57.5	C76.5 A86.7 N87 I
4836	C ₁₂ H ₂₅ -O-	-O-C ₆ H ₁₂ -CH/CH ₂ \CH ₂	K61	C>70 A87 I
4837	C ₄ H ₉ -O-C ₄ H ₉ -O-	-O-C ₆ H ₁₂ -CH/CH ₂ \CH ₂	K46	C66 A67 N69 I
4838	C ₆ H ₁₃ -O-	-O-C ₇ H ₁₄ -CH/CH ₂ \CH ₂	K51.8	C86.5 A89.6 N89.8 I
4839	C ₉ H ₁₉ -O-	-O-C ₇ H ₁₄ -CH/CH ₂ \CH ₂	K60	C87.9 A90.4 I
4840	C ₁₀ H ₂₁ -O-	-O-C ₇ H ₁₄ -CH/CH ₂ \CH ₂	K55.7	C90 A92.5 I
4841	C ₁₁ H ₂₃ -O-	-O-C ₇ H ₁₄ -CH/CH ₂ \CH ₂	K53.4	C87.6 A90.5 I
4842	C ₁₂ H ₂₅ -O-	-O-C ₇ H ₁₄ -CH/CH ₂ \CH ₂	K67.4	C86.1 A90.5 I
4843	C ₄ H ₉ -O-C ₄ H ₉ -O-	-O-C ₇ H ₁₄ -CH/CH ₂ \CH ₂	K43	C73 I
4844	C ₄ H ₉ -O-	-O-C ₈ H ₁₆ -CH/CH ₂ \CH ₂	K55.4	C81 A87.8 I
4845	C ₆ H ₁₃ -O-	-O-C ₈ H ₁₆ -CH/CH ₂ \CH ₂	K54.1	C88.2 A90.8 I
4846	C ₈ H ₁₇ -O-	-O-C ₈ H ₁₆ -CH/CH ₂ \CH ₂	K56.4	C91.7 A92.9 I
4847	C ₉ H ₁₉ -O-	-O-C ₈ H ₁₆ -CH/CH ₂ \CH ₂	K56.2	C91.8 A93 I
4848	C ₁₀ H ₂₁ -O-	-O-C ₈ H ₁₆ -CH/CH ₂ \CH ₂	K58.5	C91.6 A92 I
4849	C ₁₁ H ₂₃ -O-	-O-C ₈ H ₁₆ -CH/CH ₂ \CH ₂	K53.6	C92.3 A93.1 I
4850	C ₁₂ H ₂₅ -O-	-O-C ₈ H ₁₆ -CH/CH ₂ \CH ₂	K54.9	C92.3 A93 I
4851	C ₇ H ₁₅ -O-	-O-C ₉ H ₁₈ -CH/CH ₂ \CH ₂	K64.7	C91 I
4852	C ₈ H ₁₇ -O-	-O-C ₉ H ₁₈ -CH/CH ₂ \CH ₂	K63.7	C93.2 I
4853	C ₁₂ H ₂₅ -O-	-O-C ₁₁ H ₂₂ -CH/CH ₂ \CH ₂	K64.6	C73.8 I
4854	C ₆ H ₁₇ -	-O-CH ₂ -CH/O\CH(t)-C ₃ H ₇	1 K55	B90 A102 I
4855	C ₆ H ₁₇ -	-O-CH ₂ -CH/O\CH(t)-C ₃ H ₇	1 K70	F*101 A104 I
4857	C ₂ H ₅ -CMe ₂ -C ₄ H ₉ -O-	-O-CH ₂ -CH/O\CH(t)-C ₄ H ₉	1 K83	S87 A92 I
4858	C ₂ H ₅ -CMe ₂ -C ₆ H ₁₃ -O-	-O-CH ₂ -CH/O\CH(t)-C ₄ H ₉	1 K90	C*96 A106 I
4859	C ₂ H ₅ -CHMe-O-CH ₂ -	-C ₁₀ H ₂₁	1 K15.6	S15.2 I
4861	C ₆ H ₁₃ -CHMe-O-CH ₂ -	-C ₁₀ H ₂₁	2 K16.9	A-8.5 I
4869	C ₂ H ₅ -CHMe-COO-	-C ₁₁ H ₂₃	S K52.2	S40.7 I
4871	C ₂ H ₅ -CHMe-COO-	-O-C ₈ H ₁₇	S K66	C*62.2 I
4872	C ₂ H ₅ -CHMe-COO-	-O-C ₁₁ H ₂₃	S K43	C*64.1 S67.2 I
4873	CH ₃ -CHMe-CHCl-COO-	-C ₇ H ₁₅	S K64	X-10 I
4875	C ₂ H ₅ -CHMe-CHCl-COO-	-C ₇ H ₁₅	3 K59	X-20 I

TABLE 45




No	L	R	Cr	LC
4919	C ₂ H ₅ -CHMe-C ₃ H ₆ -O-	-C ₆ H ₁₇	S K31.2	B16.8 C*46.8 A50.8 I
4920	C ₂ H ₅ -CHMe-C ₃ H ₆ -O-	-C ₉ H ₁₉	S K23	S28 C*30 A51.5 N*52 I
4921	C ₂ H ₅ -CHMe-C ₃ H ₆ -O-	-C ₁₀ H ₂₁	S K33	S38.5 C*58 I
4922	C ₂ H ₅ -CHMe-C ₃ H ₆ -O-	-C ₁₁ H ₂₃	S K35.9	C*60 I
4923	C ₂ H ₅ -CHMe-C ₃ H ₆ -O-	-C ₁₂ H ₂₅	S K41	S23.8 C*62.2 I
4924	C ₂ H ₅ -CHMe-C ₃ H ₆ -O-	-C ₁₄ H ₂₉	S K32	B45 C*59.8 I
4925	C ₃ H ₇ -CHMe-C ₃ H ₆ -O-	-C ₉ H ₁₉	2 K15.5	C44.5 A54.5 I
4926	C ₃ H ₇ -CHMe-C ₃ H ₆ -O-	-C ₉ H ₁₇	2 K15	C9 A42.5 I
4927	C ₂ H ₅ -CHMe-C ₃ H ₆ -CHMe-CH ₂ -O-	-C ₆ H ₁₇	7 K37	A34 I
4928	CH ₃ -CHMe-C ₃ H ₅ -CHMe-C ₂ H ₄ -O-	-C ₉ H ₁₉	S K27	A40 I
4931	CH ₃ -CHMe-C ₃ H ₅ -CHMe-CH ₂ -COO-	-C ₉ H ₁₉	S K44	C* < 7 I
4932	C ₂ H ₅ -CHMe-C ₄ H ₈ -O-	-C ₆ H ₁₃	S K-5	A27 N*42 I
4933	C ₂ H ₅ -CHMe-C ₄ H ₈ -O-	-C ₇ H ₁₅	S K-6	A46.3 N*49 I
4934	C ₂ H ₅ -CHMe-C ₄ H ₈ -O-	-C ₈ H ₁₇	S K12	C*34.7 A49.5 I
4935	C ₂ H ₅ -CHMe-C ₄ H ₈ -O-	-C ₉ H ₁₉	S K10	C*46 A59 I
4936	C ₂ H ₅ -CHMe-C ₄ H ₈ -O-	-C ₁₀ H ₂₁	S K17	C*53.8 A63 I
4937	C ₂ H ₅ -CHMe-C ₄ H ₈ -O-	-C ₁₁ H ₂₃	S K20	C*59 I
4938	C ₂ H ₅ -CHMe-C ₄ H ₈ -O-	-C ₁₂ H ₂₅	S K23	S16 C*61.5 I
4939	C ₃ H ₇ -CHMe-C ₄ H ₈ -O-	-C ₈ H ₁₇	2 K3.5	S31.5 A47.5 I
4940	C ₂ H ₅ -CHMe-C ₄ H ₈ -CO-	-C ₆ H ₁₇	S K67	C*69 A79.3 I
4941	C ₂ H ₅ -CHMe-C ₄ H ₈ -COO-	-C ₆ H ₁₇	S K38.5	S24 C*44.8 I
4942	C ₂ H ₅ -CHMe-C ₄ H ₈ -COO-	-C ₁₁ H ₂₃	S K62.3	S46.5 C*60 I
4943	C ₂ H ₅ -CHMe-C ₄ H ₈ -COO-	-C ₁₄ H ₂₉	S K46	S50 C*62.8 I
4944	C ₂ H ₅ -CHMe-C ₄ H ₈ -COO-	-O-C ₆ H ₁₇	S K76	C*79.5 I
4945	C ₂ H ₅ -CHMe-C ₅ H ₁₀ -O-	-C ₆ H ₁₃	S K12	C*23.8 N*45.6 I
4946	C ₂ H ₅ -CHMe-C ₅ H ₁₀ -O-	-C ₇ H ₁₅	S K10	S16 C*39 A54 N*61 I
4947	C ₂ H ₅ -CHMe-C ₅ H ₁₀ -O-	-C ₈ H ₁₇	S K3	B14.2 C*48.6 A56.3 I
4948	C ₂ H ₅ -CHMe-C ₅ H ₁₀ -O-	-C ₉ H ₁₉	S K16	C*49.1 A61 I
4949	C ₂ H ₅ -CHMe-C ₅ H ₁₀ -O-	-C ₁₀ H ₂₁	S K41	S<? C*61 I
4950	C ₂ H ₅ -CHMe-C ₅ H ₁₀ -O-	-C ₁₁ H ₂₃	S K?	B36.7 C*68 I

TABLE 46




No	L	R	Cr	LC
4951	C ₂ H ₅ -CHMe-C ₅ H ₁₀ -O-	-C ₁₂ H ₂₅	S K40.5	C*70 I
4952	C ₂ H ₅ -CHMe-C ₅ H ₁₀ -O-	-C ₁₄ H ₂₉	S K43	B45 C*66 I
4953	C ₂ H ₅ -CHMe-C ₅ H ₁₀ -O-	-C ₈ H ₁₇	2 K3	C47.5 A58 I
4954	C ₂ H ₅ -CHMe-C ₅ H ₁₀ -O-	-O-C ₈ H ₁₇	S K40.7	C*82.8 A89.1 I
4955	C ₂ H ₅ -CHMe-C ₅ H ₁₀ -O-	-COO-C ₈ H ₁₇	S K76.5	C*79.7 I
4956	CH ₃ -CHMe-C ₆ H ₁₂ -	-C ₉ H ₁₉	K29.5	F31 A58.2 I
4957	CH ₃ -CHMe-C ₆ H ₁₂ -	-C ₁₀ H ₂₁	K38.6	F41.3 C51.4 A58.4 I
4962	C ₂ H ₅ -CHF-COO-	-C ₉ H ₁₉	1 K70	S58 I
4964	C ₂ H ₅ -CHF-COO-	-C ₁₂ H ₂₅	1 K69	A59 I
4965	C ₄ H ₉ -CHF-COO-	-C ₁₀ H ₂₁	S K46	S30 A49 I
4966	C ₄ H ₉ -CHF-COO-	-C ₁₂ H ₂₅	S K59	C*45 A52 I
4968	C ₅ H ₁₁ -CHF-COO-	-C ₁₂ H ₂₅	S K14	S? A50 I
4969	C ₆ H ₁₃ -CHF-COO-	-C ₈ H ₁₇	1 K56	A38 I
4970	C ₆ H ₁₃ -CHF-COO-	-C ₉ H ₁₉	1 K53	A46 I
4971	C ₆ H ₁₃ -CHF-COO-	-C ₁₀ H ₂₁	1 K57	S32 C*45 I
4972	C ₆ H ₁₃ -CHF-COO-	-C ₁₂ H ₂₅	1 K62	C*52 I
4973	C ₇ H ₁₅ -CHF-COO-	-C ₁₀ H ₂₁	S K59	A46 I
4974	C ₇ H ₁₅ -CHF-COO-	-C ₁₂ H ₂₅	S K22	S? A61 I
4976	C ₈ H ₁₇ -CHF-COO-	-C ₉ H ₁₉	1 K64	A46 I
4977	C ₈ H ₁₇ -CHF-COO-	-C ₁₀ H ₂₁	1 K59	C*43 A46 N*48 I
4978	C ₈ H ₁₇ -CHF-COO-	-C ₁₂ H ₂₅	S K23	S87 I
4979	C ₄ H ₉ -CHF-CH ₂ -O-	-C ₁₀ H ₂₁	S K48	C*43 A66 I
4980	C ₄ H ₉ -CHF-CH ₂ -O-	-C ₁₂ H ₂₅	S K59	S37 S39 C*43 A71 I
4981	C ₅ H ₁₁ -CHF-CH ₂ -O-	-C ₈ H ₁₇	S K24	A35 I
4982	C ₅ H ₁₁ -CHF-CH ₂ -O-	-C ₁₀ H ₂₁	S K49	C*60 A66 I
4983	C ₅ H ₁₁ -CHF-CH ₂ -O-	-C ₁₂ H ₂₅	S K60	S49 C*61 A72 I
4984	C ₆ H ₁₃ -CHF-CH ₂ -O-	-C ₈ H ₁₇	S K62	A59 I
4985	C ₆ H ₁₃ -CHF-CH ₂ -O-	-C ₉ H ₁₉	S K63	A67 I
4986	C ₆ H ₁₃ -CHF-CH ₂ -O-	-C ₁₀ H ₂₁	S K61	S49 C*62 A71 I
4987	C ₆ H ₁₃ -CHF-CH ₂ -O-	-C ₁₂ H ₂₅	S K56	C*70 A74 I

TABLE 47




No	L	R	Cr	LC
5039	CF ₃ -O-	-C ₃ H ₇	K43.1	S48.2 N-17 E
5040	CF ₃ -O-	-C ₅ H ₁₁	K32	A45.2 N-6
5041	CF ₃ -O-	-C ₇ H ₁₅	K25	A34 N-20 E
5042	C ₉ F ₁₃ -O-	-C ₈ H ₁₇	K65.1	A115.1 I
5043	C ₃ F ₇ -CH ₂ -O-	-C ₁₀ H ₂₁	K36	C52 A64 I
5044	C ₅ F ₁₁ -CH ₂ -O-	-C ₁₀ H ₂₁	K47	C73 A84 I
5045	C ₆ F ₁₃ -CH ₂ -O-	-C ₇ H ₁₅	K?	C? A? I
5046	C ₇ F ₁₅ -CH ₂ -O-	-C ₆ H ₁₃	K50	C56 A133 I
5047	C ₇ F ₁₅ -CH ₂ -O-	-C ₇ H ₁₅	K54	C67 A125 I
5048	C ₇ F ₁₅ -CH ₂ -O-	-C ₈ H ₁₇	K71	C80 A117 I
5049	C ₇ F ₁₅ -CH ₂ -O-	-C ₉ H ₁₉	K71	C85 A112 I
5050	C ₇ F ₁₅ -CH ₂ -O-	-C ₁₀ H ₂₁	K75	C87 A104 I
5051	C ₈ F ₁₇ -CH ₂ -O-	-C ₇ H ₁₅	K?	C? A? I
5052	C ₉ F ₁₉ -CH ₂ -O-	-C ₇ H ₁₅	K?	C? A? I
5053	C ₁₀ F ₂₁ -CH ₂ -O-	-C ₃ H ₇	K?	C? A? I
5054	C ₁₀ F ₂₁ -CH ₂ -O-	-C ₅ H ₁₁	K?	C? A? I
5055	C ₆ F ₁₃ -C ₃ H ₆ -O-	-C ₈ H ₁₇	K63	C95 A132 I
5056	C ₄ F ₉ -C ₄ H ₈ -O-	-C ₈ H ₁₇	K66	A114 I
5057	C ₄ F ₉ -C ₄ H ₈ -O-	-C ₁₀ H ₂₁	K58	C80 A106 I
5061	H-CF ₂ -O-	-C ₃ H ₇	K41	NO E
5062	H-CF ₂ -O-	-C ₅ H ₁₁	K21	A26 NO E
5063	H-CF ₂ -O-	-C ₇ H ₁₅	K26	A32 NO E
5064	H-CF ₂ -O-	-C ₈ H ₁₇	K26.3	S31.6 N-3 E
5065	H-C ₂ F ₄ -O-	-C ₇ H ₁₅	K46	X43 I
5066	H-CF ₂ -S-	-C ₃ H ₇	K53.2	N-16 E
5067	H-CF ₂ -S-	-C ₅ H ₁₁	K43.1	N-16 E
5068	C ₆ H ₁₃ -CHCF ₃ -O-CH ₂ -	-C ₁₀ H ₂₁	1 K56.8	S18.4 I
5070	C ₄ H ₉ -CHCF ₃ -CH ₂ -COO-	-C ₁₀ H ₂₁	1 K28	S1 S7 I
5072	H ₂ C=CH-COO-C ₆ H ₁₂ -O-	-C ₈ H ₁₇	K50	S52.5 N53 I

TABLE 48




No	L	R	Cr	LC
5106	CH ₃ -CH=CH-CH ₂ -O-	-C ₆ H ₁₃	K59	A65 N75 I
5107	C ₂ H ₅ -CH=CH-CH ₂ -O-	-C ₇ H ₁₅	K31	C30 N62 I
5108	C ₂ H ₅ -CH=CH-CH ₂ -O-	-C ₈ H ₁₇	K53	C49 A55 N61 I
5109	C ₂ H ₅ -CH=CH-CH ₂ -O-	-C ₉ H ₁₉	K56	C42 A68 I
5111	C ₃ H ₇ -CH=CH-CH ₂ -O-	-C ₈ H ₁₇	K43	C51 N66 I
5112	C ₃ H ₇ -CH=CH-CH ₂ -O-	-C ₉ H ₁₉	K49	C63 A70 N72 I
5113	C ₃ H ₇ -CH=CH-CH ₂ -O-	-C ₁₀ H ₂₁	K30	C53 A65.5 I
5114	C ₄ H ₉ -CH=CH-CH ₂ -O-	-C ₇ H ₁₅	K22	C33 N63 I
5115	C ₄ H ₉ -CH=CH-CH ₂ -O-	-C ₈ H ₁₇	K30	C55 N64 I
5116	C ₄ H ₉ -CH=CH-CH ₂ -O-	-C ₉ H ₁₉	K46	C66 A70 I
5117	C ₅ H ₁₁ -CH=CH-CH ₂ -O-	-C ₇ H ₁₅	K38	C35 N68 I
5118	C ₅ H ₁₁ -CH=CH-CH ₂ -O-	-C ₈ H ₁₇	K24	C56 N68 I
5119	C ₅ H ₁₁ -CH=CH-CH ₂ -O-	-C ₉ H ₁₉	K42	C70 A72 N73 I
5120	C ₆ H ₁₃ -CH=CH-CH ₂ -O-	-C ₇ H ₁₅	K40	C41 N66 I
5121	C ₆ H ₁₃ -CH=CH-CH ₂ -O-	-C ₈ H ₁₇	K29	C58 N66 I
5122	C ₆ H ₁₃ -CH=CH-CH ₂ -O-	-C ₉ H ₁₉	K20	C70 A71 N72 I
5123	C ₇ H ₁₅ -CH=CH-CH ₂ -O-	-C ₇ H ₁₅	K49	C42 N68 I
5124	C ₇ H ₁₅ -CH=CH-CH ₂ -O-	-C ₈ H ₁₇	K31	C59 N68 I
5125	C ₇ H ₁₅ -CH=CH-CH ₂ -O-	-C ₉ H ₁₉	K37	C72 A73 N74 I
5126	C ₈ H ₁₇ -CH=CH-CH ₂ -O-	-C ₇ H ₁₅	K43	C47 N66 I
5127	C ₈ H ₁₇ -CH=CH-CH ₂ -O-	-C ₈ H ₁₇	K40	C60 N66 I
5128	C ₈ H ₁₇ -CH=CH-CH ₂ -O-	-C ₉ H ₁₉	K36	C72 A73 I
5129	C ₉ H ₁₉ -CH=CH-CH ₂ -O-	-C ₇ H ₁₅	K55	C49 N68 I
5130	C ₉ H ₁₉ -CH=CH-CH ₂ -O-	-C ₈ H ₁₇	K44	C62 N68 I
5131	C ₉ H ₁₉ -CH=CH-CH ₂ -O-	-C ₉ H ₁₉	K42	C74 I
5132	H ₂ C=CH-C ₂ H ₄ -O-	-C ₄ H ₉	K37.3	N12.5 U
5133	H ₂ C=CH-C ₂ H ₄ -O-	-C ₇ H ₁₅	K38	A41 N49 I
5134	H ₂ C=CH-C ₂ H ₄ -O-	-C ₈ H ₁₇	K34	A46 I
5135	H ₂ C=CH-C ₂ H ₄ -O-	-C ₉ H ₁₉	K55	A56 I

TABLE 49




No	L	R	Cr	LC
5139	$C_3H_7-CH=CH-C_2H_4-COO-$	$-C_8H_{17}$	K54	A45 N50 I
5140	$C_3H_7-CH=CH-C_2H_4-COO-$	$-C_9H_{19}$	K67	A61 I
5142	$H_2C=CH-C_3H_8-O-$	$-C_7H_{15}$	K46	A45 N63 I
5143	$H_2C=CH-C_3H_8-O-$	$-C_8H_{17}$	K38	A54 N58 I
5144	$H_2C=CH-C_3H_8-O-$	$-C_9H_{19}$	K40	A65 I
5145	$CH_3-CH=CH-C_3H_8-O-$	$-C_9H_{19}$	K48	C35 A70 N72 I
5146	$C_3H_7-CH=CH-C_3H_8-O-$	$-C_7H_{15}$	K39	C45 N65 I
5147	$C_3H_7-CH=CH-C_3H_8-O-$	$-C_8H_{17}$	K32	C56 A59 N63 I
5148	$C_3H_7-CH=CH-C_3H_8-O-$	$-C_9H_{19}$	K42	C64 A73 I
5151	$H_2C=CH-C_4H_9-O-$	$-C_7H_{15}$	K27	A43 N57 I
5152	$H_2C=CH-C_4H_9-O-$	$-C_8H_{17}$	K44	A51 N55 I
5153	$H_2C=CH-C_4H_9-O-$	$-C_9H_{19}$	K48	A62 I
5154	$H_2C=CH-C_4H_9-O-$	$-C_{10}H_{21}$	K55.5	C33 A62 I
5155	$CH_3-CH=CH-C_4H_9-COO-$	$-C_7H_{15}$	K51	A34 N55 I
5156	$CH_3-CH=CH-C_4H_9-COO-$	$-C_8H_{17}$	K48	C39 A46 N52 I
5157	$CH_3-CH=CH-C_4H_9-COO-$	$-C_9H_{19}$	K56	C48 A60 I
5160	$H_2C=CH-C_5H_{10}-O-$	$-C_7H_{15}$	K56	C34 A47 N67 I
5161	$H_2C=CH-C_5H_{10}-O-$	$-C_8H_{17}$	K37	C30 A58 N64 I
5162	$H_2C=CH-C_5H_{10}-O-$	$-C_9H_{19}$	K31	A69 I
5163	$CH_3-CH=CH-C_5H_{10}-O-$	$-C_7H_{15}$	K39	C45 A65 I
5164	$CH_3-CH=CH-C_5H_{10}-O-$	$-C_8H_{17}$	K40	C52 A57 N67 I
5165	$CH_3-CH=CH-C_5H_{10}-O-$	$-C_9H_{19}$	K39	C53 A71 N72 I
5166	$H_2C=CH-C_5H_{10}-COO-$	$-C_7H_{15}$	K43	A36 N46 I
5167	$H_2C=CH-C_5H_{10}-COO-$	$-C_8H_{17}$	K37	C34 A43 N44 I
5168	$H_2C=CH-C_5H_{10}-COO-$	$-C_9H_{19}$	K48	C42 A56 I
5169	$H_2C=CH-C_5H_{10}-O-$	$-C_4H_9-CHMe-C_2H_5$	S K35	C*29 N*46 I
5170	$H_2C=CH-C_5H_{10}-O-$	$-C_5H_{10}-CHMe-C_2H_5$	S K7	C*19 N*39 I

TABLE 50




No	L	R	Cr	LC
5171	H ₂ C=CH-C ₆ H ₁₂ -O-	-C ₇ H ₁₅	K36	C33 A48 N62 I
5172	H ₂ C=CH-C ₆ H ₁₂ -O-	-C ₈ H ₁₇	K19.2	C33.3 A56.1 N60.2 I
5173	H ₂ C=CH-C ₆ H ₁₂ -O-	-C ₉ H ₁₉	K37	A67 I
5174	H ₂ C=CH-C ₆ H ₁₂ -O-	-C ₁₀ H ₂₁	K38.2	C49.6 A67.9 I
5175	H ₂ C=CH-C ₆ H ₁₂ -O-	-O-C ₈ H ₁₇	K48.5	C76.3 A92 N92.6 I
5176	H ₂ C=CH-C ₆ H ₁₂ -O-	-C ₄ H ₉ -CHMe-C ₂ H ₅	S K29	C*28 N*40 I
5177	H ₂ C=CH-C ₆ H ₁₂ -O-	-C ₅ H ₁₀ -CHMe-C ₂ H ₅	S K4	C*15 N*32 I
5178	H ₂ C=CH-C ₇ H ₁₄ -O-	-C ₇ H ₁₅	K52	C43 A54 N67 I
5179	H ₂ C=CH-C ₇ H ₁₄ -O-	-C ₈ H ₁₇	K27	C45 A62 N66 I
5180	H ₂ C=CH-C ₇ H ₁₄ -O-	-C ₉ H ₁₉	K19	C39 A71 I
5181	H ₂ C=CH-C ₇ H ₁₄ -O-	-C ₁₀ H ₂₁	K32.5	C55 A72 I
5182	H ₂ C=CH-C ₇ H ₁₄ -O-	-C ₄ H ₉ -CHMe-C ₂ H ₅	S K16	C*35 N*48 I
5183	H ₂ C=CH-C ₇ H ₁₄ -O-	-C ₅ H ₁₀ -CHMe-C ₂ H ₅	S K-1	C*28 N*42 I
5184	H ₂ C=CH-C ₈ H ₁₆ -O-	-C ₇ H ₁₅	K43	C42 A55 N64 I
5185	H ₂ C=CH-C ₈ H ₁₆ -O-	-C ₈ H ₁₇	K24	C46 A60 N63 I
5186	H ₂ C=CH-C ₈ H ₁₆ -O-	-C ₉ H ₁₉	K35	C45 A70 I
5187	H ₂ C=CH-C ₈ H ₁₆ -O-	-C ₁₀ H ₂₁	K33	C57 A70 I
5188	H ₂ C=CH-C ₈ H ₁₆ -O-	-C ₄ H ₉ -CHMe-C ₂ H ₅	S K17	C*34 N*44 I
5189	H ₂ C=CH-C ₈ H ₁₆ -O-	-C ₅ H ₁₀ -CHMe-C ₂ H ₅	S K12	C*27 N*38 I
5191	H ₂ C=CH-C ₉ H ₁₈ -O-	-C ₇ H ₁₅	K49	C46 A59 N67 I
5192	H ₂ C=CH-C ₉ H ₁₈ -O-	-C ₈ H ₁₇	K33.9	C53 A64.4 N66.2 I
5193	H ₂ C=CH-C ₉ H ₁₈ -O-	-C ₉ H ₁₉	K31.3	C52.8 A71.7 I
5194	H ₂ C=CH-C ₉ H ₁₈ -O-	-C ₁₀ H ₂₁	K39.9	C65.2 A72.5 I
5195	H ₂ C=CH-C ₉ H ₁₈ -O-	-C ₁₂ H ₂₅	K45.9	C75.5 A76.5 I
5196	H ₂ C=CH-C ₁₀ H ₂₀ -O-	-C ₇ H ₁₅	K50	C45 A60 N65 I
5197	H ₂ C=CH-C ₁₀ H ₂₀ -O-	-C ₈ H ₁₇	K36	C50 A63 N64 I
5198	H ₂ C=CH-C ₁₀ H ₂₀ -O-	-C ₉ H ₁₉	K46	C50 A70 I
5199	H ₂ C=CH-C ₉ H ₁₈ -O-	-O-C ₈ H ₁₇	K44.1	C78.5 A94.5 I
5200	H ₂ C=CH-C ₉ H ₁₈ -O-	-C ₄ H ₉ -CHMe-C ₂ H ₅	S K20	C*40 N*49 I
5201	H ₂ C=CH-C ₁₀ H ₂₀ -O-	-C ₄ H ₉ -CHMe-C ₂ H ₅	S K35	C*40 N*47 I

TABLE 51




No	L	R	Cr	LC
5202	H ₂ C=CH-C ₉ H ₁₉ -O-	-C ₉ H ₁₉ -CHMe-C ₂ H ₅	S K17	C*36 N*45 I
5203	H ₂ C=CH-C ₁₀ H ₂₀ -O-	-C ₉ H ₁₉ -CHMe-C ₂ H ₅	S K33	C*37 N*43 I
5204	C ₃ H ₇ -CH%CH-CH ₂ -O-	-C ₉ H ₁₉	K32	A17 I
5208	CH ₃ -CH%CH-C ₂ H ₄ -O-	-C ₇ H ₁₅	K45	A41 N47 I
5209	CH ₃ -CH%CH-C ₂ H ₄ -O-	-C ₈ H ₁₇	K34	A45 I
5210	CH ₃ -CH%CH-C ₂ H ₄ -O-	-C ₉ H ₁₉	K48	C25 A55 I
5211	C ₂ H ₅ -CH%CH-C ₂ H ₄ -O-	-C ₇ H ₁₅	K43	A45 N48 I
5212	C ₂ H ₅ -CH%CH-C ₂ H ₄ -O-	-C ₈ H ₁₇	K42	C32 A47 I
5213	C ₂ H ₅ -CH%CH-C ₂ H ₄ -O-	-C ₉ H ₁₉	K58	C41 A56 I
5214	C ₃ H ₇ -CH%CH-C ₂ H ₄ -O-	-C ₇ H ₁₅	K20	A44 I
5215	C ₃ H ₇ -CH%CH-C ₂ H ₄ -O-	-C ₈ H ₁₇	K33	C35 A46 I
5216	C ₃ H ₇ -CH%CH-C ₂ H ₄ -O-	-C ₉ H ₁₉	K34	C45 A54 I
5217	C ₄ H ₉ -CH%CH-C ₂ H ₄ -O-	-C ₇ H ₁₅	K28	A43 N44 I
5218	C ₄ H ₉ -CH%CH-C ₂ H ₄ -O-	-C ₈ H ₁₇	K25	C34 A46 I
5219	C ₄ H ₉ -CH%CH-C ₂ H ₄ -O-	-C ₉ H ₁₉	K24	C43 A54 I
5220	C ₅ H ₁₁ -CH%CH-C ₂ H ₄ -O-	-C ₇ H ₁₅	K25	A40 I
5221	C ₅ H ₁₁ -CH%CH-C ₂ H ₄ -O-	-C ₈ H ₁₇	K12	C30 A42 I
5222	C ₅ H ₁₁ -CH%CH-C ₂ H ₄ -O-	-C ₉ H ₁₉	K6	C38 A51 I
5223	C ₆ H ₁₃ -CH%CH-C ₂ H ₄ -O-	-C ₇ H ₁₅	K33	A39 I
5224	C ₆ H ₁₃ -CH%CH-C ₂ H ₄ -O-	-C ₈ H ₁₇	K22	C25 A41 I
5225	C ₆ H ₁₃ -CH%CH-C ₂ H ₄ -O-	-C ₉ H ₁₉	K19	C34 A49 I
5226	C ₇ H ₁₅ -CH%CH-C ₂ H ₄ -O-	-C ₇ H ₁₅	K40	A37 I
5227	C ₇ H ₁₅ -CH%CH-C ₂ H ₄ -O-	-C ₈ H ₁₇	K30	C20 A39 I
5228	C ₇ H ₁₅ -CH%CH-C ₂ H ₄ -O-	-C ₉ H ₁₉	K26	C24 A47 I
5229	C ₈ H ₁₇ -CH%CH-C ₂ H ₄ -O-	-C ₇ H ₁₅	K31	A35 I
5230	C ₈ H ₁₇ -CH%CH-C ₂ H ₄ -O-	-C ₈ H ₁₇	K32	C14 A41 I
5231	C ₈ H ₁₇ -CH%CH-C ₂ H ₄ -O-	-C ₉ H ₁₉	K29	C14 A50 I
5232	CH ₃ -CH%CH-C ₃ H ₆ -O-	-C ₉ H ₁₉	K22	A46 I
5233	C ₂ H ₅ -CH%CH-C ₃ H ₆ -COO-	-C ₇ H ₁₅	K26	A31 I

TABLE 52




No	L	R	Cr	LC
27740	Cl-CF ₂ -O-	-C ₆ H ₅	K30	S130.6 N135.2 I
27749	NC-	-C ₇ H ₁₅	K82	A158 N223 I
27750	NC-	-O-C ₂ H ₅	K144.5	N232 B
27751	NC-	-O-C ₃ H ₇	K114.5	N223.5 B
27752	NC-	-O-C ₅ H ₁₁	K93	N205 B
27753	NC-	-CH ₂ -CHMe-C ₂ H ₅	1 K76	S125 N*178 I
27754	NC-	-C ₂ H ₄ -CHMe-C ₂ H ₅	1 K101	S159 N*189.5 I
27755	C ₂ H ₅ -	-C ₇ H ₁₅	K68	S179 N182 I
27756	C ₃ H ₇ -	-C ₂ H ₅	K125.5	S128.5 N167 I
27757	C ₃ H ₇ -	-C ₃ H ₇	K116.5	S175 N194.5 I
27758	C ₃ H ₇ -	-C ₅ H ₁₁	K51	S190 I
27759	C ₄ H ₉ -	-C ₂ H ₅	K108.5	S140 N163.5 I
27760	C ₄ H ₉ -	-C ₅ H ₁₁	K37.5	S187 I
27761	C ₅ H ₁₁ -	-C ₂ H ₅	K101	S139 N167 I
27762	C ₅ H ₁₁ -	-C ₃ H ₇	K93.5	S179 N190 I
27763	C ₅ H ₁₁ -	-C ₅ H ₁₁	K39.5	S189.2 I
27764	C ₅ H ₁₁ -	-C ₇ H ₁₅	K122.5	S186.5 I
27765	C ₇ H ₁₅ -	-C ₂ H ₅	K80	S136.5 N157 I
27768	C ₆ H ₁₃ -CHMe-O-CH ₂ -	-C ₇ H ₁₅	1 K36.5	A98.4 I
27769	C ₂ H ₅ -CHMe-CH ₂ -O-	-O-C ₆ H ₁₃	S K64.6	B104.9 A160.5 I
27770	C ₂ H ₅ -CHMe-CH ₂ -O-	-O-C ₉ H ₁₉	S K61.7	B108.2 A156 I
27771	C ₂ H ₅ -CHMe-C ₃ H ₆ -O-	-O-C ₆ H ₁₃	S K68	B101 A160.9 I
27772	C ₂ H ₅ -CHMe-C ₃ H ₆ -O-	-O-C ₉ H ₁₉	S K63.5	B103 A157.4 I

TABLE 53




No	L	R	Cr	LC
28508	C ₅ H ₁₁ -	-OOC-C ₁₀ H ₂₁	K118	C133 N172 I
28509	C ₅ H ₁₁ -	-OOC-C ₁₁ H ₂₃	K120	C138 N169 I
28510	C ₄ H ₉ -CHF-COO-	-C ₆ H ₁₃	S K34	B98 A137 I
28511	C ₄ H ₉ -CHF-COO-	-C ₇ H ₁₅	S K53	B101 A143 I
28512	C ₄ H ₉ -CHF-COO-	-C ₈ H ₁₇	S K41	B109 A143 I
28513	C ₄ H ₉ -CHF-COO-	-C ₉ H ₁₉	S K49	B113 A145 I
28514	C ₄ H ₉ -CHF-COO-	-C ₁₀ H ₂₁	S K48	B116 A145 I
28515	C ₄ H ₉ -CHF-COO-	-O-C ₆ H ₁₃	R K58	C*81 A161 N*165 I
28516	C ₄ H ₉ -CHF-COO-	-O-C ₇ H ₁₅	R K44	B78 C*95 A162 N*163 I
28517	C ₄ H ₉ -CHF-COO-	-O-C ₈ H ₁₇	R K53	888 C*102 A162 I
28518	C ₄ H ₉ -CHF-COO-	-O-C ₉ H ₁₉	R K60	892 C*106 A163 I
28519	C ₄ H ₉ -CHF-COO-	-O-C ₁₀ H ₂₁	R K35	S70 898 C*108 A165 I
28522	C ₅ H ₁₁ -	-O-CH ₂ -CH=CH-C ₅ H ₁₁	K97	C115 N176 I
28523	C ₅ H ₁₁ -	-O-CH ₂ -CH=CH-C ₆ H ₁₃	K94	C125 N170 I
28524	C ₅ H ₁₁ -	-O-CH ₂ -CH=CH-C ₇ H ₁₅	K86	C135 N167 I
28525	C ₅ H ₁₁ -	-O-CH ₂ -CH=CH-C ₈ H ₁₇	K93	C140 N163 I
28526	C ₅ H ₁₁ -	-O-C ₃ H ₆ -CH=CH-C ₃ H ₇	K87	C93 N184 I
28528	C ₅ H ₁₁ -	-O-C ₅ H ₁₀ -CH=CH ₂	K55	C65 A112 N185 I
28529	C ₅ H ₁₁ -	-O-C ₅ H ₁₀ -CH=CH-CH ₃	K81	C111 A130 N185 I
28530	C ₅ H ₁₁ -	-O-C ₆ H ₁₂ -CH=CH ₂	K67	C96 A121 N176 I
28531	C ₅ H ₁₁ -	-O-C ₇ H ₁₄ -CH=CH ₂	K59	C91 A142 N176 I
28532	C ₅ H ₁₁ -	-O-C ₈ H ₁₆ -CH=CH ₂	K55	C103 A145 N169 I
28533	C ₅ H ₁₁ -	-O-C ₉ H ₁₈ -CH=CH ₂	K57	C97 A151 N168 I
28535	C ₅ H ₁₁ -	-O-C ₄ H ₈ -CH=CH-C ₂ H ₅	K86	C85 N168 I
28536	C ₅ H ₁₁ -	-O-C ₄ H ₈ -CH/CH ₂ \CH ₂	K81	S75 N180 I
28537	C ₃ H ₇ -	-O-C ₆ H ₁₂ -CH/CH ₂ \CH ₂	K80	S70 C84 N174 I


TABLE 54



No	L	R	Cr	LC
28896	C ₆ H ₁₁ -	-C ₆ H ₁₁	K33.4	S121.2 I




No	L	R	Cr	LC
28548	C ₆ H ₁₇ -O-	-C ₆ H ₁₇	K51	C63 A113 N121 I




No	L	R	Cr	LC
33521	C ₅ H ₁₁ -	-C ₆ H ₁₃	K72	S65 N104 I
33522	C ₅ H ₁₁ -	-C ₇ H ₁₅	K76	S86 N109 I
33523	C ₅ H ₁₁ -	-C ₉ H ₁₉	K52	S107 N113 I
33524	C ₆ H ₁₃ -	-C ₆ H ₁₃	K61	S76 N100.8 I
33525	C ₆ H ₁₃ -	-C ₇ H ₁₅	K48	S92 N107 I
33526	C ₆ H ₁₃ -	-C ₉ H ₁₉	K66	S109 N110 I
33527	C ₆ H ₁₇ -	-C ₆ H ₁₇	K73	F66 C103.5 I

TABLE 55




No	L	R	Cr	LC
33600	C ₄ H ₉ -O-CHMe-COO-	-C ₈ H ₁₇	S K44	C*60 N*96 I
33601	C ₄ H ₉ -O-CHMe-COO-	-O-C ₈ H ₁₇	S K68	C*103 N*138 I
33603	C ₆ H ₁₃ -O-	-C ₄ H ₉ -CHMe-C ₂ H ₅	S K56	C*54 N*152 I
33604	C ₇ H ₁₅ -O-	-C ₄ H ₉ -CHMe-C ₂ H ₅	S K64	C*65 N*148 I
33605	C ₈ H ₁₇ -O-	-C ₄ H ₉ -CHMe-C ₂ H ₅	S K71	C*70 N*142 I
33606	C ₉ H ₁₉ -O-	-C ₄ H ₉ -CHMe-C ₂ H ₅	S K78	C*77 N*142 I
33607	C ₁₀ H ₂₁ -O-	-C ₄ H ₉ -CHMe-C ₂ H ₅	S K74	C*82 N*141 I
33608	C ₁₁ H ₂₃ -O-	-C ₄ H ₉ -CHMe-C ₂ H ₅	S K78	C*85 N*136 I
33609	C ₁₂ H ₂₅ -O-	-C ₄ H ₉ -CHMe-C ₂ H ₅	S K83	C*88 N*133 I
33610	C ₆ H ₁₃ -O-	-C ₅ H ₁₁ -CHMe-C ₂ H ₅	S K72	C*50 N*148 I
33611	C ₇ H ₁₅ -O-	-C ₅ H ₁₁ -CHMe-C ₂ H ₅	S K56	C*64 N*144 I
33612	C ₈ H ₁₇ -O-	-C ₅ H ₁₁ -CHMe-C ₂ H ₅	S K56	C*72 N*142 I
33613	C ₉ H ₁₉ -O-	-C ₅ H ₁₁ -CHMe-C ₂ H ₅	S K68	C*80 N*138 I
33614	C ₁₀ H ₂₁ -O-	-C ₅ H ₁₁ -CHMe-C ₂ H ₅	S K86	C*84 N*137 I
33615	C ₁₁ H ₂₃ -O-	-C ₅ H ₁₁ -CHMe-C ₂ H ₅	S K83	C*90 N*132 I
33616	C ₁₂ H ₂₅ -O-	-C ₅ H ₁₁ -CHMe-C ₂ H ₅	S K69	C*94 N*132 I
33618	C ₆ H ₁₃ -CHMe-O-	-O-C ₈ H ₁₇	1 K72	C*48 N*115 I
33620	CH ₃ -CHMe-CHCl-COO-	-C ₇ H ₁₅	S K70	C*96 N*202 I
33621	CH ₃ -CHMe-CHCl-COO-	-C ₉ H ₁₉	S K62	C*69 N*157 I
33622	C ₇ H ₁₅ -CHMe-CHCl-COO-	-C ₈ H ₁₇	3 K?	C*77 N*124 I

TABLE 56




No	L	R	Cr	LC
36376	C ₆ H ₅ -	-O-C ₆ H ₅ -	2 K66	S190 I




No	L	R	Cr	LC
37030	C ₂ H ₅ -	-CN	K137	S136 N243 I
37031	C ₅ H ₁₁ -	-CN	K117	S192 N248 I
37033	CH ₃ -	-C ₁₀ H ₂₁ -	K76	C77 N124 I
37035	C ₂ H ₅ -	-C ₁₀ H ₂₁ -	K82	C82 N142 I
37038	C ₃ H ₇ -	-C ₁₀ H ₂₁ -	K76	C89 N161 I
37039	C ₃ H ₇ -	-C ₁₂ H ₂₅ -	K64.9	S76.3 C108.1 N152.8 I
37041	C ₄ H ₉ -	-C ₁₀ H ₂₁ -	K40	B82 C99 N160 I
37042	C ₄ H ₉ -	-C ₁₂ H ₂₅ -	K80	S82 S83.8 C115.3 N152.7 I
37046	C ₅ H ₁₁ -	-C ₁₀ H ₂₁ -	K64	B85 C104 N161 I
37047	C ₅ H ₁₁ -	-C ₁₁ H ₂₃ -	K70	S80 S82.7 C114.5 N160.5 I
37048	C ₅ H ₁₁ -	-C ₁₂ H ₂₅ -	K67	S83 S87.2 C121.5 N156 I
37051	C ₇ H ₁₅ -	-C ₁₀ H ₂₁ -	K78	B89 C116 N158 I
37052	C ₉ H ₁₉ -	-C ₁₀ H ₂₁ -	K77	S85 C123 N153 I
37053	C ₁₀ H ₂₁ -	-C ₁₀ H ₂₁ -	K77	S87 C125 N150 I
37054	C ₅ H ₁₁ -	-O-C ₆ H ₅ -	K72.1	S68 S74 C100 N193 I
37055	C ₅ H ₁₁ -	-O-C ₉ H ₁₉ -	K74.3	G69 C117.7 N189 I
37056	C ₅ H ₁₁ -	-O-C ₁₀ H ₂₁ -	K74.7	G72.5 C129.8 N186.5 I
37058	H ₂ C=CH-C ₂ H ₅ -	-C ₁₀ H ₂₁ -	K71	C92 N162 I
37059	CH ₃ -CH=CH-C ₂ H ₅ -	-C ₁₀ H ₂₁ -	K52	S56 S64 S69 C92 N170 I

TABLE 57




No	L	R	Cr	LC
37078	(Me) ₂ C=CH-C ₂ H ₄ -	-C ₁₀ H ₂₁	2 K40	C83 N106 I
37079	(Me) ₂ C=CH-C ₂ H ₄ -	-O-C ₁₀ H ₂₁	2 K82	C112 N138 I
37080	CH ₃ -	-C ₁₀ H ₂₁	2 K50	SS4 C68 N107 I




No	L	R	Cr	LC
37109	H-	-C ₆ H ₁₃	K44	N53 W
37110	H-	-C ₈ H ₁₇	K41.3	C51 A57.6 N60.2 W
37111	H-	-C ₉ H ₁₉	K52.8	C56.8 A67.2 W
37112	H-	-C ₁₀ H ₂₁	K44	C64.9 A67.7 W
37113	H-	-C ₁₁ H ₂₃	K48	C70.2 A71.6 W
37114	H-	-C ₁₂ H ₂₅	K52	C72.3 W
37115	H-	-O-C ₇ H ₁₅	K56.4	C71.3 A83.4 N85.1 W
37116	H-	-O-C ₈ H ₁₇	K69.2	C75.8 A90.2 W
37117	H-	-O-C ₁₁ H ₂₃	K68	C95 W
37118	C ₂ H ₅ -OOC-	-C ₈ H ₁₇	1 K38	C*36 I

TABLE 58




No	L	R	Cr	LC
9165	C ₂ H ₅ -CHMe-CH ₂ -OOC-	-O-C ₁₁ H ₂₂ -O-H	S K80	C*58.9 A72.8 I
9179	C ₅ H ₁₁ -	-Cl	K69	N37 E
9182	C ₁₀ H ₂₁ -O-	-Cl	K85.5	C86.5 I
9200	CH ₃ -	-CN	K160	N65 E
9201	C ₂ H ₅ -	-CN	K110	N62 E
9209	C ₁₀ H ₂₁ -	-CN	K64.4	A47.9 N62.1 B
9210	C ₁₁ H ₂₃ -	-CN	K64	A61.4 N66.7 I
9211	C ₁₂ H ₂₅ -	-CN	K72	A64.7 N66 I
9221	C ₁₄ H ₂₉ -O-	-CN	K96	A91 I
9226	C ₇ H ₁₅ -	-O-C ₃ H ₆ -CN	K85.5	A70 N77 I




No	L	R	Cr	LC
9227	C ₇ H ₁₅ -O-	-O-C ₃ H ₆ -CN	K105.5	N102.5 U
9228	C ₅ H ₁₁ -	-O-C ₅ H ₁₀ -CN	K63.4	A53 N70 I
9230	C ₂ H ₅ -CHMe-C ₂ H ₄ -	-CN	S K81	N*23.5 B
9237	H ₂ C=CH-CH ₂ -O-	-CN	K115.2	N104.1 I
9243	CH ₃ -NMe-	-NO ₂	K217	X220 Z
9256	C ₄ H ₉ -	-C ₇ H ₁₅	K6.2	S-2.5 N17.5 I
9257	C ₄ H ₉ -	-C ₈ H ₁₇	K14.2	S10.3 N16.5 I
9258	C ₄ H ₉ -	-C ₉ H ₁₉	K30	S20.5 N27 I
9259	C ₅ H ₁₁ -	-C ₆ H ₁₃	K31.2	S21 I
9260	C ₅ H ₁₁ -	-C ₇ H ₁₅	K27.3	S17.5 N39.1 I
9261	C ₅ H ₁₁ -	-C ₈ H ₁₇	K8.6	S30.5 N33.7 I
9262	C ₅ H ₁₁ -	-C ₉ H ₁₉	K28	S37 N44.9 I
9263	C ₆ H ₁₃ -	-C ₇ H ₁₅	K19.3	S20 N30 I
9264	C ₆ H ₁₃ -	-C ₈ H ₁₇	K22.2	S27.8 I
9265	C ₆ H ₁₃ -	-C ₉ H ₁₉	K23.7	S31.7 I
9266	C ₇ H ₁₅ -	-C ₇ H ₁₅	K41.6	S35.2 N40.8 I
9267	C ₇ H ₁₅ -	-C ₉ H ₁₉	K20	S43.8 I
9271	CH ₃ -	-O-CH ₃	K124.8	N32.1 E

TABLE 59




No	L	R	Cr	LC
5352	C ₁₂ H ₂₅ -	-CN	K87	A81 I
5353	C ₁₃ H ₂₇ -	-CN	K87	S80 B
5355	C ₈ H ₁₇ -O-	-CN	K84	A112 I
5356	C ₁₀ H ₂₁ -O-	-CN	K70	A111 I
5357	C ₁₂ H ₂₅ -O-	-CN	K85	A111 I
5358	C ₁₂ H ₂₅ -	-O-C ₄ H ₉	K48	S43 I
5360	CH ₃ -O-	-C ₈ H ₁₇	K68	A63 I
5361	CH ₃ -O-	-C ₁₂ H ₂₅	K90	A83 I
5362	C ₈ H ₁₇ -O-	-C ₈ H ₁₇	K65	C64 A79 I
5367	C ₁₂ H ₂₅ -O-	-O-CH ₂ -CHMe-C ₂ H ₅	S K63	A45 I
5369	C ₈ H ₁₇ -O-	-COO-CH ₂ -CHMe-C ₂ H ₅	S K41	S52 A60 I
5370	C ₁₂ H ₂₅ -O-	-COO-CH ₂ -CHMe-C ₂ H ₅	S K42	A60 I
5371	C ₈ H ₁₇ -O-	-O-C ₃ H ₆ -CHMe-C ₂ H ₅	S K42	C* 61 A66 I
5372	C ₁₂ H ₂₅ -O-	-O-C ₃ H ₆ -CHMe-C ₂ H ₅	S K50	C* 63 A72 I
5374	C ₂ H ₅ -CHMe-CH ₂ -O-	-O-C ₁₂ H ₂₅	S K56	A46 I
5376	C ₂ H ₅ -CHMe-CH ₂ -OOC-	-O-C ₁₂ H ₂₅	S K58	C* 45 A49 I
5377	C ₂ H ₅ -CHMe-C ₃ H ₆ -OOC-	-O-C ₁₂ H ₂₅	1 K?	A<? I
5378	C ₃ H ₇ -CHMe-C ₄ H ₉ -O-	-C ₈ H ₁₇	2 K48	C56. 5 I
5379	C ₂ H ₅ -CHMe-C ₅ H ₁₀ -O-	-C ₈ H ₁₇	2 K49	C62 I




No	L	R	Cr	LC
5381	C ₅ H ₁₁ -CH=CH-CH ₂ -O-	-C ₈ H ₁₇	K48	C77 I

TABLE 60




No	L	R	Cr	LC
5352	C ₁₂ H ₂₅ -	-CN	K87	A81 I
5353	C ₁₃ H ₂₇ -	-CN	K87	S80 B
5355	C ₈ H ₁₇ -O-	-CN	K84	A112 I
5356	C ₁₀ H ₂₁ -O-	-CN	K70	A111 I
5357	C ₁₂ H ₂₅ -O-	-CN	K85	A111 I
5358	C ₁₂ H ₂₅ -	-O-C ₄ H ₉	K48	S43 I
5360	CH ₃ -O-	-C ₈ H ₁₇	K68	A63 I
5361	CH ₃ -O-	-C ₁₂ H ₂₅	K90	A83 I
5362	C ₈ H ₁₇ -O-	-C ₈ H ₁₇	K65	C64 A79 I
5367	C ₁₂ H ₂₅ -O-	-O-CH ₂ -CHMe-C ₂ H ₅	S K63	A45 I
5369	C ₈ H ₁₇ -O-	-COO-CH ₂ -CHMe-C ₂ H ₅	S K41	S52 A60 I
5370	C ₁₂ H ₂₅ -O-	-COO-CH ₂ -CHMe-C ₂ H ₅	S K42	A60 I
5371	C ₈ H ₁₇ -O-	-O-C ₃ H ₆ -CHMe-C ₂ H ₅	S K42	C* 61 A66 I
5372	C ₁₂ H ₂₅ -O-	-O-C ₃ H ₆ -CHMe-C ₂ H ₅	S K50	C* 63 A72 I
5374	C ₂ H ₅ -CHMe-CH ₂ -O-	-O-C ₁₂ H ₂₅	S K56	A46 I
5376	C ₂ H ₅ -CHMe-CH ₂ -OOC-	-O-C ₁₂ H ₂₅	S K58	C* 45 A49 I
5377	C ₂ H ₅ -CHMe-C ₃ H ₆ -OOC-	-O-C ₁₂ H ₂₅	1 K?	A<? I
5378	C ₃ H ₇ -CHMe-C ₄ H ₉ -O-	-C ₈ H ₁₇	2 K48	C56.5 I
5379	C ₂ H ₅ -CHMe-C ₅ H ₁₁ -O-	-C ₈ H ₁₇	2 K49	C62 I

TABLE 61




No	L	R	Cr	LC
25427	CH ₃ -	-CN	K196	A221 N296 I
25428	C ₂ H ₅ -	-CN	K190	A197 N278 I
25429	C ₃ H ₇ -	-CN	K169	A179 N277 I
25430	C ₄ H ₉ -	-CN	K129	A139 N256 I
25431	C ₅ H ₁₁ -	-CN	K131	A140 N263 I
25432	C ₆ H ₁₃ -	-CN	K107	A125 N225 U
25433	C ₇ H ₁₅ -	-CN	K110	A132 N242 I
25434	C ₈ H ₁₇ -	-CN	K125	A133 N240 I
25435	C ₉ H ₁₉ -	-CN	K105	A107 N232 I
25436	C ₁₂ H ₂₅ -	-CN	K109	C119 A227 I
25437	C ₁₈ H ₃₃ -	-CN	K106	C119 A221 I
25438	CH ₃ -O-	-CN	K182	S169 N321 I
25439	C ₇ H ₁₅ -O-	-CN	K97	X267 I
25440	C ₈ H ₁₇ -O-	-CN	K96	X270 I
25441	C ₉ H ₁₉ -O-	-CN	K102	X263 I
25442	C ₁₀ H ₂₁ -O-	-CN	K104	X252 I
25443	C ₁₁ H ₂₃ -O-	-CN	K109	X263 I
25444	C ₁₂ H ₂₅ -O-	-CN	K105	X252 I
25445	C ₁₃ H ₂₇ -O-	-CN	K103	X246 I
25450	C ₄ H ₉ -	-C ₄ H ₉	K161.3	C166.4 N181.9 I
25451	C ₅ H ₁₁ -	-C ₅ H ₁₁	K134.3	C173.6 A182.2 N191.3 I
25452	C ₆ H ₁₃ -	-C ₆ H ₁₃	K116.1	C172.3 A179.2 I

TABLE 62




No	L	R	Cr	LC
25453	C ₇ H ₁₅ -	-C ₇ H ₁₅	K109.6	C175 A187 I
25454	C ₈ H ₁₇ -	-C ₈ H ₁₇	K104.6	C178 A187 I
25455	C ₉ H ₁₉ -	-C ₉ H ₁₉	K108.8	C177 I
25456	C ₁₀ H ₂₁ -	-C ₁₀ H ₂₁	K112	S106 C170.5 I
25458	C ₂ H ₅ -	-O-CH ₃	K162	A163 N229 I
25460	C ₄ H ₉ -	-O-CH ₃	K138	A139 N230 I
25462	C ₆ H ₁₃ -	-O-CH ₃	K137	A138 N206 U
25464	C ₈ H ₁₇ -	-O-CH ₃	K135	A136 N225 U
25466	C ₁₂ H ₂₅ -	-O-CH ₃	K131	A169 N180 I
25467	C ₁₆ H ₃₃ -	-O-CH ₃	K127	A175 I
25469	C ₅ H ₁₁ -	-OOC-C ₃ H ₇	K158	S200 N219 I
25473	C ₄ H ₉ -O-	-O-C ₄ H ₉	K170.3	C218 N246 I
25474	C ₅ H ₁₁ -O-	-O-C ₅ H ₁₁	K153.4	C211 N224 I
25475	C ₆ H ₁₃ -O-	-O-C ₆ H ₁₃	K135.7	B139.6 C212 N220 I
25476	C ₇ H ₁₅ -O-	-O-C ₇ H ₁₅	K126	B128.5 C211 N212 I
25477	C ₈ H ₁₇ -O-	-O-C ₈ H ₁₇	K118.8	B121.1 C209 I
25478	C ₉ H ₁₉ -O-	-O-C ₉ H ₁₉	K118.7	C204 I
25479	C ₁₀ H ₂₁ -O-	-O-C ₁₀ H ₂₁	K113	C201 I
25481	C ₈ H ₁₇ -O-	-COO-CHMe-C ₂ H ₅	1 K11	C'161 A184 I
25482	C ₁₀ H ₂₁ -O-	-COO-CHMe-C ₆ H ₁₃	1 K138	C'139 A162 I

TABLE 63




No	L	R	Cr	LC
25483	C ₁₂ H ₂₅ -	-O-CH ₂ -CHMe-C ₂ H ₅	S K67	S100 C* 155 A157 I
25484	C ₁₀ H ₂₁ -	-COO-CH ₂ -CHMe-C ₂ H ₅	S K85	C* 120 A166 I
25485	C ₁₂ H ₂₅ -	-COO-CH ₂ -CHMe-C ₂ H ₅	S K95	C* 130 A162 I
25486	C ₁₆ H ₃₃ -	-COO-CH ₂ -CHMe-C ₂ H ₅	S K95	C* 100 A165 I
25487	C ₇ H ₁₅ -O-	-COO-CH ₂ -CHMe-C ₂ H ₅	S K126	C* 175 A200 I
25488	C ₈ H ₁₇ -O-	-COO-CH ₂ -CHMe-C ₂ H ₅	S K109	C* 131 A182 I
25489	C ₉ H ₁₉ -O-	-COO-CH ₂ -CHMe-C ₂ H ₅	S K113	C* 171 A199 I
25490	C ₁₀ H ₂₁ -O-	-COO-CH ₂ -CHMe-C ₂ H ₅	S K98	C* 168 A187 I
25491	C ₁₁ H ₂₃ -O-	-COO-CH ₂ -CHMe-C ₂ H ₅	S K90	C* 160 A193 I
25492	C ₁₂ H ₂₅ -O-	-COO-CH ₂ -CHMe-C ₂ H ₅	S K110	C* 166 A186 I
25493	C ₁₃ H ₂₇ -O-	-COO-CH ₂ -CHMe-C ₂ H ₅	S K100	C* 160 A185 I
25494	C ₁₀ H ₂₁ -O-	-COO-C ₃ H ₆ -CHMe-C ₂ H ₅	S K68	C* 168 A199 I




No	L	R	Cr	LC
26944	F-	-O-C ₄ H ₉	K118.7	A202.3 I
26945	F-	-O-C ₅ H ₁₁	K120	A204 I
26946	F-	-O-C ₆ H ₁₃	K110.5	A195.5 I
26947	F-	-O-C ₇ H ₁₅	K117.1	A191.1 I
26948	F-	-O-C ₈ H ₁₇	K115.6	A188 I
26949	F-	-O-C ₉ H ₁₉	K116.2	A179.4 I
26950	F-	-O-C ₁₀ H ₂₁	K117.1	A178.6 I
26951	F-	-O-C ₁₂ H ₂₅	K121.3	A170.5 I
26952	C ₃ H ₇ -	-O-C ₄ H ₉	K91.7	E149.2 B161 A198.7 N201.3 I
26953	C ₃ H ₇ -	-O-C ₅ H ₁₁	K92.4	E143 B156 A191.2 N192.5 I
26954	C ₃ H ₇ -	-O-C ₆ H ₁₃	K92.6	E135.9 B149.8 A191.4 N192.1 I
26955	C ₃ H ₇ -	-O-C ₇ H ₁₅	K77.3	E132.7 B147.8 A187.9 I
26956	C ₃ H ₇ -	-O-C ₈ H ₁₇	K86.8	E130.5 B149.9 A198.5 U
26957	C ₃ H ₇ -	-O-C ₉ H ₁₉	K91.8	E120.7 B138.3 N180.5 I
26958	C ₃ H ₇ -	-O-C ₁₀ H ₂₁	K93.2	E118 B135 N181 I
26959	C ₃ H ₇ -	-O-C ₁₂ H ₂₅	K105.4	E108 B128.4 N171.7 I

TABLE 64




No	L	R	Cr	LC
5543	C ₆ H ₅ -	-C ₆ H ₁₃	K57.5	A56.5 I
5544	C ₆ H ₁₃ -	-C ₄ H ₉	K45	A61.5 I
5545	C ₆ H ₁₃ -	-C ₅ H ₁₁	K31	A68 I
5546	C ₆ H ₁₃ -	-C ₆ H ₁₃	K44	A68 I
5547	C ₆ H ₁₃ -	-C ₇ H ₁₅	K43	A69.5 I
5548	C ₇ H ₁₅ -	-C ₇ H ₁₅	K41	A72 I
5549	C ₈ H ₁₇ -	-C ₄ H ₉	K36.5	A64.5 I
5550	C ₈ H ₁₇ -	-C ₅ H ₁₁	K37	B46 A71 I
5551	C ₈ H ₁₇ -	-C ₆ H ₁₃	K44	B49 A72 I
5552	C ₈ H ₁₇ -	-C ₇ H ₁₅	K50	B51.5 A73.5 I
5553	C ₉ H ₁₉ -	-C ₄ H ₉	K37	A63.5 I
5554	C ₉ H ₁₉ -	-C ₅ H ₁₁	K42	A78 I
5555	C ₉ H ₁₉ -	-C ₆ H ₁₃	K34	A73 I
5556	C ₉ H ₁₉ -	-C ₇ H ₁₅	K44	A73 I
5560	C ₅ H ₁₁ -O-	-C ₄ H ₉	K55	A101 I
5561	C ₅ H ₁₁ -O-	-C ₆ H ₁₃	K58	A103 I
5562	C ₆ H ₁₃ -O-	-CH ₃	K99	A101 I
5563	C ₆ H ₁₃ -O-	-C ₄ H ₉	K57	A100 I
5564	C ₆ H ₁₃ -O-	-C ₆ H ₁₃	K55	A103 I

TABLE 65




No	L	R	Cr	LC
5567	C ₂ H ₅ -CHMe-CH ₂ -O-	-C ₆ H ₁₇	S K57.8	A53.9 I
5568	C ₂ H ₅ -CHMe-C ₃ H ₆ -O-	-C ₄ H ₉	S K42.5	C*66.2 A77.3 I
5569	C ₂ H ₅ -CHMe-C ₃ H ₆ -O-	-C ₅ H ₁₁	S K50.5	C*76.5 A82 I
5570	C ₂ H ₅ -CHMe-C ₃ H ₆ -O-	-C ₆ H ₁₃	S K49	C*75.1 A80.1 I
5571	C ₂ H ₅ -CHMe-C ₃ H ₆ -O-	-C ₇ H ₁₅	S K55	C*77.1 A82 I
5572	C ₂ H ₅ -CHMe-C ₃ H ₆ -O-	-C ₈ H ₁₇	S K48	C*72.1 A76.9 I
5573	C ₂ H ₅ -CHMe-C ₄ H ₈ -O-	-C ₆ H ₁₃	S K34.5	C*70.7 A78.1 I
5574	C ₂ H ₅ -CHMe-C ₄ H ₈ -O-	-C ₈ H ₁₇	S K52.5	C*70 A73 I
5575	C ₂ H ₅ -CHMe-C ₄ H ₈ -COO-	-C ₆ H ₁₇	S K68	C*79.6 A80.8 I
5576	C ₂ H ₅ -CHMe-C ₅ H ₁₀ -O-	-C ₂ H ₅	S K33	A85.4 I
5577	C ₂ H ₅ -CHMe-C ₅ H ₁₀ -O-	-C ₃ H ₇	S K34.5	A93.4 I
5578	C ₂ H ₅ -CHMe-C ₅ H ₁₀ -O-	-C ₄ H ₉	S K29.8	C*57.1 A85 I
5579	C ₂ H ₅ -CHMe-C ₅ H ₁₀ -O-	-C ₅ H ₁₁	S K44	C*76.5 A89.5 I
5580	C ₂ H ₅ -CHMe-C ₅ H ₁₀ -O-	-C ₆ H ₁₃	S K37	C*79.3 A85.7 I
5581	C ₂ H ₅ -CHMe-C ₅ H ₁₀ -O-	-C ₇ H ₁₅	S K50.5	C*86.9 A88.8 I
5582	C ₂ H ₅ -CHMe-C ₅ H ₁₀ -O-	-C ₈ H ₁₇	S K44.5	C*81.2 A84.6 I
5583	C ₂ H ₅ -CHMe-C ₅ H ₁₀ -O-	-C ₉ H ₁₉	S K59.5	C*86 I
5584	C ₂ H ₅ -CHMe-C ₅ H ₁₀ -O-	-C ₁₀ H ₂₁	S K51.5	C*81.2 I

TABLE 66




No	L	R	Cr	LC
5654	C ₆ H ₁₁ -O-	-C ₆ H ₁₃	K65	C58.5 I
5655	C ₆ H ₁₁ -O-	-C ₇ H ₁₅	K49	C52.5 N63 I
5656	C ₆ H ₁₁ -O-	-C ₈ H ₁₇	K55	A68 I
5657	C ₆ H ₁₁ -O-	-C ₇ H ₁₅	K58	C67 A74 N76 I
5658	C ₆ H ₉ -O-	-O-C ₆ H ₉	K75.5	S57.5 N74 I
5659	C ₆ H ₉ -O-	-O-C ₆ H ₁₃	K70	S68.5 N80 I
5660	C ₆ H ₁₁ -O-	-O-C ₆ H ₉	K53.5	S61 N71 I
5661	C ₆ H ₁₁ -O-	-O-C ₆ H ₁₃	K55.5	S70 S72.5 N82 I
5676	C ₇ H ₁₅ -COO-	-C ₆ H ₁₃	K56	C50.5 A65 I




No	L	R	Cr	LC
7081	O ₂ N-	-OOC-C ₁₆ H ₂₆ -Si(O ₂ Me) ₂ -cy	K?	A50 I
7083	F-	-C ₂ H ₅	K<20	N-36.2 I
7084	F-	-C ₃ H ₇	K<20	N-14.6 I
7089	NC-	-C ₆ H ₁₃	K29.7	N14.5 I
7097	C ₆ H ₉ -	-C ₆ H ₁₃	K20	B44 I
7098	C ₆ H ₉ -O-	-C ₆ H ₁₃	K40	B78 I
7099	CH ₃ -OOC-	-C ₅ H ₁₁	K86.5	A90.5 I
7100	C ₅ H ₇ -OOC-	-C ₅ H ₁₁	K37.8	A68 I
7101	C ₆ H ₉ -OOC-	-C ₅ H ₁₁	K42	A57.8 I
7102	C ₅ H ₁₁ -OOC-	-C ₅ H ₁₁	K45.5	A59 I

TABLE 67




No	L	R	Cr	LC
7260	C ₆ H ₁₁ -	-O-C ₆ H ₁₁ -	K72	A114
7261	C ₆ H ₅ -O-	-C ₆ H ₅	K79	C96 N108
7262	C ₆ H ₁₁ -O-	-C ₆ H ₅	K86	C101 N106.5
7264	C ₆ H ₅ -O-	-O-C ₆ H ₅	K104	C112 N142 N150
7265	C ₆ H ₅ -O-	-O-C ₆ H ₁₁ -	K92	C95 A140 N142.5
7266	C ₆ H ₁₁ -O-	-O-CH ₃	K99	A116 N127
7267	C ₆ H ₁₁ -O-	-O-C ₆ H ₁₁ -	K74.5	C135.5 A144
7268	C ₆ H ₅ -S-	-O-C ₆ H ₁₁ -	K71.8	A119

TABLE 68




No	L	R	Cr	LC
7276	C ₂ H ₅ -O-	-CN	K150	S144 N189 I
7277	C ₆ H ₁₃ -	-C ₆ H ₁₃	K68	C106 N116 I
7281	C ₅ H ₁₁ -	-O-C ₄ H ₉	K77	S76 N118 I
7285	C ₅ H ₁₁ -O-	-C ₅ H ₁₁	K73	C77 N118 I
7286	C ₅ H ₁₁ -O-	-C ₆ H ₁₃	K73	C88 N114 I
7287	C ₅ H ₁₁ -O-	-C ₇ H ₁₅	K71	C96 A98 N118 I
7288	C ₅ H ₁₁ -O-	-C ₈ H ₁₇	K73	C92 A105 N112 I
7289	C ₆ H ₁₃ -O-	-C ₅ H ₁₁	K68	C93 N125 I
7290	C ₆ H ₁₃ -O-	-C ₆ H ₁₃	K66	C98 N117 I
7291	C ₆ H ₁₃ -O-	-C ₇ H ₁₅	K65	C104 A106 N121 I
7292	C ₆ H ₁₃ -O-	-C ₈ H ₁₇	K69	C104 A113 N117 I
7293	C ₇ H ₁₅ -O-	-C ₅ H ₁₁	K73	C98 N121 I
7294	C ₇ H ₁₅ -O-	-C ₆ H ₁₃	K70	C105 N116 I
7295	C ₇ H ₁₅ -O-	-C ₇ H ₁₅	K70	C109 A113 N120 I
7296	C ₇ H ₁₅ -O-	-C ₈ H ₁₇	K71	C109 A115 N116 I
7297	C ₈ H ₁₇ -O-	-C ₅ H ₁₁	K72	C104 N120 I
7298	C ₈ H ₁₇ -O-	-C ₆ H ₁₃	K68	C106 N116 I
7299	C ₈ H ₁₇ -O-	-C ₇ H ₁₅	K70	C109 A117 N120 I




No	L	R	Cr	LC
7260	C ₅ H ₁₁ -	-O-C ₈ H ₁₇	K72	A114 I
7261	C ₄ H ₉ -O-	-C ₄ H ₉	K79	C96 N108 I
7262	C ₅ H ₁₁ -O-	-C ₄ H ₉	K86	C101 N106.5 I
7264	C ₄ H ₉ -O-	-O-C ₄ H ₉	K104	C112 A142 N150 I
7265	C ₄ H ₉ -O-	-O-C ₅ H ₁₁	K92	C95 A140 N142.5 I
7266	C ₉ H ₁₉ -O-	-O-CH ₃	K99	A116 N127 I
7267	C ₉ H ₁₉ -O-	-O-C ₈ H ₁₇	K74.5	C135.5 A144 I
7268	C ₄ H ₉ -S-	-O-C ₈ H ₁₇	K71.8	A119 I

TABLE 69




No	L	R	Cr	LC
7300	C ₆ H ₁₇ -O-	-C ₆ H ₁₇	K69	C113 A118 I
7301	C ₉ H ₁₉ -O-	-C ₅ H ₁₁	K76	C107 A109 N118 I
7302	C ₉ H ₁₉ -O-	-C ₆ H ₁₃	K76	C111 A113 N116 I
7303	C ₉ H ₁₉ -O-	-C ₇ H ₁₅	K76	C113 A119 I
7304	C ₉ H ₁₉ -O-	-C ₈ H ₁₇	K75	C114 A117 I
7305	C ₁₀ H ₂₁ -O-	-C ₅ H ₁₁	K77	C107 A113 N118 I
7306	C ₁₀ H ₂₁ -O-	-C ₆ H ₁₃	K75	C110 A114 N116 I
7307	C ₁₀ H ₂₁ -O-	-C ₇ H ₁₅	K74	C114 A119 I
7308	C ₁₀ H ₂₁ -O-	-C ₈ H ₁₇	K68	C114 A116 I
7309	C ₁₁ H ₂₃ -O-	-C ₅ H ₁₁	K83	C105 A114 N116 I
7310	C ₁₁ H ₂₃ -O-	-C ₆ H ₁₃	K82	C110 A115 I
7311	C ₁₁ H ₂₃ -O-	-C ₇ H ₁₅	K81	C113 A118 I
7312	C ₁₁ H ₂₃ -O-	-C ₈ H ₁₇	K80	C115 A117 I
7313	C ₁₂ H ₂₅ -O-	-C ₅ H ₁₁	K83	C104 A114 N116 I
7314	C ₁₂ H ₂₅ -O-	-C ₆ H ₁₃	K103	C108 A113 I
7315	C ₁₂ H ₂₅ -O-	-C ₇ H ₁₅	K79	C112 A118 I
7316	C ₁₂ H ₂₅ -O-	-C ₈ H ₁₇	K79	C113 A115 I
7317	C ₅ H ₁₁ -CFMe-COO-	-C ₈ H ₁₇	1 K65.3	S63.5 I

TABLE 70




No	L	R	Cr	LC
27333	CH ₃ -	-H	K153	A151.5 N163.5 I
27334	C ₂ H ₅ -	-H	K142	A164 I
27335	C ₃ H ₇ -	-H	K125	A175.5 I
27336	C ₄ H ₉ -	-H	K120.5	A170 I
27337	C ₅ H ₁₁ -	-H	K113	A175 I
27338	C ₆ H ₁₃ -	-H	K99.5	A176 I
27339	C ₇ H ₁₅ -	-H	K86	E88 A170 I
27340	C ₈ H ₁₇ -	-H	K60	E82 A176 I
27341	C ₉ H ₁₉ -	-H	K61	S82 A173 I
27342	C ₁₀ H ₂₁ -	-H	K53	E83 A171 I
27343	CH ₃ -O-	-H	K169	A163 N203 I
27344	C ₂ H ₅ -O-	-H	K175	A202 N216 I
27345	C ₃ H ₇ -O-	-H	K157	A204 I
27346	C ₄ H ₉ -O-	-H	K145	E130 A206 I
27347	C ₆ H ₁₇ -O-	-H	K96	E115 A195 I
27348	C ₁₀ H ₂₁ -O-	-H	K98	E120 A194 I
27349	C ₁₆ H ₃₃ -O-	-H	K109	E106 A182.5 I
27351	C ₅ H ₁₁ -Oxazolidinyl-N-oxy-C ₄ H ₉ -O-	-H 2	K118	C101 A108 I
27352	C ₈ H ₁₇ -Oxazolidinyl-N-oxy-C ₇ H ₁₅ -O-	-H 2	K79	E99 C119 A134 I
27353	CH ₃ -Oxazolidinyl-N-oxy-C ₈ H ₁₇ -O-	-H 2	K113	C123 A158.5 I




No	L	R	Cr	LC
8797	C ₆ H ₁₃ -	-C ₆ H ₁₃	K170	S172 A236 I


TABLE 71



No	L	R	Cr	LC
8797	C ₆ H ₁₃ -	-C ₆ H ₁₃	K170	S172 A236 I



No	L	R	Cr	LC
28635	C ₅ H ₁₁ -	-C ₆ H ₁₃	K67	S125 A204 N214 I




No	L	R	Cr	LC
7557	C ₆ H ₁₇ -O-	-F	K71.5	A128.5 I
7558	C ₆ H ₁₇ -O-	-Cl	K72	E94.5 A164 I
7559	C ₆ H ₁₇ -O-	-Br	K75.5	E107.5 A149.5 I
7561	C ₆ H ₁₃ -	-C ₆ H ₁₃	K54	A45 N56 I
7562	C ₆ H ₁₇ -	-C ₆ H ₁₃	K62	A69 I
7563	C ₆ H ₁₇ -O-	-C ₆ H ₁₃	K55	C106 I
7570	C ₆ H ₁₇ -O-	-O-C ₄ H ₉	K70.8	S99.8 N123.1 I
7572	C ₁₂ H ₂₅ -O-	-O-CH ₃	K90.7	S96.9 N113.4 I

55 **Example A1**

44.6 g (0.34 mol) of 4-cyanobenzaldehyde and 54.4 g (0.64 mol) of o-aminobenzenethiol were dissolved in 300 ml of dimethyl sulfoxide, and the temperature of the solution was raised to 140°C. The produced water and the dimethyl sulfoxide were distilled off. After heating for one hr, the residue was cooled, water was added thereto, and the resultant


precipitate was collected by filtration and washed with ethanol. The crude crystal thus obtained was recrystallized from ethyl acetate to give 2-(4'-cyanophenyl)benzothiazole. 22.4 g (0.095 mol) of the compound was dissolved in 250 ml of acetic acid, and 18.6 g (0.116 mol) of bromine was dropwise added thereto. As soon as bromine was added, a yellow bromine adduct was produced. Subsequently, 150 ml of water was added, and the mixture was stirred at 80°C for 2 hr. It was then cooled, and the resultant precipitate was collected by filtration and washed with ethanol. The crude product thus obtained was recrystallized from ethyl acetate.

A 60 % by weight dispersion of 0.8 g (0.02 mol) of sodium hydride in an oil was suspended in 50 ml of ether, 3.22 g (0.022 mol) of 1-octanethiol was dropwise added thereto, and the mixture was refluxed for 30 min. Thereafter, the ether was distilled off, 50 ml of N,N-dimethylimidazolidinone was added to the residue, and the temperature of the system was raised to 60°C. 0.01 mol of 2-(4'-cyanophenyl)-6-bromobenzothiazole was added to the solution, and stirring was continued for one hr. The solution was cooled, water was added thereto, and the resultant precipitate was collected by filtration and washed with ethanol. The product thus obtained was recrystallized from a hexane/ethyl acetate mixed solution to give a compound represented by the following formula:




Example A2

1.31 g (0.01 mol) of 4-cyanobenzaldehyde, 2.5 g (0.01 mol) of 2-amino-6-hexyloxybenzothiazole, and 30 ml of ethanol were heated at 70°C for 2 hr. The reaction mixture was then cooled to room temperature, and the resultant solid matter was collected by filtration and recrystallized from ethanol to give a compound represented by the following formula:



Example A3

2.21 g (0.01 mol) of 2,5-diamino-1,4-benzenedithiol/dihydrochloric acid adduct, 5.34 g (0.024 mol) of 4-hexyloxybenzoic acid, 3 g of phosphorus pentaoxide, and 50 ml of methanesulfonic acid were allowed to react at 90°C for one hr and then heated at 80°C for 5 hr. The resultant product was collected by filtration and recrystallized from N-methylpyrrolidone to give a compound represented by the following formula:




Example A4

2.56 g (0.01 mol) of 2,6-dimercaptobenzo(1,2-d:5,6-d')bisthiazole, 4.54 g (0.02 mol) of 4-hexyloxybenzyl chloride, 1.2 g of potassium carbonate, and 15 ml of N-methylpyrrolidone were heated at 80°C for 3 hr. The reaction mixture was

EP 0 763 532 A2

poured into water, and the resultant solid matter was collected by filtration and washed with water, methanol, and chloroform. It was then recrystallized from benzene to give a compound represented by the following formula:



wherein $R = \text{CH}_3(\text{CH}_2)_5\text{O}$.

Example A5

The procedure of Example A1 was repeated to prepare liquid crystalline compounds represented by the general formula (A) wherein R_1 and R_2 represent the following groups. The liquid crystalline compounds thus obtained had the same properties as the liquid crystalline compound prepared in Example A1.

Example	R_1	R_2
A5-1	$\text{CH}_3(\text{CH}_2)_9\text{O}$	CN
A5-2	$\text{CH}_3\text{CH}_2\text{C}^*\text{H}(\text{CH}_3)\text{CH}_2\text{O}$	CN
A5-3	$\text{CH}_3(\text{CH}_2)_5\text{O}$	$\text{O}(\text{CH}_2)_9\text{CH}_3$
A5-4	NO_2	$\text{S}(\text{CH}_2)_7\text{CH}_3$
A5-5	NO_2	$\text{O}(\text{CH}_2)_7\text{CH}_3$
A5-6	F	$\text{O}(\text{CH}_2)_9\text{CH}_3$

Example A6

The procedure of Example A2 was repeated to prepare liquid crystalline compounds represented by the general formula (B) wherein R_1 and R_2 represent the following groups. The liquid crystalline compounds thus obtained had the same properties as the liquid crystalline compound prepared in Example A2.

Example	R_1	R_2	Z
A6-1	NO_2	$\text{O}(\text{CH}_2)_9\text{CH}_3$	$\text{CH}=\text{N}$
A6-2	$\text{CH}_3(\text{CH}_2)_5\text{O}$	$\text{O}(\text{CH}_2)_5\text{CH}_3$	COO
A6-3	$\text{CH}_3\text{CH}_2\text{C}^*\text{H}(\text{CH}_3)\text{CH}_2\text{O}$	$\text{O}(\text{CH}_2)_7\text{CH}_3$	$\text{CH}=\text{CH}$
A6-4	CN	$\text{O}(\text{CH}_2)_8\text{CH}_3$	$\text{CH}=\text{CH}$
A6-5	$\text{CH}_3(\text{CH}_2)_9\text{O}$	$\text{O}(\text{CH}_2)_3\text{CH}_3$	$\text{C}=\text{C}$
A6-6	$\text{CH}_3(\text{CH}_2)_5\text{O}$	$\text{O}(\text{CH}_2)_5\text{CH}_3$	$\text{N}=\text{N}$

Example A7

The procedure of Example A3 was repeated to prepare liquid crystalline compounds represented by the general formula (C) wherein R_1 represents the following groups. The liquid crystalline compounds thus obtained had the same properties as the liquid crystalline compound prepared in Example A3.

Example	R ₁
A7-1	CH ₃ (CH ₂) ₉ O
A7-2	CH ₃ (CH ₂) ₉
A7-3	CH ₃ (CH ₂) ₉ S
A7-4	CH ₃ (CH ₂) ₅ S
A7-5	CH ₃ (CH ₂) ₈ S
A7-6	CH ₃ CH ₂ C*H(CH ₃)CH ₂ O

Example A8

The procedure of Example A3 was repeated to prepare liquid crystalline compounds represented by the general formula (D) wherein R₁ represents the following group. The liquid crystalline compounds thus obtained had the same properties as the liquid crystalline compound prepared in Example A4.

Example	R ₁	Z
A8-1	CH ₃ (CH ₂) ₅ O	COO
A8-2	CH ₃ (CH ₂) ₅ O	CH=N
A8-3	CH ₃ CH ₂ C*H(CH ₃)CH ₂ O	CH=CH
A8-4	CH ₃ (CH ₂) ₅ S	CH=N
A8-5	CH ₃ (CH ₂) ₃ O	N=N
A8-6	CH ₃ (CH ₂) ₉ O	COO

According to the present invention, novel liquid crystalline compounds are provided which exhibit liquid crystallinity and, in addition, photoconductivity and fluorescence. The novel liquid crystalline compounds are useful as materials for liquid crystal displays, photosensitive materials for electrophotography and the like.

Example B

[Synthesis of 2-(4'-heptyloxyphenyl)benzothiazole]

74.2 g (0.34 mol) of 4-heptyloxybenzaldehyde and 54.4 g (0.46 mol) of o-aminobenzenethiol were dissolved in 300 ml of dimethyl sulfoxide, and the temperature of the solution was raised to 140°C. The produced water and the dimethyl sulfoxide were distilled off. After heating for one hr, the residue was cooled, water was added thereto, and the resultant precipitate was collected by filtration and washed with ethanol. The crude crystal thus obtained was recrystallized from ethyl acetate. The yield was 90%.

The above compound exhibited the following peaks in NMR spectrum:

¹H-NMR (CDCl₃)

δ = 0.90 (3H, t, J = 6.6 Hz), 1.25-1.47 (8H, m), 1.81 (2H, quint, J = 6.6 Hz), 4.01 (2H, t, J = 6.5 Hz), 6.97 (2H, d, J = 8.5 Hz), 7.33 (1H, d, J = 8.9 Hz), 7.45 (1H, t, J = 8.5 Hz), 7.86 (1H, d, J = 7.9 Hz), 8.01 (1H, d, J = 8.9 Hz), 8.02 (2H, d, J = 8.5 Hz)

Further, it exhibited the following peaks in IR (KBr disc) spectrum:

506, 568, 622, 648, 698, 730, 968, 1010, 1037, 1300, 1316, 1394, 1417, 1441, 1470, 1483, 1520, 1603, 2852, 2912 cm⁻¹

[Synthesis of 2-(4'-heptyloxyphenyl)-6-bromobenzothiazole]

31.0 g (0.095 mol) of 2-(4'-heptyloxyphenyl)benzothiazole was dissolved in 250 ml of acetic acid, and 18.6 g (0.116 mol) of bromine was dropwise added thereto. As soon as bromine was added, a yellow bromine adduct was produced. Subsequently, 150 ml of water was added, and the mixture was stirred at 80°C for 2 hr. It was then cooled, and the resultant precipitate was collected by filtration and washed with ethanol. The crude product thus obtained was recrystallised from ethyl acetate. The yield was 68%.

The above compound exhibited the following peaks in NMR spectrum:

^1H NMR (CDCl_3) δ = 0.90 (3H, t, J = 6.6 Hz), 1.33-1.50 (8H, m), 1.81 (2H, quint, J = 6.6 Hz), 4.03 (2H, t, J = 6.6 Hz), 6.98 (2H, d, J = 8.6 Hz), 7.55 (1H, dd, J_1 = 2.0 and J_2 = 8.6 Hz), 7.85 (1H, d, J = 8.6 Hz), 7.98 (1H, d, J = 2.0 Hz), 7.99 (2H, d, J = 8.6 Hz)

Further, it exhibited the following peaks in IR (KBr disc) spectrum:

520, 563, 622, 666, 695, 723, 748, 859, 1015, 1040, 1090, 1115, 1224, 1393, 1438, 1474, 1488, 1520, 1541, 2855, 2922, 2937 cm^{-1}

[General process for synthesizing 2-(4'-alkoxyphenyl)-6-alkylthiobenzothiazole derivatives]

A 60 % by weight dispersion of 0.8 g (0.02 mol) of sodium hydride in an oil was suspended in 50 ml of ether, 0.022 mol of a corresponding alkanethiol was dropwise added thereto, and the mixture was refluxed for 30 min. Thereafter, the ether was distilled off, 50 ml of N,N' -dimethylimidazolidinone was added to the residue, and the temperature of the system was raised to 60°C. 0.01 mol of 2-(4'-heptyloxyphenyl)-6-bromobenzothiazole was added to the solution, and stirring was continued for one hr. The solution was cooled, water was added thereto, and the resultant precipitate was collected by filtration and washed with ethanol. The crude product thus obtained was recrystallized from hexane.

2-(4'-alkoxyphenyl)-6-alkylthiobenzothiazole, having the same R (heptyl group) and different R', had the following properties.

[2-(4'-heptyloxyphenyl)-6-hexylthiobenzothiazole] (yield 65%):

^1H NMR (CDCl_3) δ = 0.89 (3H, t, J = 6.6 Hz), 0.90 (3H, t, J = 6.6 Hz), 1.27-1.47 (14H, m), 1.67 (2H, quint, J = 7.2 Hz), 1.82 (2H, quint, J = 6.6 Hz), 2.98 (2H, t, J = 7.2 Hz), 4.02 (2H, t, J = 6.6 Hz), 6.98 (2H, d, J = 8.6 Hz), 7.43 (1H, dd, J_1 = 1.7 and J_2 = 8.3 Hz), 7.82 (1H, d, J = 1.7 Hz), 7.91 (1H, d, J = 8.3 Hz), 7.99 (2H, d, J = 8.6 Hz)

IR (KBr disc)

520, 570, 621, 701, 727, 966, 1010, 1040, 1112, 1276, 1306, 1396, 1418, 1441, 1474, 1485, 1520, 1543, 1575, 1606, 2855, 2956 cm^{-1}

Heating: Cryst (80.5°C) - SmA (103.7°C) - iso (2°C/min)

Cooling: Iso (103.2°C) - SmA (83.9°C) - Cryst (5°C/min)

[2-(4'-heptyloxyphenyl)-6-octylthiobenzothiazole] (yield 54%):

^1H NMR (CDCl_3) δ = 0.87 (3H, t, J = 6.9 Hz), 0.90 (3H, t, J = 6.6 Hz), 1.18-1.47 (18H, m), 1.67 (2H, quint, J = 7.3 Hz), 1.81 (2H, quint, J = 6.6 Hz), 2.97 (2H, t, J = 7.3 Hz), 4.02 (2H, t, J = 6.6 Hz), 6.98 (2H, d, J = 8.9 Hz), 7.42 (1H, dd, J_1 = 1.6 and J_2 = 8.6 Hz), 7.81 (1H, d, J = 1.6 Hz), 7.90 (1H, d, J = 8.6 Hz), 7.98 (2H, d, J = 8.9 Hz)

IR (KBr disc)

520, 570, 621, 702, 727, 774, 843, 967, 1017, 1041, 1112, 1176, 1276, 1306, 1396, 1441, 1474, 1486, 1520, 1543, 1575, 1607, 2855, 2956 cm^{-1}

Heating: Cryst (94.0°C) - SmA (102.0°C) - iso (2°C/min)

Cooling: Iso (100.3°C) - SmA (89.8°C) - Sm? (78.2°C) - Cryst (5°C/min)

[2-(4'-heptyloxyphenyl)-6-decylthiobenzothiazole] (yield 63%):

^1H NMR (CDCl_3) δ = 0.87 (3H, t, J = 6.9 Hz), 0.90 (3H, t, J = 6.6 Hz), 1.25-1.47 (22H, m), 1.66 (2H, quint, J = 7.3 Hz), 1.81 (2H, quint, J = 6.6 Hz), 2.96 (2H, t, J = 7.3 Hz), 4.02 (2H, t, J = 6.6 Hz), 6.97 (2H, d, J = 8.9 Hz), 7.43 (1H, dd, J_1 = 2.0 and J_2 = 8.6 Hz), 7.81 (1H, d, J = 2.2 Hz), 7.89 (1H, d, J = 8.6 Hz), 7.98 (2H, d, J = 8.9 Hz)

IR (KBr disc)

570, 812, 842, 967, 1018, 1041, 1112, 1177, 1306, 1393, 1441, 1474, 1485, 1519, 1575, 1607, 2853, 2957 cm^{-1}

Heating: Cryst (95.5°C) - SmA (100.9°C) - iso (2°C/min)

Cooling: Iso (100.6°C) - SmA (93.1°C) - Cryst (5°C/min)

[2-(4'-heptyloxyphenyl)-6-dodecylthiobenzothiazole] (yield 67%):

¹H NMR (CDCl₃) δ = 0.87 (3H, t, J = 7.0 Hz), 0.90 (3H, t, J = 6.6 Hz), 1.28-1.46 (26H, m), 1.62 (2H, quint, J = 7.6 Hz), 1.78 (2H, quint, J = 7.6 Hz), 2.97 (2H, t, J = 7.6 Hz), 4.02 (2H, t, J = 6.6 Hz), 6.97 (2H, d, J = 8.6 Hz), 7.42 (1H, dd, J₁ = 2.0 and J₂ = 8.6 Hz), 7.81 (1H, d, J = 2.0 Hz), 7.90 (1H, d, J = 8.6 Hz), 7.98 (2H, d, J = 8.6 Hz)

IR (KBr disc)

571, 812, 841, 967, 1018, 1111, 1178, 1306, 1395, 1474, 1486, 1519, 1607, 2852, 2920, 2956 cm⁻¹

Heating: Cryst (90.0°C) - SmA (98.0°C) - iso (2°C/min)

Cooling: Iso (96.1°C) - SmA (85.7°C) - Cryst (5°C/min)

UV - VIS λ_{max} = 327 nm (10⁻⁶M in CC1₃)

PL (He - Cd Laser 324 nm) λ_{max} = 420, 438 nm

Example C

Synthesis Example 1 of Intermediate

[Synthesis of 2-(4'-heptyloxyphenyl)benzothiazole]

74.2 g (0.34 mol) of 4-heptyloxybenzaldehyde and 54.4 g (0.46 mol) of o-aminobenzenethiol were dissolved in 300 ml of dimethyl sulfoxide, and the temperature of the solution was raised to 140°C. The produced water and the dimethyl sulfoxide were distilled off. After heating for one hr, the residue was cooled, water was added thereto, and the resultant precipitate was collected by filtration and washed with ethanol. The crude crystal thus obtained was recrystallized from ethyl acetate. The yield was 90%.

The above compound exhibited the following peaks in NMR spectrum:

¹H NMR (CDCl₃)

δ = 0.90 (3H, t, J = 6.6 Hz), 1.25-1.47 (8H, m), 1.81 (2H, quint, J = 6.6 Hz), 4.01 (2H, t, J = 6.5 Hz), 6.97 (2H, d, J = 8.5 Hz), 7.33 (1H, d, J = 8.9 Hz), 7.45 (1H, t, J = 8.5 Hz), 7.86 (1H, d, J = 7.9 Hz), 8.01 (1H, d, J = 8.9 Hz), 8.02 (2H, d, J = 8.5 Hz)

Further, it exhibited the following peaks in IR (KBr disc) spectrum:

506, 568, 622, 648, 698, 730, 968, 1010, 1037, 1300, 1316, 1394, 1417, 1441, 1470, 1483, 1520, 1603, 2852, 2912 cm⁻¹

Synthesis Example 2 of Intermediate

[Synthesis of 2-(4'-heptyloxyphenyl)-6-bromobenzothiazole]

31.0 g (0.095 mol) of 2-(4'-heptyloxyphenyl)benzothiazole was dissolved in 250 ml of acetic acid, and 18.6 g (0.116 mol) of bromine was dropwise added thereto. As soon as bromine was added, a yellow bromine adduct was produced. Subsequently, 150 ml of water was added, and the mixture was stirred at 80°C for 2 hr. It was then cooled, and the resultant precipitate was collected by filtration and washed with ethanol. The crude product thus obtained was recrystallized from ethyl acetate. The yield was 68%.

The above compound exhibited the following peaks in NMR spectrum:

¹H NMR (CDCl₃) δ = 0.90 (3H, t, J = 6.6 Hz), 1.33-1.50 (8H, m), 1.81 (2H, quint, J = 6.6 Hz), 4.03 (2H, t, J = 6.6 Hz), 6.98 (2H, d, J = 8.6 Hz), 7.55 (1H, dd, J₁ = 2.0 and J₂ = 8.6 Hz), 7.85 (1H, d, J = 8.6 Hz), 7.98 (1H, d, J = 2.0 Hz), 7.99 (2H, d, J = 8.6 Hz)

Further, it exhibited the following peaks in IR (KBr disc) spectrum:

520, 563, 622, 666, 695, 723, 748, 859, 1015, 1040, 1090, 1115, 1224, 1393, 1438, 1474, 1488, 1520, 1541, 2855, 2922, 2937 cm⁻¹

Examples C1 to C4

[General process for synthesizing 2-(4'-alkoxyphenyl)-6-alkylthiobenzothiazole derivatives]

A 60 % by weight dispersion of 0.8 g (0.02 mol) of sodium hydride in an oil was suspended in 50 ml of ether, 0.022 mol of a corresponding alkanethiol was dropwise added thereto, and the mixture was refluxed for 30 min. Thereafter, the ether was distilled off, 50 ml of N,N'-dimethylimidazolidinone was added to the residue, and the temperature of the system was raised to 60°C. 0.01 mol of 2-(4'-heptyloxyphenyl)-6-bromobenzothiazole was added to the solution, and stirring was continued for one hr. The solution was cooled, water was added thereto, and the resultant precipitate was collected by filtration and washed with ethanol. The crude product thus obtained was recrystallized from hexane.

EP 0 763 532 A2

2-(4'-alkoxyphenyl)-6-alkylthiobenzothiazole, having the same R (heptyl group) and different R', had the following properties.

Example C1

[2-(4'-heptyloxyphenyl)-6-hexylthiobenzothiazole] (yield 65%):

^1H NMR (CDCl_3) δ = 0.89 (3H, t, J = 6.6 Hz), 0.90 (3H, t, J = 6.6 Hz), 1.27-1.47 (14H, m), 1.67 (2H, quint, J = 7.2 Hz), 1.82 (2H, quint, J = 6.6 Hz), 2.98 (2H, t, J = 7.2 Hz), 4.02 (2H, t, J = 6.6 Hz), 6.98 (2H, d, J = 8.6 Hz), 7.43 (1H, dd, J1 = 1.7 and J2 = 8.3 Hz), 7.82 (1H, d, J = 1.7 Hz), 7.91 (1H, d, J = 8.3 Hz), 7.99 (2H, d, J = 8.6 Hz)

IR (KBr disc)

520, 570, 621, 701, 727, 966, 1010, 1040, 1112, 1276, 1306, 1396, 1418, 1441, 1474, 1485, 1520, 1543, 1575, 1606, 2855, 2956 cm^{-1}

Heating: Cryst (80.5°C) - SmA (103.7°C) - iso (2°C/min)

Cooling: Iso (103.2°C) - SmA (83.9°C) - Cryst (5°C/min)

Example C2

[2-(4'-heptyloxyphenyl)-6-octylthiobenzothiazole] (yield 54%):

^1H NMR (CDCl_3) δ = 0.87 (3H, t, J = 6.9 Hz), 0.90 (3H, t, J = 6.6 Hz), 1.18-1.47 (18H, m), 1.67 (2H, quint, J = 7.3 Hz), 1.81 (2H, quint, J = 6.6 Hz), 2.97 (2H, t, J = 7.3 Hz), 4.02 (2H, t, J = 6.6 Hz), 6.98 (2H, d, J = 8.9 Hz), 7.42 (1H, dd, J1 = 1.6 and J2 = 8.6 Hz), 7.81 (1H, d, J = 1.6 Hz), 7.90 (1H, d, J = 8.6 Hz), 7.98 (2H, d, J = 8.9 Hz)

IR (KBr disc)

520, 570, 621, 702, 727, 774, 843, 967, 1017, 1041, 1112, 1176, 1276, 1306, 1396, 1441, 1474, 1486, 1520, 1543, 1575, 1607, 2855, 2956 cm^{-1}

Heating: Cryst (94.0°C) - SmA (102.0°C) - iso (2°C/min)

Cooling: Iso (100.3°C) - SmA (89.8°C) - Sm? (78.2°C) - Cryst (5°C/min)

Example C3

[2-(4'-heptyloxyphenyl)-6-decylthiobenzothiazole] (yield 63%):

^1H NMR (CDCl_3) δ = 0.87 (3H, t, J = 6.9 Hz), 0.90 (3H, t, J = 6.6 Hz), 1.25-1.47 (22H, m), 1.66 (2H, quint, J = 7.3 Hz), 1.81 (2H, quint, J = 6.6 Hz), 2.96 (2H, t, J = 7.3 Hz), 4.02 (2H, t, J = 6.6 Hz), 6.97 (2H, d, J = 8.9 Hz), 7.43 (1H, dd, J1 = 2.0 and J2 = 8.6 Hz), 7.81 (1H, d, J = 2.2 Hz), 7.89 (1H, d, J = 8.6 Hz), 7.98 (2H, d, J = 8.9 Hz)

IR (KBr disc)

570, 812, 842, 967, 1018, 1041, 1112, 1177, 1306, 1393, 1441, 1474, 1485, 1519, 1575, 1607, 2853, 2957 cm^{-1}

Heating: Cryst (95.5°C) - SmA (100.9°C) - iso (2°C/min)

Cooling: Iso (100.6°C) - SmA (93.1°C) - Cryst (5°C/min)

Example C4

[2-(4'-heptyloxyphenyl)-6-dodecylthiobenzothiazole] (yield 67%):

^1H NMR (CDCl_3) δ = 0.87 (3H, t, J = 7.0 Hz), 0.90 (3H, t, J = 6.6 Hz), 1.28-1.46 (26H, m), 1.62 (2H, quint, J = 7.6 Hz), 1.78 (2H, quint, J = 7.6 Hz), 2.97 (2H, t, J = 7.6 Hz), 4.02 (2H, t, J = 6.6 Hz), 6.97 (2H, d, J = 8.6 Hz), 7.42 (1H, dd, J1 = 2.0 and J2 = 8.6 Hz), 7.81 (1H, d, J = 2.0 Hz), 7.90 (1H, d, J = 8.6 Hz), 7.98 (2H, d, J = 8.6 Hz)

IR (KBr disc)

571, 812, 841, 967, 1018, 1111, 1178, 1306, 1395, 1474, 1486, 1519, 1607, 2852, 2920, 2956 cm^{-1}

Heating: Cryst (90.0°C) - SmA (98.0°C) - iso (2°C/min)

Cooling: Iso (96.1°C) - SmA (85.7°C) - Cryst (5°C/min)

UV - VIS λ_{max} = 327 nm (10^{-6}M in CCl_4)

PL (He - Cd Laser 324 nm) λ_{max} = 420; 438 nm

Examples C5 to C10

Liquid crystalline compounds represented by the above general formula wherein R and R' represent the following groups were prepared in the same manner as in the above examples and comparative examples. All the liquid crystal-




line compounds thus obtained had the same properties as those prepared in Examples C1 to C4.

Example	R	R'
Example C5	Hexyl group	Heptyl group
Example C6	Octyl group	Nonyl group
Example C7	Hexyl group	Undecynyl group
Example C8	Decyl group	Tetradecyl group
Example C9	Amyl group	Tridecyl group
Example C10	Dodecyl group	Heptyl group

According to the present invention, novel liquid crystalline compounds which exhibit liquid crystallinity and, in addition, photoconductivity and fluorescence. The novel liquid crystalline compounds are useful as materials for liquid crystal displays, photosensitive materials for electrophotography and the like.

Claims



1. A process for producing a liquid crystalline compound represented by the general formula (A), comprising the steps of: reacting a compound represented by the general formula (1) with a compound represented by the general formula (2); brominating the reaction product to give a compound represented by the general formula (3); and substituting the bromine atom of the compound (3) with an R_2 group to obtain the liquid crystalline compound (A):



wherein R_1 and R_2 represent (a) a cyano group, (b) a nitro group, (c) a fluorine atom, or (d) a $C_1 - C_{22}$ straight-chain or branched, saturated or unsaturated, alkyl or alkoxy group attached to the aromatic ring through an oxygen atom, or a sulfur atom, provided that at least one of R_1 and R_2 represents said alkyl or alkoxy group.




2. A process for producing a liquid crystalline compound represented by the general formula (B), comprising the step of: reacting a compound represented by the general formula (4) with a compound represented by the general for-

mula (5) to obtain the liquid crystalline compound (B):





20 wherein R₁ and R₂ represent (a) a cyano group, (b) a nitro group, (c) a fluorine atom, or (d) a C₁ - C₂₂ straight-chain or branched saturated or unsaturated, alkyl or alkoxy group attached to the aromatic ring through an oxygen atom, or a sulfur atom, provided that at least one of R₁ and R₂ represents said alkyl or alkoxy group; and X and Y are respectively groups which are reacted with each other to form Z selected from a -COO-, -OCO-, -N=N-, -CH=N-, -N=N-, -CH₂S-, -CH=CH-, or -C=C- group.

- 25 3. A process for producing a liquid crystalline compound represented by the general formula (C), comprising the step of: reacting 2 moles of a compound represented by the general formula (6) with one mole of a compound represented by the general formula (7) to obtain the liquid crystalline compound (C):




45 wherein R₁ is a C₁ - C₂₂ straight-chain or branched saturated or unsaturated alkyl or alkoxy group attached to the aromatic ring through an oxygen or sulfur.

- 50 4. A process for producing a liquid crystalline compound represented by the general formula (D), comprising the step of: reacting two moles of a compound represented by the general formula (8) with one mole of a compound represented by the general formula (9) to obtain the liquid crystalline compound (D):




20 wherein R_1 is a $C_1 - C_{22}$ straight-chain or branched saturated or unsaturated alkyl or alkoxy group attached to the aromatic ring through an oxygen or sulfur group; and X and Y are respectively groups which are reacted with each other to form Z selected from a $-COO-$, $-OCO-$, $-N=N-$, $-CH=N-$, $-N=N-$, $-CH_2S-$, $-CH=CH-$, or $-C=C-$ group.

- 25 5. A process for producing a liquid crystalline compound represented by the following general formula (I), comprising the steps of: reacting a 4-alkoxybenzaldehyde with o-aminobenzenethiol to synthesize a 2-(4'-alkoxyphenyl)benzothiazole; brominating the 2-(4'-alkoxyphenyl)benzothiazole to synthesize a 2-(4'-alkoxyphenyl)-6-bromobenzothiazole; and reacting the resultant bromide with an alkanethiol to obtain the liquid crystalline compound (I):



35 wherein R represents a $C_4 - C_{20}$ alkyl group; and R' represents a $C_4 - C_{20}$ alkyl group, provided that the total number of carbon atoms contained in R and R' is 10 or more.

- 40 6. A liquid crystalline compound represented by the following general formula (II):



wherein R represents C_7H_{15} and R' represents C_6H_{13} , C_9H_{17} , $C_{10}H_{21}$ or $C_{12}H_{25}$.

- 50 7. A liquid crystalline charge transport material which exhibits smectic liquid crystallinity and has a reduction potential relative to a standard reference electrode (SCE) in the range of from -0.3 to -0.6 (V vs. SCE).
8. A liquid crystalline charge transport material which exhibits smectic liquid crystallinity and has an oxidation potential relative to a standard reference electrode (SCE) in the range of from 0.2 to 1.3 (V vs. SCE).
- 55 9. The liquid crystalline charge transport material according to claim 7 or 8 which has (aromatic ring of 6π electron system) n (wherein n is an integer of 1 to 4) cores and exhibits smectic liquid crystallinity.
10. The liquid crystalline charge transport material according to claim 9, wherein the aromatic ring of 6π electron system is linked through a carbon-carbon double bond or a carbon-carbon triple bond.

11. The liquid crystalline charge transport material according to claim 7 or 8 which has a core of an aromatic ring of 10 π electron system and exhibits smectic liquid crystallinity.
12. An image display device comprising the material according to claim 7 or 8 in a drive path.
13. An electroluminescence device comprising the material according to claim 7 or 8 in a drive path.
14. A photoconductor comprising the material according to claim 7 or 8 in a drive path.
15. A space light modulating device comprising the material according to claim 7 or 8 in a drive path.
16. A thin film transistor comprising the material according to claim 7 or 8 in a drive path.
17. A liquid crystalline charge transport material comprising a liquid crystalline compound produced by the process according to any one of claims 1 to 4.




FIG. 1




FIG. 2




FIG. 3




FIG. 4




FIG. 5




FIG. 6

(19)



Europäisches Patentamt

European Patent Office

Office européen des brevets



(11)

EP 0 763 532 A3

(12)

EUROPEAN PATENT APPLICATION

(88) Date of publication A3:
02.05.2001 Bulletin 2001/18

(43) Date of publication A2:
19.03.1997 Bulletin 1997/12

(21) Application number: 96113638.9

(22) Date of filing: 26.08.1996

(51) Int. Cl.⁷: C07D 277/66, C09K 19/34,
G02F 1/13, C09K 11/06,
G11C 13/04, C09K 19/02

(84) Designated Contracting States:
DE FR GB

(30) Priority: 25.08.1995 JP 23903795
25.08.1995 JP 23903895
25.03.1996 JP 9304496
25.03.1996 JP 9304596

(71) Applicant:
DAI NIPPON PRINTING CO., LTD.
Shinjuku-ku, Tokyo-to (JP)

(72) Inventors:
• Hanna, Junichi
Yokohama-shi, Kanagawa-ken (JP)
• Funabashi, Masahiro
Yokohama-shi, Kanagawa-ken (JP)

• Akada, Masanori,
c/o Dai Nippon Printing Co., Ltd.
Shinjuku-ku, Tokyo-to (JP)
• Ando, Masayuki,
c/o Dai Nippon Printing Co., Ltd.
Shinjuku-ku, Tokyo-to (JP)
• Kosaka, Yozo,
c/o Dai Nippon Printing Co., Ltd.
Shinjuku-ku, Tokyo-to (JP)

(74) Representative:
Müller-Boré & Partner
Patentanwälte
Grafinger Strasse 2
81671 München (DE)

(54) Liquid crystalline compound and use thereof

(57) A process for producing a liquid crystalline compound represented by the following general formula (A):





FIG. 1

EP 0 763 532 A3



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 96 11 3638

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.6)
A	EP 0 498 277 A (CANON KABUSHIKI KAISHA) 12 August 1992 (1992-08-12) * page 3 - page 7 *	1,6,17	C07D277/66 C09K19/34 G02F1/13 C09K11/06 G11C13/04 C09K19/02
A	DE 43 36 447 A (HOECHST AG) 27 April 1995 (1995-04-27) * the whole document *	2,6,17	
A	US 5 371 232 A (CHRISTOPH BOMBA ET AL.) 6 December 1994 (1994-12-06) * the whole document *	1,6	
A	US 4 861 897 A (JEFFERY B. PRESS ET AL.) 29 August 1989 (1989-08-29) * column 4 *	1,2	
A	US 4 803 241 A (MAX A. WEAVER ET AL.) 7 February 1989 (1989-02-07) * the whole document *	2,6	
A	US 4 727 154 A (THEODOR PAPENFUBS) 23 February 1988 (1988-02-23) * the whole document *	1	
A	PATENT ABSTRACTS OF JAPAN vol. 1995, no. 06, 31 July 1995 (1995-07-31) & JP 07 070096 A (DOUJIN KAGAKU KENKYUSHO:KK;), 14 March 1995 (1995-03-14) * abstract *	1,6	TECHNICAL FIELDS SEARCHED (Int.Cl.6) C07D C09K G11C
A	PATENT ABSTRACTS OF JAPAN vol. 0174, no. 92 (C-1107), 7 September 1993 (1993-09-07) & JP 05 125076 A (CANON INC;), 21 May 1993 (1993-05-21) * abstract *	1,6,17	
-/--			
The search report has been drawn up for all claims			
BEEF...		Date of completion of the search 8 March 2001	Examiner Boulon, A
<p>CAUTION: DOCUMENTS</p> <p>X: particular document cited alone Y: particular document cited with another document of the same category A: technical document O: non-written document P: intermediate document</p> <p>T: theory or principle underlying the invention E: earlier patent document, but published on, or after the filing date D: document cited in the application L: document cited for other reasons &: member of the same patent family, corresponding document</p>			

EPO FORM 1503 03 02 (P04C01)



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 96 11 3638

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.CI.6)
A	PATENT ABSTRACTS OF JAPAN vol. 0171, no. 02 (C-1031), 2 March 1993 (1993-03-02) & JP 04 290885 A (MITSUBISHI KASEI CORP.) * abstract *	3,6	<div>TECHNICAL FIELDS SEARCHED (Int.CI.6)</div>
A	PATENT ABSTRACTS OF JAPAN vol. 0141, no. 15 (C-0696), 5 March 1990 (1990-03-05) & JP 01 316386 A (AGENCY OF IND SCIENCE & TECHNOL;), 21 December 1989 (1989-12-21) * abstract *	3,6	
A	TATSUYA HATTORI ET AL.: "Novel Two- Step Synthesis of Polybenzothiazoles via Precursor Polyamides from 2,5-Bis(isopropylthio)-1,4-Phenylenediamin e and Aromatic Dicarboxylic Acid Chlorides" JOURNAL OF POLYMER SCIENCE, PART A: POLYMER CHEMISTRY, vol. 30, no. 2, February 1992 (1992-02), pages 197-202, XP002142922 * the whole document *	1-4	
A	TATSUYA HATTORI ET AL.: "Novel two step Synthesis of Poly(benzothiazoles) via New Precursor Polyamides from 2,5-Bis'(cyanoethyl)thio!-1,4-phenylenedia mine and Aromatic Dicarboxylic Acid Chlorides" MACROMOLECULES, vol. 26, no. 16, 2 August 1993 (1993-08-02), pages 4089-4093, XP000384126 * the whole document *	1-4	
The present search report has been drawn up for all claims			
Place of search		Date of completion of the search	Examiner
BERLIN		8 March 2001	Boulon, A
<div>CATEGORY OF CITED DOCUMENTS</div> <div> X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document </div>			

EPO FORM 1503 03/82 (Pp. Col1)



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 96 11 3638

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.6)
A,P	DE 44 29 597 A (BASF AG) 22 February 1996 (1996-02-22) * page 2, line 34 - line 47 *	7-9,12, 14,16	
A,P	DE 44 22 332 A (BASF AG) 4 January 1996 (1996-01-04) * page 2, line 25 - page 3, line 60; claims 1,14; examples 9,10 *	7-9,12	
A	EP 0 364 185 A (NAT RES DEV) 18 April 1990 (1990-04-18) * page 2, line 63 - line 67 * * page 3, line 37 - line 60; examples 1,2 *	7-9	
The present search report has been drawn up for all claims			TECHNICAL FIELDS SEARCHED (Int.Cl.6)
Place of search BERLIN		Date of completion of the search 8 March 2001	Examiner Boulon, A
<p>CATEGORY OF CITED DOCUMENTS</p> <p>X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document</p> <p>T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document</p>			

EPO FORM 1503 03 82 (P4/C01)



European Patent
Office

Application Number

EP 96 11 3638

CLAIMS INCURRING FEES

The present European patent application comprised at the time of filing more than ten claims.

- ☐ Only part of the claims have been paid within the prescribed time limit. The present European search report has been drawn up for the first ten claims and for those claims for which claims fees have been paid, namely claim(s):
- ☐ No claims fees have been paid within the prescribed time limit. The present European search report has been drawn up for the first ten claims.

LACK OF UNITY OF INVENTION

The Search Division considers that the present European patent application does not comply with the requirements of unity of invention and relates to several inventions or groups of inventions, namely:

see sheet B

- ☒ All further search fees have been paid within the fixed time limit. The present European search report has been drawn up for all claims.
- ☐ As all searchable claims could be searched without effort justifying an additional fee, the Search Division did not invite payment of any additional fee.
- ☐ Only part of the further search fees have been paid within the fixed time limit. The present European search report has been drawn up for those parts of the European patent application which relate to the inventions in respect of which search fees have been paid, namely claims:
- ☐ None of the further search fees have been paid within the fixed time limit. The present European search report has been drawn up for those parts of the European patent application which relate to the invention first mentioned in the claims, namely claims:



European Patent
Office

LACK OF UNITY OF INVENTION
SHEET B

Application Number

EP 96 11 3638

The Search Division considers that the present European patent application does not comply with the requirements of unity of invention and relates to several inventions or groups of inventions, namely:

1. Claims: 1-6, 17

Processes for producing liquid crystalline benzothiazole derivatives, liquid crystalline benzothiazoles and charge transport material comprising the compounds produced by the said processes.

2. Claims: 7-16

A liquid crystalline charge transport material and an image device comprising the said material.

ANNEX TO THE EUROPEAN SEARCH REPORT ON EUROPEAN PATENT APPLICATION NO.

EP 96 11 3638

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

08-03-2001

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 498277 A	12-08-1992	JP 2952053 B	20-09-1999
		JP 4253789 A	09-09-1992
		AT 129240 T	15-11-1995
		DE 69205451 D	23-11-1995
		DE 69205451 T	28-03-1996
		US 5194177 A	16-03-1993
DE 4336447 A	27-04-1995	WO 9511890 A	04-05-1995
US 5371232 A	06-12-1994	DE 4227029 A	17-02-1994
		DE 59309603 D	01-07-1999
		EP 0583682 A	23-02-1994
		JP 6184128 A	05-07-1994
US 4861897 A	29-08-1989	NONE	
US 4803241 A	07-02-1989	NONE	
US 4727154 A	23-02-1988	DE 3528032 A	05-02-1987
		DE 3667971 D	08-02-1990
		EP 0214423 A	18-03-1987
		JP 62033164 A	13-02-1987
JP 07070096 A	14-03-1995	JP 2537476 B	25-09-1996
JP 05125076 A	21-05-1993	NONE	
JP 04290885 A	15-10-1992	NONE	
JP 01316386 A	21-12-1989	JP 1838399 C	25-04-1994
		JP 5055513 B	17-08-1993
DE 4429597 A	22-02-1996	WO 9606144 A	29-02-1996
		EP 0776353 A	04-06-1997
		JP 10504311 T	28-04-1998
		US 6036883 A	14-03-2000
		US 5798197 A	25-08-1998
DE 4422332 A	04-01-1996	WO 9600208 A	04-01-1996
		EP 0767776 A	16-04-1997
		JP 10502065 T	24-02-1998
EP 0364185 A	18-04-1990	DE 68911465 D	27-01-1994
		DE 68911465 T	14-04-1994
		GB 2223493 A,B	11-04-1990
		HK 78095 A	26-05-1995

EPO FORM P0459

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82

ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.

EP 96 11 3638

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

08-03-2001

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0364185 A		HK 103192 A	24-12-1992
		JP 2208391 A	17-08-1990
		SG 24695 G	18-08-1995
		SG 106692 G	29-01-1993
		US 5370820 A	06-12-1994
<hr/>			

EPOFORM P459

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82